

**AEROSPACE  
MATERIAL  
SPECIFICATION**

**SAE AMS-B-20148A**

Issued 1998-07  
Cancelled 2008-11

Superseded by AMS4063, AMS4064,  
AMS4255, AMS4256

Brazing Sheet, Aluminum Alloy

RATIONALE

AMS-B-20148A has been designated cancelled and superseded because equivalent technical requirements are provided by the AMS Specifications listed below.

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of November 2008 and has been superseded by the material in the Superseding Specifications List, as applicable. The requirements of the latest issue of the Alloys listed below shall be fulfilled whenever reference is made to the cancelled AMS-B-20148A. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications, noting that it has been superseded by the following list of AMS Specifications.

Cancelled specifications are available from SAE.

AMS-B-20148 Class	Temper	Superseding Specifications
#11	O	AMS4063
#12	O	AMS4064
#11	H12	No similar specification
#11	H14	No similar specification
#12	H12	No similar specification
#12	H14	No similar specification
#21	O	No similar specification
#21	F	AMS4255
#22	O	No similar specification
#22	F	AMS4256
#23	O	No similar specification
#23	F	No similar specification
#24	O	No similar specification
#24	F	No similar specification

SAENORM.COM Click to view the full PDF of AMS-B-20148a

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2008 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this Technical Report, please visit**  
<http://www.sae.org/technical/standards/AMS-B-20148A>

## NOTICE

This document has been taken directly from U.S. Military Specification MIL-B-20148D, Amendment 1, and contains only minor editorial and format changes required to bring it into conformance with the publishing requirements of SAE technical standards. The initial release of this document is intended to replace MIL-B-20148D, Amendment 1. Any part numbers established by the original specification remain unchanged.

The original Military Specification was adopted as an SAE standard under the provisions of the SAE Technical Standards Board (TSB) Rules and Regulations (TSB 001) pertaining to accelerated adoption of government specifications and standards. TSB rules provide for (a) the publication of portions of unrevised government specifications and standards without consensus voting at the SAE Committee level, and (b) the use of the existing government specification or standard format.

Under Department of Defense policies and procedures, any qualifications requirements and associated qualified products lists are mandatory to DOD contracts. Any requirement relating to qualified products lists (QPL's) has not been adopted by SAE and is not part of this technical report.

1. SCOPE:

1.1 Scope:

This specification covers aluminum alloy brazing sheet for use in brazed aluminum joints.

SAENORM.COM : Click to view the full PDF of [ams-b-20148a](#)

## 1.2 Classification:

Aluminum brazing sheet shall be supplied in the following alloys and tempers (see 6.3 for cross reference information). Information pertaining to classes #21 and #22 is contained in Appendix A - see 6.3.1:

Alloy	Tempers
#11 Brazing sheet (3003 Core, 4343 Cladding)	0, H12, H14
#12 Brazing sheet (3003 Core, 4343 Cladding)	0, H12, H14
#21 Brazing sheet (6951 Core, 4343 Clad) (formerly class 3)	Tempers 0, F
#22 Brazing sheet (6951 Core, 4343 Clad) (formerly class 4)	Tempers 0, F
#23 Brazing sheet (6951 Core, 4045 Cladding)	0, F
#24 Brazing sheet (6951 Core, 4045 Cladding)	0, F

Odd numbered sheet is supplied with cladding on one side and even numbered sheet is supplied with cladding on both sides (see Table III).

1.2.1 Form: Brazing sheet is available in either coil or sheet form.

## 2. APPLICABLE DOCUMENTS:

### 2.1 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM B 557 Tension Testing Wrought and Cast Aluminum and Magnesium Alloy Products

ASTM B 660 Standard Practice for Packaging/Packing of Aluminum and Magnesium Products

ASTM E 34 Standard Test Methods for Chemical Analysis of Aluminum and Aluminum Base Alloy

### 2.2 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-129 Marking for Shipment and Storage

### 2.3 ANSI Publication:

Available from American National Standards Institute, 1430 Broadway, New York, NY 10018.

ANSI H35.2 American National Standard Dimensional Tolerances for Aluminum Mill Products

### 2.4 AWS Publication:

Available from American Welding Society, P. O. Box 351040, Miami, FL 33135.

AWS A5.8 Specification for Brazing Filler Metal

## 3. REQUIREMENTS:

### 3.1 Chemical composition:

Material shall conform to the chemical composition detailed in Table I.

### 3.2 Mechanical properties:

Mechanical properties shall conform with those detailed in Table II for the alloy and temper specified. There are no mechanical tests required for the "F" temper.

### 3.3 Cladding thickness:

The cladding bonded to the aluminum core shall have a thickness that meets the requirements of Table III.

### 3.4 Dimensional tolerances:

Sheet shall not vary from specified dimensions by an amount greater than those tolerances specified in ANSI H35.2 for flatness, thickness, width, length and lateral bow for aluminum alloys.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for inspection:

Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

- 4.1.1 Responsibility for compliance: All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.
- 4.2 Sampling:
- 4.2.1 Lot: A lot shall consist of an identifiable quantity of sheet of the same alloy, temper and nominal thickness submitted for inspection at one time.
- 4.2.2 Sampling for chemical analysis:
- 4.2.2.1 Ingot analysis: At least one sample shall be taken from each group of ingots of the same alloy, poured simultaneously from the same source of molten metal by the producer and analyzed to determine conformance with 3.1. Ingots not conforming to the requirements of 3.1 shall be rejected. Complete ingot analysis shall be maintained at the producers facility and shall be available to the procuring activity for review upon request.
- 4.2.2.2 Finished product analysis: Specimens of products shall be analyzed when the compliance of an inspection lot with 3.1 is doubtful. The sampling procedure applied shall comply with the most applicable procedure from among the following:
- 4.2.2.2.1 Ingot identities known: When ingot identities of units comprising an inspection lot are known, one specimen from a unit from the products representing the ingot shall be analyzed in accordance with 4.4.1.
- 4.2.2.2.2 Ingot identities indeterminable: When ingot identities of units comprising an inspection lot can not be determined, the number of specimens taken for analysis in accordance with 4.4.1 shall comply with the following:
- From a lot of flat sheet, one specimen from each 2000 pounds or fraction thereof constituting the lot;
  - From a lot of coils, one specimen from each coil.
- Not more than one specimen shall be taken from the same unit when more than one unit is available.
- 4.2.3 Sampling for mechanical tests: One tension test specimen shall be taken for each 2000 pounds or less of sheet comprising the lot, except that not more than one specimen shall be taken from the same sheet.

- 4.2.4 Sampling for visual and dimensional examination: Each sheet shall be examined to determine conformance to this specification with respect to workmanship and markings. Examinations for dimensions shall be made at specified intervals to ensure conformance to the tolerances specified. When approved by the procuring activity, the producer may use a system of statistical quality control for dimensional, marking and workmanship examinations.

TABLE I. Chemical composition 1/ 2/

Elements	#11 and #12 Brazing Sheet		#23 and #24 Brazing Sheet	
	Core (3003)	Cladding (4343)	Core (6951)	Cladding (4045)
Silicon	0.6	6.8 - 8.2	0.2 - 0.5	9.0 - 11.0
Iron	0.7	0.8	0.8	0.8
Copper	0.05 - 0.2	0.25	0.15 - 0.4	0.3
Manganese	1.0 - 1.5	0.1	0.1	0.05
Magnesium	----	----	0.4 - 0.8	0.05
Zinc	0.1	0.2	0.2	0.1
Other elements				
Each	0.05	0.05	0.05	0.05 <sup>3/</sup>
Total <sup>4/</sup>	0.15	0.15	0.15	0.15
Aluminum	Remainder	Remainder	Remainder	Remainder

- 1/ Analysis shall routinely be made only for the elements specifically mentioned in Table I. If, however, the presence of other elements is indicated or suspected in the amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of specified limits.
- 2/ Composition is maximum weight percent unless shown as a range.
- 3/ Also 0.20 percent maximum titanium.
- 4/ The sum of those "Other elements" 0.010 percent or more each, expressed to the second decimal before determining the sum.

TABLE II. Mechanical properties

Class	Temper	Thickness (inches)	Tensile strength		Elongation In 2 Inches Minimum (percent) <sup>1/</sup>
			Minimum (lbf/in <sup>2</sup> )	Maximum (lbf/in <sup>2</sup> )	
#11 and #12	0	0.006-0.007	---	20000	12
		0.008-0.012	---	20000	15
		0.013-0.031	---	20000	18
		0.032-0.050	---	20000	20
		0.051-0.249	---	20000	23
	H12	0.019-0.050 0.051-0.249	17000 17000	23000 23000	4 6
H14	0.019-0.050 0.051-0.249	20000 20000	26000 26000	3 5	
#23 and #24	0	0.020-0.031	---	21000	18
		0.032-0.050	---	21000	20
		0.051-0.249	---	21000	23

<sup>1/</sup> Not required for material 1/2 inch or less in width.

#### 4.3 Examination:

- 4.3.1 Visual and dimensional examination: Each sample sheet selected in accordance with 4.2.4 shall be examined visually and dimensionally to verify conformance to this specification.
- 4.3.2 Preservation, packaging, packing and marking for shipment: The preservation, packaging, packing and marking of shipment shall be examined to determine compliance with the requirements of Section 5.

#### 4.4 Test procedures:

- 4.4.1 Chemical analysis: Chemical analysis shall be made by the wet chemical method in accordance with ASTM E 34, by spectrographic or other analytical method approved by the procuring activity.
- 4.4.2 Mechanical properties:
- 4.4.2.1 Test specimens: Tension test specimens shall conform to ASTM B 557. Sheet less than 3/4 inch in width shall be tested in full section. Test specimens shall be taken parallel to the direction of finish rolling for #11 and #12 brazing sheet and perpendicular to the direction of finish rolling for #23 and #24 brazing sheet.

4.4.2.2 Tension test: Tension tests shall conform with the requirements of ASTM B 557.

4.5 Cladding thickness:

If a question arises concerning the uniformity of cladding on the finished product, not fewer than three transverse samples, approximately 3/4 inch in length, shall be mounted to expose an edge perpendicular to the plane of the sample and polished for microscopic examination. After etching with Keller's etch or other suitable etch to differentiate between core and cladding, each specimen shall be examined at a magnification of 100X. The maximum and minimum cladding thickness shall be measured in each of 5 fields approximately 1/10 inch apart along each clad side of the exposed edge of each mounted specimen. The mean of the 10 thickness measurements on each side of the exposed edge of each mounted specimen is the mean cladding thickness for that side.

4.6 Rejection and retest:

Unless otherwise specified, failure of a specimen to meet a test requirement shall be cause for rejection of the lot. A retest consisting of two specimens from the original sample to replace each failed specimen may be performed. If one of the retest specimens fails, the lot shall be rejected with no further testing permitted.

5. PACKAGING:

5.1 Preservation, packaging, packing and marking:

All sheets shall be preserved, packaged, packed and marked in accordance with the requirements of ASTM B 660. Unless otherwise specified, material shall be preserved, packaged, packed and marked in accordance with Level C.

5.2 Marking:

In addition to any special or other identification marking required by the contract (see 6.1), each sheet shall be marked in accordance with MIL-STD-129.

5.3 Packaging inspection:

All packaging requirements shall be inspected in accordance with 4.3.2 to ensure compliance.

6. NOTES:

6.1 Ordering data:

Procurement documents shall specify the following:

- a. Title, number and date of this specification.
- b. Alloy, temper and form required (see 1.2).
- c. Length, width and thickness required (see 3.4).
- d. Levels of preservation, packaging, packing and marking, if other than Level C (see 5.1).

## 6.2 General notes:

- 6.2.1 Numbers 11, 12, 21 and 22 brazing sheet, after heating to brazing temperatures, will be fully annealed regardless of the condition in which it was originally supplied. The tensile strength may be expected to vary between 14500 to 20000 pounds per square inch. For this reason, brazing sheet should not be ordered in any temper other than annealed unless very little or no forming is necessary and the higher tensile strength of the alloy is of some particular advantage in the use of the material subsequent to brazing.
- 6.2.2 Numbers 21, 22, 23, 24 brazing sheet have an alloy core that responds to heat treatment. On cooling in still air from the brazing temperature, tensile strengths of approximately 23000 pounds per square inch may be expected. A more rapid cooling rate, as in as air blast, may produce tensile strengths of approximately 27000 pounds per square inch. Somewhat higher values are realized for more rapid quenching rates, and aging for 8 hours at 350°F may be expected to produce further increases in tensile strength to approximately 35000 pounds per square inch.
- 6.2.3 Aluminum brazing sheet clad on one side only should be ordered whenever practicable. Brazing sheet clad on both sides should only be used when the joint or part necessitates the flowing of the brazing material into the joint from both side, or when there are joints on both faces of a plate. It should also be noted that aluminum clad materials conforming to QQ-A-250/3, QQ-A-250/5, QQ-A-250/13, QQ-A-250/15 and QQ-A-250/18 are not intended for nor are suitable as "brazing sheet".

## 6.3 Cross reference information:

MIL-B-20148C	Class 1	Class 2	Class 5	Class 6
MIL-B-20148D	#11	#12	#23	#24

- 6.3.1 Classes 3 and 4 of MIL-B-20148C have been deleted from this revision due to the absence of any domestic producers of these particular alloys. The information pertaining to classes 3 and 4 of Revision C has been placed in Appendix A. When classes 3 and 4 (now 21 and 22) are required, the information in Appendix A, or portions thereof, shall be considered additional requirements when so directed by the Contracting Officer.
- 6.3.2 Classes 7 and 8 of MIL-B-20148C have been deleted from this revision. AWS A5.8 Classes BA1Si-2 and BA1Si-4 may be used in lieu of Class 7 and 8, respectively.

## 6.4 Subject term (keyword) listing:

Aluminum  
 Brazing  
 Sheet, aluminum  
 Sheet, brazing

TABLE III. Cladding thickness

Class	Total Thickness of Composite Product (inches) <sup>1</sup>	Number of Sides Clad	Thickness of Each Cladding Plate, nominal (Percent of Total Thickness)	Minimum Mean Thickness of cladding on finished sheets (Percent of Total Thickness)	Maximum Mean Thickness of cladding on finished sheets (Percent of Total Thickness)
#11	T ≤ 0.063	One	10	8	12
	T ≥ 0.064	One	5	4	8
#12	T ≤ 0.063	Both	10	8	12
	T ≥ 0.064	Both	5	4	8
#23	T ≤ 0.090	One	10	8	12
	T ≥ 0.091	One	5	4	8
#24	T ≤ 0.090	Both	10	8	12
	T ≥ 0.091	Both	5	4	8

<sup>1</sup>/ T = Total Thickness of Composite Material.