

SAE-AMS-QQ-A-200/15

ADOPTION NOTICE

SAE-AMS-QQ-A-200/15, "Aluminum Alloy Bar, Rod, and Shapes, Extruded, 7075-T76 Improved Exfoliation Resistance", was adopted on 30-JUN-98 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Industrial Supply Center, 700 Robbins Avenue, Philadelphia, PA 19111-5096. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

**Custodians:**  
Army - MR  
Navy - AS  
Air Force - 11  
DLA - IS

**Adopting Activities:**  
DLA - IS  
(Project 9530-0570-014)

SAENORM.COM : Click to view the full PDF of amsqqq-a-200-15

FSC 9530

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

**SAE** The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space®  
**INTERNATIONAL**

400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE MATERIAL SPECIFICATION

**SAE**

AMS-QQ-A-200/15

Issued

JUL 1997

Submitted for recognition as an American National Standard

## ALUMINUM ALLOY BAR, ROD, AND SHAPES, EXTRUDED, 7075-T76 IMPROVED EXFOLIATION RESISTANCE

UNS A97075

### NOTICE

This document has been taken directly from Federal Specification QQ-A-200/15B and contains only minor editorial and format changes required to bring it into conformance with the publishing requirements of SAE technical standards.

The original Federal Specification was adopted as an SAE standard under the provisions of the SAE Technical Standards Board (TSB) Rules and Regulations (TSB 001) pertaining to accelerated adoption of government specifications and standards. TSB rules provide for (a) the publication of portions of unrevised government specifications and standards without consensus voting at the SAE Committee level, (b) the use of the existing government specification or standard format, and (c) the exclusion of any qualified product list (QPL) sections.

The complete requirements for procuring aluminum alloy 7075-T76 bar, rod, and shapes extruded described herein shall consist of this document and the latest issue of AMS-QQ-A-200.

#### 1. SCOPE AND CLASSIFICATION:

##### 1.1 Scope:

This specification covers the specific requirements for aluminum alloy 7075-T76 bar, rod, and shapes produced by extrusion (See AMS-QQ-A-200/11 for specific requirements for 7075 extrusions in other tempers).

##### 1.2.1 Tempers: Bar, rod, and shapes are classified in the following tempers as specified (See 6.2): T76, T76510, or T76511. Definitions of tempers are specified in AMS-QQ-A-200.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1997 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:

(412) 772-7154  
(412) 776-4970

FAX: (412) 776-0243  
FAX: (412) 776-0790

2. APPLICABLE DOCUMENTS:

See AMS-QQ-A-200.

3. REQUIREMENTS:

3.1 Chemical Composition:

The chemical composition shall conform to the requirements specified in Table I.

TABLE I. Chemical Composition 1/

Element	Percent	
	Minimum	Maximum
Copper	1.2	2.0
Magnesium	2.1	2.9
Manganese	-	0.30
Chromium	0.18	0.28
Titanium	-	0.20
Iron	-	0.50
Silicon	-	0.40
Zinc	5.1	6.1
Other Elements, each	-	0.05
Other Elements, total 2/	-	0.15
Aluminum	Remainder	

1/ Analysis shall routinely be made only for the elements specifically mentioned in Table I. If, however, the presence of other elements is indicated or suspected in amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of specified limits.

2/ The sum of those "Others" metallic elements 0.010 percent or more each, expressed to the second decimal before determining the sum.

AMS-QQ-A-200/15

SAE

AMS-QQ-A-200/15

3.2 Mechanical Properties:

Mechanical properties of as-supplied material in the longitudinal (extrusion) direction shall conform to property requirements specified in Table II, except as exempted from elongation requirements by AMS-QQ-A-200.

TABLE II. Mechanical Properties

Temper	Specified Thickness, (bar and shapes); diameter, rod Inches	Area Square Inches	Ultimate Tensile Strength minimum ksi	Yield Strength at 0.2 percent Offset or at extension indicated		Elongation in 2 inches or 4 times specimen diameter minimum percent
				minimum ksi	Extension under load inch per inch	
All (T76, T76510, and T76511)	up thru 0.049	All	73.0	63.0	0.0082	7
	0.050 - 0.124	All	74.0	64.0	0.0082	7
	0.125 - 0.249	up thru 20	74.0	64.0	0.0082	7
	0.250 - 0.499	up thru 20	75.0	65.0	0.0084	7
	0.500 - 1.000	up thru 20	75.0	65.0	0.0084	7
	1.001 - 2.000	up thru 20	75.0	65.0	0.0084	7
	2.001 - 3.000	up thru 20	74.0	64.0	0.0082	7
	3.001 - 4.000	up thru 20	74.0	63.0	0.0082	7

3.3 Internal Defects:

When specified (See 6.2), rod, bar, and shapes shall be ultrasonically inspected (See AMS-QQ-A-200). Acceptance limits shall be as specified in Table III. All extrusions in the inspection lot shall be inspected.

AMS-QQ-A-200/15

SAE

AMS-QQ-A-200/15

TABLE III. Ultrasonic Discontinuity Acceptance Limits 1/, 2/

Thickness (bar and shapes), inches <u>3/</u>	Maximum Weight of Piece (pounds)	Maximum Width to Thickness Ratio	Discontinuity Class <u>4/</u>
0.500 - 1.499	600	10 to 1	B
1.500 and over	600	10 to 1	A

1/ Discontinuities in excess of those listed in Table III may be allowed subject to approval of the procuring activity, if it is established that they will be removed by machining or that they are in noncritical areas.

2/ Requirements for ultrasonic inspection for sizes, maximum weights, and discontinuity classes differing from those shown in Table III and for rod shall be specified in the contract provided the techniques and standards are agreed to by the procuring activity and the contractor (See 6.2).

3/ For thickness of a shape, see definition for shape in AMS-QQ-A-200.

4/ Discontinuity class limits are defined in MIL-STD-2154.

3.4 Resistance to Exfoliation Corrosion and Stress-Corrosion Cracking:

3.4.1 Exfoliation Corrosion: Material, tested in accordance with 4.2.4, shall not show exfoliation corrosion equivalent to or in excess of that depicted in Figure 2 of ASTM G 34-72 for category B. The frequency of tests shall be in accordance with AMS-QQ-A-200.

3.4.2 Stress-Corrosion Cracking: Extrusions, 0.750-inch and over in thickness, shall exhibit no susceptibility to stress-corrosion cracking under the conditions of the test specified in 4.2.5. The frequency of tests shall be in accordance with AMS-QQ-A-200.

3.4.3 Lot Acceptance Control Criteria: Resistance to exfoliation corrosion and stress-corrosion cracking for each inspection lot of material shall be determined by the following control criteria (See 4.1.2 and 4.2.6).

Determine electrical conductivity and mechanical properties.

If the conductivity is 38.0 percent International Annealed Copper Standards (IACS) or higher, and the tensile properties meet the minimum limits specified herein, the material is acceptable.

If the conductivity is at least 36.0 percent IACS but less than 38.0 percent IACS, and the tensile properties meet the limits specified herein, the material shall either be tested as specified in 4.2.4 or be reprocessed.

If the conductivity is below 36.0 percent IACS, the material is not acceptable and must be reprocessed.