



# AEROSPACE MATERIAL SPECIFICATION

AMS-QQ-A-250/14

REV. B

Issued 1997-08  
Noncurrent 2007-04  
Reaffirmed 2013-05  
Stabilized 2014-02

Superseding AMS-QQ-A-250/14A

Aluminum Alloy 7178, Plate and Sheet  
(Composition similar to UNS A97178)

## RATIONALE

AMS-QQ-A-250/14B has been designated stabilized because alloy 7178 is not recommended for new designs.

## STABILIZATION NOTICE

AMS-QQ-A-250/14B has been declared "STABILIZED" by AMS Committee D and AMS does not recommend its use for new design due to corrosion concerns. The products included in this document may no longer be commercially available. Previously this document was "Non-Current". This document will no longer be updated and may no longer represent standard industry practice. The last technical update of this document occurred in August 1997. Users of this document should refer any certification issues (e.g. exceptions listed on the certification report) to the cognizant engineering organization for their disposition. CAUTION: In many cases the purchaser is not the cognizant engineering organization (i.e. purchaser may be a sub tier supplier).

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
SAE WEB ADDRESS: <http://www.sae.org>

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMSQA250/14B>

## NOTICE

This document has been taken directly from Federal Specification QQ-A-250/14E and contains only minor editorial and format changes required to bring it into conformance with the publishing requirements of SAE technical standards.

The original Federal Specification was adopted as an SAE standard under the provisions of the SAE Technical Standards Board (TSB) Rules and Regulations (TSB 001) pertaining to accelerated adoption of government specifications and standards. TSB rules provide for (a) the publication of portions of unrevised government specifications and standards without consensus voting at the SAE Committee level, (b) the use of the existing government specification or standard format, and (c) the exclusion of any qualified product list (QPL) sections.

The complete requirements for procuring 7178 aluminum alloy plate and sheet described herein shall consist of this document and the latest issue of AMS-QQ-A-250.

## 1. SCOPE AND CLASSIFICATION:

### 1.1 Scope:

This specification covers the specific requirements for 7178 aluminum alloy plate and sheet material; the general requirements are covered in AMS-QQ-A-250.

### 1.2 Classification:

1.2.1 Tempers: The plate and sheet are classified in one of the following tempers as specified (See 6.2): O, T6, T62, T651, or F temper. Definitions of these tempers are specified in AMS-QQ-A-250.

## 2. APPLICABLE DOCUMENTS:

See AMS-QQ-A-250.

SAENORM.COM : Click to view the full PDF of amsqqa250-14b

### 3. REQUIREMENTS:

#### 3.1 Chemical Composition:

3.1.1 The chemical composition shall conform to the requirements specified in Table I.

TABLE I. Chemical Composition <sup>1/</sup>

	Percent	
	Minimum	Maximum
Zinc	6.3	7.3
Magnesium	2.4	3.1
Copper	1.6	2.4
Chromium	0.18	0.35
Iron	-	0.50
Silicon	-	0.40
Manganese	-	0.30
Titanium	-	0.20
Other Elements, each	-	0.05
Other Elements, total		0.15
Aluminum	Remainder	

<sup>1/</sup> Analysis shall routinely be made only for the elements specifically mentioned in Table I. If, however, the presence of other elements is indicated or suspected in amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of specified limits.

#### 3.2 Mechanical Properties:

3.2.1 Mechanical Properties of Material as Supplied: The mechanical properties perpendicular to the direction of final rolling, except for material under 9 inches in width, shall conform to the requirements of Table II for the temper specified. For material under 9 inches in width, the mechanical properties parallel to the direction of final rolling shall conform to the requirements of Table II for the temper specified.

TABLE II. Mechanical Properties

Temper	Thickness	Tensile Strength minimum	Yield Strength at 0.2 percent Offset minimum	Elongation in 2 in. or 4 times D <u>1/</u> , <u>2/</u> minimum
	Inches	ksi	ksi	percent
O	0.015 thru 0.499	<u>3/</u> 40.0	<u>3/</u> 21.0	10
	0.500	<u>3/</u> 40.0	-	10
T6 and	0.015 thru 0.044	83.0	72.0	7
T62 <u>4/</u>	0.045 thru 0.249	84.0	73.0	8
T651 and T62 <u>4/</u>	0.250 thru 0.499	84.0	73.0	8
	0.500 thru 1.000	84.0	73.0	6
	1.001 thru 1.500	84.0	73.0	4
	1.501 thru 2.000	80.0	70.0	3
F	All	<u>5/</u>	<u>5/</u>	<u>5/</u>

1/ Not required for material 1/2 inch or less in width.

2/ D represents specimen diameter.

3/ Maximum.

4/ Material in the T62 temper is not available from material producers.

5/ No requirements.

3.2.2 Mechanical Properties After Heat Treatment: In addition to conforming to the requirements of 3.2.1, material in the annealed (O) and the as-fabricated (F) tempers shall, after proper solution heat-treatment and aging, also conform to the requirements of Table II for the T6 and T62 tempers. Material as received in the T6 and T651 tempers shall, after proper re-solution heat-treatment and aging, be capable of conforming to the requirements specified in Table II for the T6 and T62 tempers.

### 3.3 Internal Defects:

When specified (See 6.2), plate shall be ultrasonically inspected (See AMS-QQ-A-250). Acceptance limits shall be as specified in Table III.