

AEROSPACE MATERIAL SPECIFICATION

SAE AMS-QQ-A-250/22

REV. B

Issued	1997-08
Revised	1998-09
Noncurrent	2007-03
Reaf Nonc	2012-04

Superseding AMS-QQ-A-250/22A

Aluminum Alloy, 7178-T76, Alclad Plate and Sheet,
Improved Exfoliation Resistant

UNS A87178

RATIONALE

AMS-QQ-A-250/22B has been reaffirmed to comply with the SAE five-year review policy.

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of March 2007. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those specifications which have previously been widely used and which may be required for production or processing of existing designs in the future. The Aerospace Materials Division, however, does not recommend these specifications for future use in new designs. "NONCURRENT" specifications are available from SAE upon request.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMSQQA250/22B>**

NOTICE

This document has been taken directly from Federal Specification QQ-A-250/22A and contains only minor editorial and format changes required to bring it into conformance with the publishing requirements of SAE technical standards.

The original Federal Specification was adopted as an SAE standard under the provisions of the SAE Technical Standards Board (TSB) Rules and Regulations (TSB 001) pertaining to accelerated adoption of government specifications and standards. TSB rules provide for (a) the publication of portions of unrevised government specifications and standards without consensus voting at the SAE Committee level, (b) the use of the existing government specification or standard format, and (c) the exclusion of any qualified product list (QPL) sections.

The complete requirements for procuring 7178 aluminum alloy alclad plate and sheet for improved exfoliation resistance described herein shall consist of this document and the latest issue of AMS-QQ-A-250.

SAENORM.COM : Click to view the full PDF of amsqq250_22b

1. SCOPE AND CLASSIFICATION:

1.1 Scope:

This specification covers the specific requirements for improved exfoliation resistant alclad aluminum alloy 7178-T76 sheet and -T7651 plate. The general requirements are covered in AMS-QQ-A-250. The plate and sheet covered by this specification shall be an integral composite product consisting of a heat-treatable aluminum alloy (7178) core with thin layers of an aluminum alloy (7072) anodic to the core and of approximately equal thickness, bonded to both surfaces

1.2 Classification:

Sheet shall be furnished only in the T76 temper and plate shall be furnished only in the T7651 temper, as specified (See 6.2). Definitions of these tempers are in accordance with AMS-QQ-A-250 and as follows:

T76 - Solution heat-treated and artificially aged sufficient to produce required improved resistance to exfoliation and stress-corrosion cracking.

T7651 - Solution heat-treated, stress relieved by stretching to produce a permanent set of 2 percent nominal but not less than 1-1/2 nor more than 3 percent, and artificially aged sufficient to produce improved resistance to exfoliation and stress-corrosion cracking. Plate shall receive no further straightening after stretching.

2. APPLICABLE DOCUMENTS:

See AMS-QQ-A-250.

3. REQUIREMENTS:

3.1 Chemical Composition:

The chemical composition of the core ingots or slabs and of the cladding plates used for the manufacture of the clad plates and sheets shall conform to the requirements specified in Table I for core and cladding, respectively.

TABLE I. Chemical Composition ^{1/}

Element	Composition			
	Core (7178) Percent		Cladding (7072) Percent	
	Minimum	Maximum	Minimum	Maximum
Zinc	6.3	7.3	0.8	1.3
Magnesium	2.4	3.1	---	0.10
Copper	1.6	2.4	---	0.10
Chromium	0.18	0.35	---	---
Manganese	---	0.30	---	0.10
Iron	---	0.50	---	<u>2/</u>
Silicon	---	0.40	---	<u>2/</u>
Titanium	---	0.20	---	---
Other Elements, each	---	0.05	---	0.05
Other Elements, total	---	0.15	---	0.15
Aluminum	Remainder		Remainder	

^{1/} Analysis shall routinely be made only for the elements specifically mentioned in Table I. If, however, the presence of other elements is indicated or suspected in amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of specified limits.

^{2/} Iron plus silicon 0.7 percent maximum.

3.2 Mechanical Properties:

Mechanical properties perpendicular to the direction of final rolling, except for material under 9 inches in width, shall conform to the requirements of Table II for the temper specified. For material under 9 inches in width, the mechanical properties parallel to the direction of final rolling shall conform to the requirements of Table II for the temper specified.

TABLE II. Mechanical Properties

Temper	Thickness Inches	Tensile Strength, ksi minimum	Yield Strength at 0.2 percent Offset, ksi minimum	Elongation in 2 inches or 4 times D. percent mini- mum <u>2/</u> <u>3/</u>
T76 <u>1/</u>	0.045-0.187	71.0	60.0	8
	0.188-0.249	73.0	61.0	8
T7651	0.250-0.499	72.0	60.0	8
	0.500-1.000	73.0	62.0	6

1/ Mechanical property requirements for sheet under 0.045 inch in thickness are subject to inquiry.

2/ Not required for material 1/2-inch and under in width.

3/ D represents specimen diameter.

3.3 Cladding Thickness:

3.3.1 Thickness of Cladding Plates: The aluminum alloy (7072) plates that are bonded to the two sides of the aluminum alloy (7178) ingot or slab to form a composite that is to be rolled to the finished thickness shall each have a thickness not less than that specified in Table III.

3.3.2 Average Thickness of Cladding: When specified (See 6.2), the average cladding thickness of the finished sheet or plate shall be determined. Samples, examined in accordance with AMS-QQ-A-250, shall show an average of cladding on each side as specified in Table III.

TABLE III. Cladding Thickness

Thickness of Finished Plate or Sheet in inches	Nominal Cladding Thickness per Side; percent of Composite Thickness	Average Minimum Cladding Thickness per Side on Finished Plate or Sheet; percent of plate or sheet thickness
Under 0.063	4.0	3.2
0.063 thru 0.187	2.5	2.0
0.188 and over <u>1/</u>	1.5	1.2

1/ For plate 0.500 inch and over, the average cladding thickness per side shall have a maximum value of 3 percent of the plate thickness.

3.4 Exfoliation and Stress-Corrosion Cracking:

Material in the T76 and the T7651 tempers when tested in accordance with 4.2.1 and 4.2.2 shall show neither exfoliation corrosion equivalent to or in excess of that depicted in Figure 2 of ASTM G 34-72 for Category B nor stress-corrosion cracking susceptibility beyond the acceptance criteria detailed in 4.2.2.5.

3.4.1 Lot Acceptance Control Criteria for T76 and T7651 Tempers: Susceptibility to exfoliation and stress-corrosion cracking for each inspection lot of T76 and T7651 temper material shall be determined by the following control criteria (See 4.1.2 and 4.2.2):

3.4.1.1 Determine mechanical properties and electrical conductivity.

3.4.1.2 If the conductivity is 38 percent IACS or higher, and the tensile properties meet the minimum limits herein, the material is acceptable.

3.4.1.3 If the conductivity is at least 35 percent IACS but less than 38 percent IACS, the material shall be tested as specified or reprocessed.

3.4.1.4 If the conductivity is below 35 percent IACS, the material is not acceptable and must be reprocessed.

3.5 Internal Defects:

Unless otherwise specified (See 6.2), plate shall be ultrasonically inspected (See AMS-QQ-A-250). Acceptance limits shall be as specified in Table IV.

TABLE IV. Ultrasonic Discontinuity Acceptance Limits ^{1/}

Thickness Inches	Maximum Weight per Piece pounds	Discontinuity Class ^{2/}
0.500 thru 1.000	2,000	B

^{1/} Discontinuities in excess of those listed in Table IV may be allowed, subject to approval of the procuring activity, if it is established that they will be removed by machining or that they are in non-critical areas.

^{2/} The discontinuity class limits are defined in MIL-I-8950.

3.6 Marking:

In addition to the marking required in FED-STD-184, plate and sheet shall be identified by an inspection lot number in at least one location on each piece.

4. QUALITY ASSURANCE PROVISIONS:

See AMS-QQ-A-250 and the following:

4.1 Sampling:

4.1.1 For Exfoliation and Stress-Corrosion Cracking Tests: Two samples shall be taken for each 4,000 pounds or less of the first three production lots for each size range of sheet and plate listed in Table II. Thereafter, surveillance testing shall be performed on at least one sample per month for each size range of sheet and plate produced during that month which had previously been produced with acceptable exfoliation resistance. The surveillance test sample shall be taken from an inspection lot which has met the requirements of 3.4.1.2. Samples as above shall be taken for stress-corrosion cracking test when thickness permit (See 4.2.2).

4.1.2 For Mechanical Property and Conductivity Tests: Sampling shall be in accordance with AMS-QQ-A-250 for mechanical property tests. Mechanical properties and conductivities shall be determined on the same samples (See 4.2.3). Conductivity shall be determined prior to testing for mechanical properties.

4.2 Tests:

4.2.1 Exfoliation Corrosion Test: Test shall be performed in accordance with ASTM G 34-72. Full thickness specimens of sheet and plate large enough to provide visual assessment of attack may be used; however, for all materials 0.100 inch or more in thickness, 10 percent of the thickness shall be removed by machining one surface. The machined surface shall be evaluated.

4.2.2 Stress-Corrosion Cracking Test: Stress-corrosion cracking tests shall be performed on plate 0.75 inch and over in thickness as follows:

4.2.2.1 Specimens: Specimens shall be selected in a manner such as to permit application of the specific tension stress in the short-transverse direction. Specimens shall be C-Rings as described in Method 823 of FED-STD-151 or in ASTM G 38.

4.2.2.2 Exposure Period: Exposure shall be for thirty (30) days.

4.2.2.3 Tension Stress: The tensile stress applied in the short-transverse direction (perpendicular to grain flow) shall be 25.0 ksi and the specimen shall be held at constant strain.

- 4.2.2.4 Exposure Procedure: The stressed specimen shall be exposed to a 3.5 percent salt solution prepared by dissolving reagent grade sodium chloride (NaCl) in distilled or deionized ASTM D 1193, Type II, water. The pH of the solution shall be 6.4 to 7.2. The solution temperature shall be $75\text{ }^{\circ}\text{F} \pm 2$, air temperature shall be $80\text{ }^{\circ}\text{F} \pm 2$, and with a relative humidity of $45\text{ percent} \pm 6$. The alternate immersion cycle shall consist of 10 minutes immersion in solution and 50 minutes in air, with sufficient circulation to dry the specimens slowly before the next immersion.
- 4.2.2.5 Stress-Corrosion Test Results: After 30 day exposure, the specimen shall exhibit no visual evidence of stress-corrosion cracking. Any highly directional attack which is suspected of concealing a stress-corrosion crack shall be cross sectioned and examined metallographically. An example of stress-corrosion cracking is shown in Figure 1. Figure 2 illustrates pitting type attack which does not constitute failure.
- 4.2.3 Electrical Conductivity Tests: The conductivity shall be determined by taking three electrical conductivity readings at random on each sample. For thicknesses under 0.100 inch, the conductivity shall be determined on the surface after removal of the cladding. For thicknesses of 0.100 inch and over, the conductivity shall be determined on the machined surface after machining one surface of the sample to a depth of approximately 10 percent of the product thickness. The surface machining may be accomplished by chemical milling. The average of three readings shall be used as the conductivity acceptance criteria of 3.4.1.

4.3 Records:

The producer shall maintain records of the performance of all inspection lots sampled and tested. Upon request of the procuring activity, such records shall be made available. These records shall be maintained for not less than one year after completion of the contract or purchase order.

5. PREPARATION FOR DELIVERY:

See AMS-QQ-A-250.

6. NOTES:

6.1 Intended Use:

This alloy is intended for use where high strength is required and where exfoliation and stress-corrosion resistance superior to 7178-T6 is required in high performance military aircraft.