

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS-QQ-A-250/9A

Issued AUG 1997
Revised SEP 2006

Superseding AMS-QQ-A-250/9

Aluminum Alloy 5456, Plate and Sheet

(Composition similar to UNS A95456)

RATIONALE

AMS-QQ-A-250/9A updates the temper designations for currently produced materials and supersedes the H321 temper with marine grade material in accordance with ASTM B 928.

NOTICE

The original issue of this document was taken directly from Federal Specification QQ-A-250/9F and contains only minor editorial and format changes required to bring it into conformance with the publishing requirements of SAE technical standards. AMS-QQ-A-250/9A updates the temper designations for currently produced materials and supersedes the H321 temper with marine grade material in accordance with ASTM B 928.

The original Federal Specification was adopted as an SAE standard under the provisions of the SAE Technical Standards Board (TSB) Rules and Regulations (TSB 001) pertaining to accelerated adoption of government specifications and standards. TSB rules provide for (a) the publication of portions of unrevised government specifications and standards without consensus voting at the SAE Committee level, (b) the use of the existing government specification or standard format, and (c) the exclusion of any qualified product list (QPL) sections.

The complete requirements for procuring 5456 aluminum alloy plate and sheet described herein shall consist of this document and the latest issue of AMS-QQ-A-250.

SAENORM.COM : Click to view the full PDF of AMS-QQ-A-250_9a

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

1. SCOPE AND CLASSIFICATION

1.1 Scope

This specification covers the specific requirements for 5456 aluminum alloy plate and sheet; the general requirements are covered in AMS-QQ-A-250.

1.2 Classification

1.2.1 Tempers

The plate and sheet are classified in one of the following tempers as specified (See 6.2). Definitions of these tempers are specified in AMS-QQ-A-250.

O - Annealed

H112 - As rolled, properties as specified in Table 2.

H321 - Strain-hardened one-quarter hard (hot rolled) temper and then stabilized. The requirements of ASTM B 928 shall apply and shall supersede the requirements herein. Alloy 5456 temper H321 per AMS-QQ-A-250/9 is superseded by Alloy 5456 temper H321 of ASTM B 928.

H323 - Cancelled.

H343 - Cancelled.

2. APPLICABLE DOCUMENTS

See AMS-QQ-A-250.

3. REQUIREMENTS

3.1 Chemical Composition

3.1.1 The chemical composition shall conform to the requirements specified in Table 1.

TABLE 1 - CHEMICAL COMPOSITION 1/

Element	Percent Minimum	Percent Maximum
Magnesium	4.7	5.5
Manganese	0.50	1.0
Chromium	0.05	0.20
Iron + Silicon	--	0.40
Zinc	--	0.25
Titanium	--	0.20
Copper	--	0.10
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

1/ Analysis shall routinely be made only for the elements specifically mentioned in Table 1. If, however, the presence of other elements is indicated or suspected in amounts greater than the specified limits, further analysis shall be made to determine that these elements are not present in excess of specified limits.

3.2 Mechanical Properties

3.2.1 Mechanical Properties of Material as Supplied

The mechanical properties parallel to the direction of final rolling shall conform to the requirements of Table 2 for the temper specified.

TABLE 2 - MECHANICAL PROPERTIES (SEE 6.4)

Temper	Thickness Inches	Tensile	Tensile	Yield Strength	Yield Strength	Elongation in 2 in.
		Strength Minimum ksi	Strength Maximum ksi	at 0.2 percent Offset Minimum ksi	at 0.2 percent Offset Maximum ksi	or 4 times D 1/ 2/ Minimum Percent
O	0.051 thru 1.500	42.0	53.0	19.0	30.0	16
	1.501 thru 3.000	41.0	52.0	18.0	30.0	16
	3.001 thru 5.000	40.0	-	17.0	-	14
	5.001 thru 7.000	39.0	-	16.0	-	14
	7.001 thru 8.000	38.0	-	15.0	-	12
H112	0.250 thru 1.500	42.0	-	19.0	-	12
	1.501 thru 3.000	41.0	-	18.0	-	12

1/ Not required for material 1/2 inch or less in width.

2/ D represents specimen diameter.

4. QUALITY ASSURANCE PROVISIONS

See AMS-QQ-A-250.

5. PREPARATION FOR DELIVERY

See AMS-QQ-A-250.

6. NOTES

6.1 Intended Use

Sheet and plate of aluminum alloy 5456 are used for applications requiring weldable, moderate strength, nonheat-treatable alloy.

6.2 Ordering Data

Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

AMS-QQ-A-250/9A

Form and temper required (See 1.2.1)

Dimensions required

Requirements for sizes not specifically covered (See AMS-QQ-A-250)

Selection of applicable levels of preservation, packaging, and packing required if other than Level C (See AMS-QQ-A-250).

6.3 Product produced and marked to the requirements of AMS-QQ-A-250/9 also meets the requirements of QQ-A-250/9F. Product produced and marked to the requirements of QQ-A-250/9F also meets the requirements of AMS-QQ-A-250/9.

6.4 The properties listed in 3.2.1 are exactly the same as were in QQ-A-250/9, Revision F. These properties have not been substantiated in accordance with the AMS Manual for Preparation of Aerospace Specifications.