

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS-QQ-C-320A

Issued JUL 2000
Cancelled JUL 2007

Superseded by AMS 2460

Chromium Plating (Electrodeposited)

RATIONALE

AMS-QQ-C-320 has been designated cancelled and superseded because equivalent technical requirements are provided by AMS 2460.

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of July, 2007, and has been superseded by AMS 2460, Plating Chromium. The requirements of the latest issue of AMS 2460 shall be fulfilled whenever reference is made to the cancelled AMS-QQ-C-320. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications, noting that it has been superseded by AMS 2460.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of AMS-QQ-C-320a

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

SAENORM.COM : Click to view the full PDF of amsqqc320a

Issued JUL 2000
Cancelled JUL 2007

Superseded by AMS 2460

Chromium Plating (Electrodeposited)

NOTICE

This document has been taken directly from U.S. Military Specification QQ-C-320B, Amendment 4 and contains only minor editorial and format changes required to bring it into conformance with the publishing requirements of SAE technical standards. The initial release of this document is intended to replace QQ-C-320B, Amendment 4. Any part numbers established by the original specification remain unchanged.

The original Military Specification was adopted as an SAE standard under the provisions of the SAE Technical Standards Board (TSB) Rules and Regulations (TSB 001) pertaining to accelerated adoption of government specifications and standards. TSB rules provide for (a) the publication of portions of unrevised government specifications and standards without consensus voting at the SAE Committee level, and (b) the use of the existing government specification or standard format.

Under Department of Defense policies and procedures, any qualification requirements and associated qualified products lists are mandatory for DOD contracts. Any requirement relating to qualified products lists (QPL's) has not been adopted by SAE and is not part of this SAE technical document.

SAENORM.COM : Click to view the full PDF of AMS-QQ-C-320A

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org

SAE WEB ADDRESS:

<http://www.sae.org>

1. SCOPE AND CLASSIFICATION:

1.1 Scope:

This specification covers the requirements for electrodeposited chromium plating.

1.2 Classification:

1.2.1 Classes: Electrodeposited chromium plating shall be of the following classes, as specified (see 6.2):

Class 1 - Corrosion protective plating (see 3.3.1)

Class 2 - Engineering plating (see 3.3.2)

1.2.2 Finish: Class 1 plating shall be of the following types of finish, as specified (see 6.2):

Type I - Bright finish

Type II - Satin finish

2. APPLICABLE DOCUMENTS:

The following specifications and standards form a part of this document to the extent specified herein.

2.1 U.S. Government Publications:

Available from DODSSP Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

QQ-N-290 Nickel Plating (Electrodeposited)

MIL-S-5000 Steel, Chrome-Nickel-Molybdenum, (E4340), Bars and Reforging Stock
MIL-S-5002 Surface Treatments and Inorganic Coatings for Metal Surfaces of Weapons Systems

MIL-S-13165 Shot Peening of Ferrous Parts

MIL-R-81841 Rotary Flap Peening of Metal Parts

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes

MIL-STD-1312 Fasteners, Test Methods

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

- ASTM B-487 Measurement of Metal and Oxide Coating Thickness by Microscopic Examination of a Cross Section
- ASTM B-499 Measurement of Coating Thicknesses by the Magnetic Method: Nonmagnetic Coatings on Magnetic Basis Metals
- ASTM B-504 Measuring the Thickness of Metallic Coatings by the Coulometric Method
- ASTM B-556 Thin Chromium Coatings by the Spot Test, Guideline for Measurement of
- ASTM B-578 Measurement of Microhardness of Electroplated Coatings
- ASTM E-8 Tension Testing of Metallic Materials

3. REQUIREMENTS:

3.1 Materials:

The materials used shall be such as to produce platings which meet the requirements of this specification.

3.2 General requirements:

- 3.2.1 High tensile steel parts: Unless otherwise specified (see 6.2), steel parts having an ultimate tensile strength greater than 240,000 psi (1655 MPa) shall not be plated without specific approval of the procuring activity.
- 3.2.2 Stress relief treatment: All steel parts having an ultimate tensile strength of 150,000 psi (1034 MPa) and above, which are machined, ground, cold formed or cold straightened, shall be baked at a minimum of $375 \pm 25^{\circ}\text{F}$ ($191 \pm 14^{\circ}\text{C}$) for three hours or more prior to cleaning and plating for the relief of damaging residual tensile stresses. When peening is required (see 3.3.2.3 and 3.3.2.5), thermal stress relief shall be performed prior to shot or rotary flap peening.
- 3.2.3 Cleaning: Unless otherwise specified (see 6.2), all steel parts shall be cleaned in accordance with MIL-S-5002. Other basis metals shall be cleaned by methods which shall not damage the substrate and shall not interfere with adhesion of the deposit.
- 3.2.4 Plating application: Unless otherwise specified (see 6.2), the plating shall be applied after all basis metal heat treatments and mechanical operations, such as machining, brazing, welding, forming and perforating of the article, have been completed.
- 3.2.5 Underplating: Unless otherwise specified (see 6.2), class 1 plating shall be applied over an intermediate plating of nickel in accordance with QQ-N-290 on steel, zinc and zinc-based alloys or copper and copper-based alloys. Unless otherwise specified (see 6.2), class 2 plating shall be deposited on the basis metal without a preliminary plating of another metal. In no case shall any underplate be substituted for any part of the specified chromium thickness.

- 3.2.6 Embrittlement relief: All coated steel parts having an ultimate tensile strength of 160 ksi and higher (or Rockwell hardness C36 and higher) shall be baked at $375^{\circ} \pm 25^{\circ}\text{F}$ ($191^{\circ} \pm 14^{\circ}\text{C}$), within four hours after plating, in accordance with the following times:

Minimum Baking Times	
Tensile Strength ksi	Time (At Temperature) Hours
160 - 180	3
181 - 220	8
221 and above	12

- 3.2.7 Coverage: Unless otherwise specified (see 6.2), the plating shall cover all surfaces including roots of threads, corners and recesses.
- 3.2.8 Boundaries: Boundaries of class 2 plating which covers only a portion of the surface shall be free from beads, nodules, jagged edges and other irregularities.
- 3.2.9 Finish: For class 1 plating, the finish or luster shall be as specified (see 1.2.3 and 6.2). Type I of class 1 shall be a fully bright finish, smooth, uniform in appearance and free from frosty areas. Type II of class 1 shall be a satin finish, smooth and uniform in appearance. Unless otherwise specified (see 6.2), either a fully bright or a dull matte finish, smooth and free from frosty areas shall be acceptable for class 2 plating finish.
- 3.3 Processing:
- 3.3.1 Class 1 processing: Parts for class 1 deposition shall be plated to specific dimensions as specified (see 3.4.1.1). When specified (see 6.2), parts shall be processed in accordance with procedural instructions for form of chromium deposit (see 6.5).
- 3.3.2 Class 2 processing: Parts for class 2 deposition shall be plated to specific dimensions as specified (see 3.4.2.1). Unless otherwise specified (see 6.2), steel parts shall be processed in accordance with the procedural instructions of the procuring activity as follows:
- 3.3.2.1 Peening: All class 2 plated parts which are designed for unlimited life under dynamic loads, shall be peened in accordance with MIL-S-13165 or MIL-R-81841 prior to plating. Unless otherwise specified in the applicable drawings, the peening shall be accomplished on all surfaces for which the plating is required and on all immediately adjacent surfaces when they contain notches, fillets or other abrupt changes of section size where stress will be concentrated. Plated parts which are subjected to static loads or designed for limited life under dynamic loads or combinations thereof, need not be peened prior to plating, unless specified in the contract, order, or applicable drawing.

3.4 Detail requirements:

3.4.1 Class 1:

- 3.4.1.1 Thickness: Unless otherwise specified (see 6.2), the minimum thickness of class 1 chromium plating shall be 0.00001 inch or 0.01 mil (0.25 micrometre) on all visible surfaces which can be touched by a ball 0.75 inch (19 mm) in diameter. Unless otherwise specified (see 6.2), holes, deep recesses and other openings, bases of angles, and articles with internal threads from which the external environment is completely excluded and where a controlled deposit cannot be normally obtained shall not be subjected to a thickness requirement but shall show evidence of plating. There shall be no bare areas.
- 3.4.1.2 Underplating: Class 1 plating is normally used with an underplate system of nickel or copper. Where such requirements exist (see 3.2.5), the underplate thickness shall be in accordance with QQ-N-290. The thickness of the underplate shall not be used in determination of the specified chromium plating thickness.
- 3.4.1.3 Adhesion: The adhesion of the plating and any underplate shall be such that, when examined at a magnification of approximately 4 diameters, neither the chromium plating nor any electrodeposited underplate(s) shall show separation from the basis metal or from each other at their common interface(s) when subjected to the test described in 4.5.2. The interface between a plating and the basis metal is the surface of the basis metal before plating. The formation of cracks in the plate or the basis metal which does not result in flaking, peeling or blistering of the plating shall not be cause for rejection.

3.4.2 Class 2:

- 3.4.2.1 Thickness: The minimum, maximum or range of thickness for class 2 plating shall be as specified in the contract, purchase order or on the applicable drawing (see 6.2). If a thickness is not specified, the minimum thickness for the finished part shall be 0.002 inch or 2 mils (51 μm). The thickness requirement for class 2 plating shall apply after all metal finishing and post-plating grinding operations have been completed.
- 3.4.2.2 Adhesion: The adhesion of the plating and any underplate shall be such that when examined at a magnification of approximately 4 diameters, neither the plating, nor any electrodeposited underplate shall show separation from the basis metal or from each other at their common interface(s) when subjected to the test described in 4.5.2. The interface between a plating and the basis metal is the surface of the basis metal before plating. The formation of cracks in the basis metal or the plate which do not result in flaking, peeling or blistering of the plate shall not be cause for rejection.
- 3.4.2.3 Hardness: The minimum hardness of a cross-section class 2 plating, when subjected to the microhardness test detailed in 4.5.3, shall be 600 Vickers Hardness Number (VHN) or equivalent if the plating is finished to a semi-bright or matte luster (see 3.2.9). If the plating is finished to a bright or bright pebbly luster, the minimum hardness shall be 850 Vickers Hardness Number (VHN) or equivalent.

3.4.2.4 Porosity: The class 2 plating, by being as free from porosity as possible, shall be capable of protecting the basis metal from corrosion due to pits, pores or cracking. When subjected to the test detailed in 4.5.4, specimens shall show no more than a total of 15 isolated spots or pits, none larger than 1/32 inch (0.79 mm) in diameter, in a total of 150 square inches (967.8 sq. cms) of test area grouped from five or more test pieces; nor more than five isolated spots or pits, none larger than 1/32 inch (0.79 mm) in a total of 30 square inches (193.6 sq. cms) from one or more test pieces, except those areas within 1/16 inch (1.59 mm) from identification markings and contact marks after processing.

3.5 Workmanship:

3.5.1 Basis metal: The basis metal shall be free from visible defects that will be detrimental to the appearance or protective value of the plating. The basis metal shall be subjected to such cleaning and plating procedures as necessary to yield deposits herein specified.

3.5.2 Appearance: The plating shall be smooth, fine grained, adherent, uniform in appearance, free from blisters, pits, nodules, excessive edge build-up and other defects. The plating shall show no indication of contamination or improper operation of equipment used to produce the deposit, such as excessively powdered or darkened plating, build-up and other defects. The size and number of contact marks shall be at a minimum consistent with good practice. The location of contact marks shall be in areas of minimum exposure to service environmental conditions where important to the function of the part. Superficial staining which has been demonstrated as resulting from rinsing or slight discoloration resulting from baking operations to relieve embrittlement, as specified above (see 3.2.6), shall not be cause for rejection. All details of workmanship shall conform to the best practice for high quality plating.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for inspection:

Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the Inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Classification of inspection:

The inspection requirements specified herein are classified as follows:

- a. Production control inspection (see 4.3).
- b. Quality conformance inspection (see 4.4).

4.3 Production control inspection:

- 4.3.1 Control records: When specified in the contract or order (see 6.2), the supplier shall maintain a record of each processing bath, showing all additional chemicals or treatment solutions to the unit, the results of all chemical analyses performed, and the quantity of parts plated during operation. Upon request of the procuring activity, such records as well as reports of the test results shall be made available. These records shall be maintained for not less than one year after completion of the contract or purchase order.
- 4.3.2 Production control: The equipment, procedures and operations employed by a supplier shall be capable of producing high quality electrodeposited platings as specified in this document. When specified by the procuring activity (see 6.2), the supplier, prior to production, shall demonstrate the capability of the process used to show freedom from hydrogen embrittlement damage as indicated by satisfactory behavior of specimens prepared (see 6.2.2) and tested in accordance with 4.3.2.1 to comply to the requirements of MIL-S-5002 for preproduction process qualification.
- 4.3.2.1 Preproduction control: For preproduction control, four round notched steel specimens shall be prepared in accordance with 4.4.4.3 from four individual heats for a total of 16 specimens, using the specified steel alloy for which preproduction examinations of the process is to be demonstrated. Specimens shall be heat treated to the maximum tensile strength representing production usage. The specimens shall be given the same pretreatments and treatments proposed for production. The specimens shall be subject to the test detailed in 4.5.5. The process shall be considered satisfactory if all specimens show no indication of cracks or failure. The test results and production control information shall be submitted to the procuring activity for approval. Until approval has been received, parts shall not be plated.
- 4.3.3 Frequency of tests: To assure continuous control of the process as required by MIL-S-5002 and to prevent detrimental hydrogen embrittlement during production, the satisfactory behavior of specimens prepared and tested in accordance with table I shall be made once each month, or more frequently if required by the procuring activity. The results of tests made to determine conformance of electrodeposited platings to all requirements of this specification are acceptable as evidence of the properties being obtained with the equipment and procedures employed.
- 4.3.4 Production control specimens: Test specimens for production control shall be prepared in accordance with 4.4.4, 4.4.4.1 and 4.4.4.2, as applicable for the thickness, adhesion, hardness and porosity tests detailed in table I. Specimens for the production control embrittlement relief test shall be four round notched steel specimens of alloy steel 4340, conforming to MIL-S-5000, heat treated to the maximum tensile strength from one or more heats, and prepared in accordance with 4.4.4.3.

4.4 Quality conformance inspection:

- 4.4.1 Lot: A lot shall consist of plated articles of the same basis metal composition, class, deposition form and finish, plated and treated under the same conditions and approximately the same size and shape submitted for inspection at one time.
- 4.4.2 Sampling for visual examination and nondestructive tests: Sampling for visual examination and nondestructive tests shall be conducted as directed by the procuring activity (see 6.2) in accordance with MIL-STD-105 or using table II. A sample of coated parts or articles shall be drawn by taking at random from each lot the number of articles in accordance with MIL-STD-105, Level II, Acceptable Quality Level (AQL) 1.5 percent defective or as indicated in table II. The lot shall be accepted or rejected according to the procedures in 4.4.2.1 for visual examination and 4.4.2.2 for plating thickness (nondestructive tests).

Table I. Production control tests and specimens

Test	For coating classes	Requirement paragraphs	Specimen preparation paragraph <u>1</u> /	Test reference paragraphs
Thickness	1 and 2	3.4.1.1 and 3.4.1.2 or 3.4.2.1	4.4.4 and 4.4.4.1	4.5.1
Adhesion	1 and 2	3.4.1.3 or 3.4.2.2	4.4.4 and 4.4.4.1	4.5.2
Hardness	2	3.4.2.3	4.4.4 and 4.4.4.1	4.5.3
Porosity	2	3.4.2.4	4.4.4 and 4.4.4.2	4.5.4
Hydrogen embrittlement relief	1 and 2	3.2.6	4.4.4 and 4.4.4.3	4.5.5

- 1/ Standard alloy steels shall be used for production control specimens. The selection shall be at the option of the supplier; however, alloy steel such as AISI or SAE number 4340 conforming to MIL-S-5000 shall be used.

Table II. Sampling for visual examination and nondestructive tests

Number of items in lot inspections	Number of items in samples (randomly selected)	Acceptance number (maximum number of sample items nonconforming to any test)
15 or less	7 ^{1/}	0
16 to 40	10	0
41 to 110	15	0
111 to 300	25	1
301 to 500	35	1
501 and over	50	2

^{1/} If the number of items in the inspection lot is less than 7, the number of items in the sample shall equal the number of items in the inspection lot.

- 4.4.2.1 Visual examination: Samples selected in accordance with 4.4.2 shall be examined for compliance with the requirements of 3.2.7, 3.2.8, 3.2.9 and 3.5.2 after plating. If the number of nonconforming articles exceeds the acceptance number for the sample, the lot represented by the sample shall be rejected.
- 4.4.2.2 Thickness of plating (nondestructive tests): Samples selected in accordance with 4.4.2 shall be inspected and the plating thickness measured by the applicable test detailed in 4.5.1 at several locations on each article as defined in 3.4.1.1 and 3.4.1.2 or in 3.4.2.1; as applicable, for compliance with the requirement. Measurements on fastener hardware shall be made on location defined in MIL-STD-1312, Test 12. The part or article shall be considered nonconforming if one or more measurements fail to meet the specified minimum thickness. If the number of defective items in any sample exceeds the acceptance number for the specified sample, the lot represented by the sample shall be rejected. Separate specimens (see 4.4.4.1) shall not be used for thickness measurements unless a need has been demonstrated.
- 4.4.3 Sampling for destructive tests: A random sample of five plated parts or articles shall be taken from each lot for each destructive test or separately plated specimens shall be prepared in accordance with 4.4.4, 4.4.4.1, 4.4.4.2 and 4.4.4.3 to represent each lot. If the number of articles in the lot is five or less, the number of articles in the sample shall be specified by the procuring activity (see 6.2).
- 4.4.3.1 Thickness of plating (destructive tests): If sampling and testing for thickness of plating by nondestructive testing is not the option of the supplier, samples selected in accordance with 4.4.3 shall be measured for plating thickness by the applicable tests detailed in 4.5.1 at several locations as defined in 3.4.1.1 and 3.4.1.2 or in 3.4.2.1, as applicable, for compliance with the requirements. Measurements for fastener hardware shall be made at locations defined in MIL-STD-1312, Test 12. If the plating thickness at any place on any article or specimen is less than the specified minimum thickness, the lot shall be rejected. Separate specimens (see 4.4.4.1) shall not be used for thickness measurements unless a need has been demonstrated.

- 4.4.3.2 Adhesion (destructive tests): The articles on specimens used for the destructive thickness test (see 4.4.3.1), if of suitable size and form, may be used as the test pieces for the adhesion test to determine compliance with the requirements of 3.4.1.3 or 3.4.2.2. Failure of one or more of the test pieces shall constitute failure of the lot.
- 4.4.3.3 Hardness (destructive tests): When specified in the contract or order (see 6.2), compliance with the requirements for hardness shall be determined. The articles or specimens, used for the destructive thickness test (see 4.4.3.1) if of suitable size and form, may be used for the test pieces for examination to determine compliance with the requirement of 3.4.2.3. Failure of one or more of the test pieces shall constitute failure of the lot.
- 4.4.3.4 Porosity (destructive tests): When specified in the contract or order (see 6.2), compliance with the requirements for porosity shall be determined. A set of five separate test specimens prepared in accordance with 4.4.4 and 4.4.4.2 in lieu of treated plated articles shall be used to determine compliance with the requirements for porosity (see 3.4.2.4). Failure of one or more of the test specimens shall reject the lot.
- 4.4.3.5 Hydrogen embrittlement relief (destructive tests): Unless otherwise specified in the contract or order (see 6.2), conformance to the requirements of 3.2.6 for hydrogen embrittlement relief of treated steel parts shall be determined for those parts, comprising a lot, having a tensile strength of or heat treated to a tensile strength level of 180,000 psi (1241 MPa) or above and which will be subjected to a sustained tensile load in use. A random sample of five plated articles shall be taken from each lot or five specimens, prepared in accordance with 4.4.4 and 4.4.4.3 shall be used to represent the lot. When tested as specified in 4.5.5, cracks or failure by fracture shall be cause for rejection. Failure of one or more of the test pieces shall reject the lot.
- 4.4.4 Quality conformance specimen preparation: When the plated articles are of such form, shape, size and value as to prohibit use thereof, or are not readily adaptable to a test specified herein, or when destructive tests of small lot sizes are required, the test shall be made by the use of separate specimens plated concurrently with the articles represented. The separate specimens shall be of a basis metal equivalent to that of the article represented. "Equivalent" basis metal includes chemical composition, grade, condition and finish of surface prior to plating. For example, a cold-rolled steel surface should not be used to represent a hot-rolled steel surface. Due to the impracticality of forging or casting separate test specimens, hot-rolled specimens may be used to represent forged and cast-steel articles. The separate specimens may also be cut from the scrap casting when ferrous alloy castings are being plated. These separate specimens may be introduced into a lot at regular intervals prior to the cleaning operations, prior to plating and shall not be separated therefrom until after completion of plating. Conditions affecting the plating of specimens, including the spacing, plating media, bath agitation, temperature, etc. in respect to other objects being plated shall correspond as nearly as possible to those affecting the significant surfaces of the articles represented. Separate specimens shall not be used for thickness measurements, however, unless the necessity for their use has been demonstrated.
- 4.4.4.1 Specimens for thickness, adhesion, and hardness tests: If separate specimens for thickness, adhesion, and hardness tests are required, they shall be strips approximately 1 inch (25 mm) wide, 4 inches (102 mm) long and 0.04 inch (1 mm) thick.

- 4.4.4.2 Specimens for porosity tests: If separate specimens for porosity tests are required, they shall be panels not less than 10 inches (254 mm) in length, 3 inches (76 mm) in width and approximately 0.04 inch (1 mm) thick.
- 4.4.4.3 Specimens for embrittlement relief: Separate specimens for embrittlement relief test shall be round notched specimens with the axis of the specimen (load direction) perpendicular to the short transverse grain flow direction. The configuration shall be in accordance with Figure 8 of ASTM E-8 for rounded specimens. Specimens shall have a 60 degree V-notch located approximately at the center of the gage length. The cross section area at the root of the vee shall be approximately equal to half the area of the full cross section area of the specimen's reduced section. The vee shall have a 0.010 ± 0.0005 inch (0.254 ± 0.0127 mm) radius of curvature at the base of the notch (see 6.2.2).
- 4.5 Tests:
- 4.5.1 Thickness: For nondestructive measurement of plating thickness, procedures in accordance with ASTM B-499 (magnetic test method) may be used. For destructive measurement of plating thickness, procedures in accordance with ASTM B-487 (microscopic) or ASTM B-504 (coulometric) may be used. In addition to the above, other procedures embodied in MIL-STD-1312, Test 12, may be used for thickness measurement of plated fastener hardware. Class 1 plating may be measured for thickness in accordance with ASTM B-556 (spot test) within its limitations, as a destructive procedure.
- 4.5.2 Adhesion: Adhesion may be determined by scooping the surface or shearing with a sharp edge, knife, or razor through the plating down to the basis metal and examining at four diameters magnification for evidence of non-adhesion. Alternately the article or specimen may be clamped in a vise and the projecting portion bent back and forth until rupture occurs. If the edge of the ruptured plating can be peeled back or if separation between the plating and the basis metal can be seen at the point of rupture when examined at four diameters magnification, adhesion is not satisfactory. Class 2 plating shall demonstrate good adhesion by its capability to withstand the necessary grinding operations for final dimensions.
- 4.5.3 Hardness: The hardness of class 2 plating shall be determined by a microhardness traverse in accordance with ASTM B-578, except that a Vicker indenter and 100 gram load shall be used. A minimum of three hardness readings shall be made to establish the basis metal hardness in an area at least 0.125 inch (3.175 mm) from the outer surface or at mid radius of the cross section which ever is less. Readings shall be taken at 0.0005 inch (0.013 mm) intervals starting at 0.001 inch (0.025 mm) from the outer surface in a staggered pattern until the pre-established basis metal hardness is reached. The hardness reading may be plotted versus distance from the outer surface. The point at which the hardness shows a vast decrease may be taken as the limits of chromium plating.

- 4.5.4 Porosity: Prior to determining porosity by the ferroxyl test, the specimen surface shall be cleaned to remove any oil or grease. Contamination removal shall be accomplished with any acceptable solvent in accordance with MIL-S-5002. A sheet of filter paper, saturated by dipping in a ferroxyl solution heated to 180 to 200°F (82 to 94°C), shall be applied to the flat surface of the specimen or of the article. The solution composition shall be as follows:

Potassium ferricyanide ($K_3Fe(CN)_6$)	1 gm.
Sodium chloride (NaCl)	10 gms.
Agar	10 gms.
Water (distilled or deionized) to make	1 litre

After 10 minutes, the heated filter paper shall be removed. Both the plated surface and the filter paper shall be examined. Where corrosion of the basis metal will occur at pores or other defects due to the plating, dark blue spots will have been developed. Contact may further be assured by the use of a soft bristle brush moistened with the reagent solution. For a permanent record, the filter paper can be dried.

- 4.5.5 Embrittlement relief: Compliance with 3.2.6 shall be determined with samples of plated parts taken as specified in 4.4.3.5. Parts such as spring pins, lock rings, etc., which are installed in holes or rods, shall be similarly assembled using the applicable parts specifications or drawings tolerances which impose the maximum sustained tensile load on the plated part. The selected samples shall be subjected to a sustained tensile load equal to 115 percent of the maximum design yield load for which the part was designed. Parts which require special fixtures, extreme loads to comply with the above requirements, or where the maximum design yield load is not known, may be represented by separate specimens prepared in accordance with 4.4.4.3. The notched samples shall be subjected to a sustained tensile load equal to 75 percent of the ultimate notch tensile strength of the material. The articles, parts or specimens shall be held under load for at least 200 hours and then examined for cracks or fracture.

5. PREPARATION FOR DELIVERY:

5.1 Packaging and packing:

Preservation, packaging and packing methods for electrodeposited plated parts or articles employed by a supplier shall be such as to preclude damaging during shipment and handling.