

AEROSPACE MATERIAL SPECIFICATION

Tubing, Chrome-Molybdenum (4130 or 8630) Steel, Seamless and Welded

NONCURRENCY NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of July, 2003. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those specifications that have been widely used and may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these specifications for future use in new designs. "NONCURRENT" specifications are available from SAE upon request.

Similar but not necessarily identical products are covered by the following specifications:

AMS 6360	Steel Tubing, Seamless, 0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130) Normalized or Stress Relieved
AMS 6361	Steel Tubing, Seamless, 0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130) 125 ksi (862 MPa) Tensile Strength
AMS 6362	Steel Tubing, Seamless, 0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130) 150 ksi (1034 MPa) Tensile Strength

SAENORM.COM : Click to view the full PDF of AMS-T-6736A

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:
Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

NOTICE

This document has been taken directly from U.S. Military Specification MIL-T-6736B, Notice 1 and contains only minor editorial and format changes required to bring it into conformance with the publishing requirements of SAE technical standards. The initial release of this document is intended to replace MIL-T-6736B, Notice 1. Any part numbers established by the original specification remain unchanged.

The original Military Specification was adopted as an SAE standard under the provisions of the SAE Technical Standards Board (TSB) Rules and Regulations (TSB 001) pertaining to accelerated adoption of government specifications and standards. TSB rules provide for (a) the publication of portions of unrevised government specifications and standards without consensus voting at the SAE Committee level, and (b) the use of the existing government specification or standard format.

Under Department of Defense policies and procedures, any qualification requirements and associated qualified products lists are mandatory for DOD contracts. Any requirement relating to qualified products lists (QPL's) has not been adopted by SAE and is not part of this SAE technical document.

1. SCOPE:

1.1 Scope:

This specification covers chromium-molybdenum (4130) seamless and welded steel tubing of aircraft quality.

1.2 Classification:

The tubing shall be of the following grades, types, and physical conditions, as specified (see 6.2):

Grades:

All tubing - Regular grade, except that type I, condition (N) tubing is also available in a special (S) grade having reduced decarburization limits.

Types:

- Type I - Round
- Type II - Rectangular or square
- Type III - Streamline
- Type IV - Oval

1.2 (Continued):

Physical conditions:

(A) - Annealed

(N) - Normalized or stress relieved

(HT-125) - Heat treated to a minimum tensile strength of 125,000 psi

(HT-150) - Heat treated to a minimum tensile strength of 150,000 psi

(HT-180) - Heat treated to a minimum tensile strength of 180,000 psi

2. APPLICABLE DOCUMENTS:

The following publications, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2301	Aircraft Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
AMS 2640	Magnetic Particle Inspection

2.2 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-I-6868	Inspection Process, Magnetic Particle
MIL-C-16173	Corrosion Preventive Compound, Solvent Cutback, Cold Application
FED-STD-151	Metals; Test Methods
FED-STD-183	Continuous Identification Marking of Iron and Steel Products
MIL-STD-129	Marking for Shipment and Storage
MIL-STD-163	Steel Mill Products, Preparation for Shipment and Storage
MS33529	Tolerances - Seamless Steel Tubing, Aircraft Airframe, Round
MS33530	Tolerances - Welded Carbon and Alloy Steel Tubing
MS33532	Square and Rectangular Tubing - Carbon Steel and Alloy Steel, 0.35 Carbon, Maximum
MS33534	Standard Dimensions for Streamline and Oval Tubular Shapes
AND10102	Tubing - Standard Dimensions for Round Seamless Alloy Steel

3. REQUIREMENTS:

3.1 Data:

Unless otherwise specified in the contract or order, no data are required by this specification or any of the documents referenced in section 2 (see 6.2).

3.2 Material:

The tubing shall be of aircraft quality. The material shall be magnetically inspected in accordance with the procedures of AMS 2301, and shall not exceed the size and frequency rating limits indicated in the paragraph entitled "Disposition" of AMS 2301 (see 4.5).

3.2.1 Manufacturing process: The steel shall be manufactured by the open-hearth or electric-furnace process, unless a single process is specified in the contract or purchase order.

3.2.1.1 Sufficient discard shall be taken from each ingot to ensure freedom from piping and undue segregation.

3.3 Chemical composition:

The chemical composition of tubing shall be as specified in Table I.

TABLE I. Chemical composition

Element	Analysis, percent	Check analysis tolerance, ¹ percent
Carbon.....	0.27-0.33	±0.02
Manganese.....	.40- .60	±.03
Phosphorus.....	.025 (max)	+ .005
Sulfur.....	.025 (max)	+ .005
Silicon.....	.20-0.35	±.02
Chromium.....	.80-1.10	+ .05, -0.03
Molybdenum.....	.15-0.25	±.02

¹ Individual determinations may vary from the specified range to the extent shown in the check analysis column, except that elements in any heat shall not vary both above and below the specified range.

3.4 Mechanical properties:

After the last cold-draw pass, the tubing shall be normalized, stress relieved, or otherwise heat treated to develop the mechanical properties specified in table II.

TABLE II. Mechanical properties

Condition and wall thickness	Tensile strength (min.)	Yield strength at 0.2 percent set or at extension indicated		Elongation in 2 inches	
		(Min.)	Extension under load	Full tube (min.)	Strip (min.)
Inch	psi	psi	Inches in 2 inches	Percent	Percent
(A) -----	195,000				
(N) -----					
Up to 0.035 incl. -----	95,000	75,000	0.0090	10	5
Over 0.035 to 0.187 incl. -----	95,000	75,000	.0090	12	7
Over 0.187 -----	90,000	70,000	.0087	15	10
(HT-125) All walls -----	125,000	100,000	.0107	12	7
(HT-150) All walls -----	150,000	135,000	.0130	10	6
(HT-180) All walls -----	180,000	165,000	.0154	8	5

¹ Maximum.

3.5 Dimensions:

The dimensions of type I tubing shall conform to the standard dimensions shown on AND10102. The dimensions of types III and IV shall conform to the standard dimension shown on MS33534. The dimensions of type II tubing shall be as negotiated between the supplier and purchaser.

3.6 Length:

- 3.6.1 Exact lengths: Tubing of all sizes may be ordered to exact lengths or in lengths expressed as a multiple of a definite unit, with tolerances as specified in the contract or purchaser order.
- 3.6.2 Mill lengths: When exact or multiple lengths are not specified (see 6.2), tubing will be accepted in mill lengths of 5 to 20 feet, but not more than 10 percent of any order shall be furnished in lengths shorter than 12 feet.

3.7 Tolerances:

- 3.7.1 Type I: The permissible variations in dimensions of type I seamless tubing shall be as shown on MS33529 and for type I welded tubing as shown on MS33530.
- 3.7.2 Types II, III, and IV: The permissible variations in dimensions of all types II, III, and IV tubing shall be as shown on MS33532.

3.8 Grain size:

The austenitic grain size of the steel used for this tubing shall be predominantly No. 5 or finer, with grains as large as No. 3 permissible, as determined by the method specified in section 4. For seamless tubing, grain size shall be determined on a billet before piercing, hot working, or cold drawing.

3.9 Decarburization:

- 3.9.1 Regular grade: The average depth of total decarburization of regular grade, condition (N) tubing, as received from the tubing manufacturer, shall not exceed the amounts listed in table III. The depth of decarburization in table III is the total decarburization, or the sum of the depths of complete decarburization and partial decarburization on both the inner and outer surfaces of the tube. No more than 75 percent of the amount listed in table III is to appear on the outer surface of the tube. The depth of complete decarburization shall not exceed one-half the allowable total decarburization. (The word "average" means the results of several readings on a cross section of tubing.)
- 3.9.2 Special grade: The permissible decarburization of (S) grade, type I condition (N) tubing shall be one-half that listed in table III, with no complete decarburization permissible.

TABLE III - Decarburization limits

Nominal (wall) thickness (inch)	Allowable total decarburization (ID+OD) (inch)	Maximum total decarburization (OD) (inch)
Up to 0.040.....	0.010	0.008
0.041 to 0.050.....	.012	.009
0.051 to 0.070.....	.014	.011
0.071 to 0.080.....	.016	.012
0.081 to 0.090.....	.018	.014
0.091 to 0.100.....	.020	.015
0.101 to 0.150.....	.022	.017
0.151 to 0.200.....	.026	.020

3.10 Condition:

Unless otherwise specified, tubing shall be furnished in regular grade, type I, condition (N).

3.11 Identification of product:

Each tube shall be marked in accordance with FED-STD-183 and shall include the number of this specification.

3.12 Workmanship:

The tubing shall have a finish conforming to the best practice for aircraft quality material. It shall be smooth, clean, and free from heavy scale or oxide on the interior and exterior surfaces, and shall be free from burrs, seams, tears, grooves, laminations, slivers, pits, and other injurious defects. Surface imperfections, such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered as injurious defects, provided the imperfections are removable without reducing the diameter or wall thickness of the tubing below the permissible tolerance limits. The removal of surface imperfections is not required.

- 3.12.1 Weld: The weld shall not contain defects greater than 1/16-inch long or depths greater than one-half the wall thickness. The welded tubing may be pickled or otherwise cleaned, if necessary, to meet surface conditions specified herein.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for inspection:

Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Quality conformance inspection:

The examination and testing of tubing shall be classified as quality conformance inspection.

- 4.2.1 Sampling and inspection shall be performed in accordance with FED-STD-151 and as specified herein. If the material is taken from stock and is not identifiable as to heat and method of manufacture, or if the identity of any portion of the shipment is obscure in any respect, additional samples shall be selected to determine conformance of all portions of the shipment to this specification.

4.3 Lot:

A lot shall consist of tubing produced from the same heat and which is essentially homogeneous in all respects, in the same condition, of the same type, size, and wall thickness offered for delivery at the same time.

4.4 Examinations:

- 4.4.1 Examination of product: Each length of tubing shall be visually examined for compliance with surface condition and workmanship requirements. Samples selected in accordance with table IV shall be examined to assure compliance with the specified dimensions and tolerances, and identification marking requirements.

TABLE IV. Sampling plan

Lot size	Sample size	Acceptance number rejectable
1 to 15.....	All	0
16 to 180.....	15	0
181 to 300.....	35	0
301 to 500.....	50	1
Over 500.....	75	2

4.4.2 Examination of preparation for delivery: Preparation for delivery shall be examined for conformance to section 5.

4.5 Magnetic inspection:

Specimens shall be selected, inspected, and rated in accordance with the procedures of AMS 2301. Inspection shall be in accordance with MIL-I-6868 or AMS 2640.

4.6 Chemical analysis:

4.6.1 Sampling: At least one sample shall be selected for check chemical analysis in accordance with FED-STD-151 to represent each heat in the lot. The sample shall consist of not less than 2 ounces.

4.6.2 Method: Specimens shall be prepared in accordance with Methods 111 or 112 of FED-STD-151, and shall be tested by wet chemical or spectrochemical methods. In the event of dispute, analysis shall be by wet chemical methods.

4.6.3 Waiver: Samples for check of chemical analysis may be waived provided that all of the material in the lot can be identified as being made from a heat previously analyzed and found to conform to the chemical composition specified herein.

4.7 Tensile test:

4.7.1 Sampling: At least one tensile test sample shall be selected from each 1,000 feet or less of each lot for determination of mechanical properties.

4.7.2 Preparation of specimens: Tensile test specimens shall be prepared in accordance with Method 211 of FED-STD-151.

4.7.3 Method: Tensile tests and determination of yield strength and elongation shall be conducted in accordance with Method 211 of FED-STD-151.