



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE STANDARD

SAE AS1055

REV. C

Issued 1969-02
Revised 1994-06

Submitted for recognition as an American National Standard

FIRE TESTING OF FLEXIBLE HOSE, TUBE ASSEMBLIES, COILS, FITTINGS, AND SIMILAR SYSTEM COMPONENTS

1. SCOPE:

This SAE Aerospace Standard (AS) establishes uniform requirements and procedures for the fire testing of flexible hose assemblies and rigid tube assemblies (including coiled tubes) to be used in aircraft or aerospace vehicle fluid systems. These procedures may also be followed for fire tests on other piping components as specified by the customer. It also refers to standard fire test equipment to be used in conducting "referee" fire tests.

1.1 Classification:

Component assemblies shall be designated by Type and Class according to fire test duration and usage. Flame test apparatus and temperature shall be the same for each Type and Class.

1.1.1 Types:

- Type Ia - Hose Assembly, Rubber - Fuel and Oil Systems
- Type Ib - Hose Assembly, Rubber - Hydraulic Systems
- Type IIa - Hose Assembly, Polytetrafluoroethylene - Fuel and Oil Systems
- Type IIb - Hose Assembly, Polytetrafluoroethylene - Hydraulic Systems
- Type IIIa - Rigid Tubing Assembly - Fuel and Oil Systems
- Type IIIb - Rigid Tubing Assembly - Hydraulic Systems

NOTES: 1. The Types listed above, when tested to higher pressures, temperatures, and lower flow rates do not have to be retested to qualify to lower pressures, low temperatures, and/or higher flow rates.

2. An index of the types of assembly by specification is contained in Appendix A.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

SAE AS1055 Revision C

- 1.1.2 a. Class A - Fire Resistant: 5 min
b. Class B - Fireproof: 15 min

NOTE: The user of this document is cautioned that the class designation relates only to assemblies tested under flow conditions.

2. APPLICABLE DOCUMENTS:

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AS1072 Firesleeves

AIR1377 Fire Test Equipment for Flexible Hose and Tube Assemblies

2.2 Federal Standards:

Available from Federal Aviation Administration, 800 Independence Avenue, SW, Washington, DC 20591.

Federal Air Regulation (FAR) Code of Federal Regulations Volume 14, Airworthiness Standard

3. QUALIFICATION:

The component assemblies furnished under this document shall be products which have been tested and passed the fire test requirements listed herein. These products shall also have been tested and passed the performance requirements of the latest applicable specifications, or other applicable specifications designated by the purchaser.

Test report(s) proving qualification of products to this specification shall be furnished by the supplier to the purchaser and to such cognizant agencies designated by the purchaser, for acceptance of qualification. Qualification by similarity, to assemblies or parts previously tested and qualified, shall be acceptable.

3.1 Materials:

The component materials shall be uniform in quality, free from defects, consistent with good manufacturing practices and shall conform to the applicable specifications listed in 2.1 and 2.2, or other applicable specifications designated by the purchaser.

SAE AS1055 Revision C

- 3.1.1 When firesleeves are employed to meet the fire test requirements, they shall be compatible with fluid and ambient environments encountered and be free of corrosive additives and free from wicking action. Wrapped type firesleeves, where used, shall be arranged to approximate the installed condition that gives the least fire protection.

NOTE: AS1072 indicates compatibility of firesleeves with various fluids.

4. TEST PROCEDURE:

Test procedure shall conform with the following conditions:

4.1 Pretest Conditions:

- 4.1.1 Flame Temperature and Size: The flame temperature shall be $2000\text{ }^{\circ}\text{F} \pm 150\text{ }^{\circ}\text{F}$ ($1090\text{ }^{\circ}\text{C} \pm 83\text{ }^{\circ}\text{C}$) along centerline of the flame for a minimum distance of 7 in (178 mm).
- 4.1.2 Flame Intensity: The flame heat content shall be $4500 +200/-100\text{ Btu/h}$ ($1320 +60/-30\text{ watts}$) input to a 15 in (380 mm) exposed length of 1/2 in x .032 in (13 mm x 0.8 mm) refrigeration type copper tubing with a water flow rate of approximately 1 gal/min (3.8 L/m). For "Referee Heat Content" equipment, refer to AIR1377.¹
- 4.1.3 Air Velocity: Air velocity over the test assembly shall be 400 ft/min (2.03 m/s) with assembly mounted in a 25 in x 25 in (635 mm x 635 mm) hood equipped with a downstream exhaust fan. Air temperature shall be maintained within the range 40 to 100 °F (4.4 to 37.8 °C).

4.2 Test Conditions:

- 4.2.1 Vibration: Vibration shall be lateral or longitudinal with an amplitude of $\pm .062\text{ in}$ (1.59 mm) at 2000 cpm (33 Hz). Amplitude and frequency tolerance shall be $\pm 2\%$.
- 4.2.2 Oil Temperature: 200 to 230 °F (93 to 110 °C).
- 4.2.3 Oil Flow: The flow rate, using SAE No. 20 oil, shall be as given. Where specified, the system working fluid may be substituted for SAE No. 20 oil. The ID shall be taken as that of the majority of the component (i.e., the hose for a hose assembly and the tube for a tube assembly) expressed to the next higher 16th of an inch (next higher full millimeter). Flow rate tolerance shall be $\pm 3\%$.

¹ It is desirable that a calorimeter reading of $10\text{ Btu/ft}^2 \pm 1\text{ Btu/ft}^2\text{-s}$ ($113\ 500\text{ w/m}^2 \pm 11\ 350\text{ w/m}^2$) be obtained over the fire area of 10 in x 6 in (254 mm x 152 mm) in the plane of the component. Along the 7 in (178 mm) hose centerline, a calorimeter reading of $12\text{ Btu/ft}^2\text{-s} \pm 1\text{ Btu/ft}^2\text{-s}$ ($136\ 200\text{ w/m}^2 \pm 11\ 350\text{ w/m}^2$) is desirable.

SAE AS1055 Revision C

4.2.3.1 Flow Rate for Fuel and Oil Systems (Type a):

$$(\text{GPM}) = 5.0 \times \text{ID (in)}^2 \text{ or } (\text{L/min}) = 0.03 \times \text{ID (mm)}^2 \quad (\text{Eq.1})$$

4.2.3.2 Flow Rate for Hydraulic Systems (Type b):

$$(\text{GPM}) = 1.0 \times \text{ID (in)}^2 \text{ or } (\text{L/min}) = 0.006 \times \text{ID (mm)}^2 \quad (\text{Eq.2})$$

4.2.4 Pressure: The pressure shall be the working pressure of the component or, where specified, the system pressure may be substituted during the test.

4.2.5 Burner Position: The burner shall be positioned such that the distance to the side of the component is equal to the distance to the plane where the requirements of 4.1.1 and 4.1.2 are met.

In the case of testing a hose or tube assembly, a minimum of 5 in (127 mm) of the hose or tubing plus the fitting must be exposed to the fire.

5. REQUIREMENTS:

5.1 Test Equipment:

The equipment used for this fire test shall be capable of providing the test conditions of Section 4. For purposes of "referee" testing, the equipment shall be in accordance with AIR1377.

5.2 Failure:

Assemblies shall not fail by rupture or leakage before a test duration of:

- a. 5 min to be rated Class A - Fire Resistant
- b. 15 min to be rated Class B - Fireproof

Rupture or leakage shall be detected visually from a distance of 5 ft (1.5 m) or automatically with a photoelectric cell located 3.5 to 4 ft (1.1 to 1.2 m) downstream of test specimen.

6. IDENTIFICATION:

Assemblies shall be permanently and legibly identified with the following information using a permanently attached corrosion resistant steel band or permanent marking on component, unless otherwise specified by the purchaser.

- a. Manufacturer's name or trademark.
- b. Size, type, and maximum operating pressure of component assembly.
- c. Manufacturer's part number.
- d. Date of manufacture (month and year).
- e. Component assemblies suitable for use with synthetic base fluids shall be marked with the letter "S" immediately following the Type and Class designation and the letter "P" for petroleum base fluids. If suitable for both synthetic and petroleum base fluids, mark with letters "S/P", i.e.: