



AEROSPACE STANDARD

AS 1182

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

Issued 5-15-71
Revised

STANDARD MACHINING ALLOWANCE, Aircraft Quality and Premium Quality Steel Products

1. **PURPOSE:** The purpose of this document is to provide the aerospace industry with standards for minimum stock removal allowances for bars and tubing to provide surfaces which are required to pass magnetic particle inspection requirements. Surfaces after such stock removal will be free from decarburization, seams, laps, tears, cracks, pits, and other injurious surface imperfections.
2. **APPLICABLE DOCUMENTS:** The following publications form a part of this standard to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) and AISI Steel Products Manual shall apply.
 - 2.1 **SAE Publications:** Available from Society of Automotive Engineers, Inc., Two Pennsylvania Plaza, New York, New York, 10001.
 - 2.1.1 **Aerospace Material Specifications:**
 - AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel Bars and Wire and Titanium and Titanium Alloy Bars and Wire
 - AMS 2251 - Tolerances, Alloy Steel Bars
 - AMS 2243 - Tolerances, Corrosion and Heat Resistant Steel Tubing
 - AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
 - AMS 2350 - Standards and Test Methods
 - 2.2 **AISI Publications:** Available from American Iron and Steel Institute, 150 East Forty-Second Street, New York, New York, 10017.
 - 2.2.1 **Steel Products Manual:**
 - Steel Specialty Tubular Products Section
3. **REQUIREMENTS:**
 - 3.1 **Hot Rolled or Cold Drawn Low Alloy and Martensitic Corrosion Resistant Steel Bars (See 3.1.1):**

TABLE I

Hot Rolled Size Inches	Minimum Stock Removal From Surface, Inch	Cold Drawn Size Inches
Up to 0.500, incl	0.030	Up to 0.4375, incl
Over 0.500 to 0.750, incl	0.045	Over 0.4375 to 0.6875, incl
Over 0.750 to 1.000, incl	0.060	Over 0.6875 to 0.9375, incl
Over 1.000 to 1.500, incl	0.075	Over 0.9375 to 1.4375, incl
Over 1.500 to 2.000, incl	0.090	Over 1.4375 to 1.9375, incl
Over 2.000 to 2.500, incl	0.125	Over 1.9375 to 2.4375, incl
Over 2.500 to 3.500, incl	0.156	Over 2.4375 to 3.3750, incl
Over 3.500 to 4.500, incl	0.187	Over 3.3750 to 4.3750, incl
Over 4.500 to 6.000, incl	0.250	

SAE Technical Board rules provide that: "All technical reports, including standards applications, and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."