




AEROSPACE STANDARD

AS 1291

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

Issued May 1973
Revised

SLEEVE, HOSE ASSEMBLY, CHAFE GUARD, TFE OR FEP



Size	D Inside Diameter						T Wall Thickness						Weight	
	Nominal		Maximum		Minimum		Nominal		Maximum		Minimum		lbs/ft	kgs/m
	in.	mm	in.	mm	in.	mm	in.	mm	in.	mm	in.	mm		
-1	.295	7.49	.310	7.87	.280	7.11	.030	.76	.040	1.02	.020	.51	.018	.027
-2	.368	9.35	.383	9.73	.353	8.97	.030	.76	.040	1.02	.020	.51	.023	.034
-3	.429	10.90	.444	11.28	.414	10.52	.030	.76	.040	1.02	.020	.51	.026	.039
-4	.495	12.57	.505	12.83	.475	12.07	.030	.76	.040	1.02	.020	.51	.030	.045
-5	.620	15.75	.635	16.13	.605	15.37	.030	.76	.040	1.02	.020	.51	.038	.056
-6	.723	18.36	.738	18.75	.708	17.98	.030	.76	.040	1.02	.020	.51	.042	.062
-7	.767	19.48	.782	19.86	.752	19.10	.030	.76	.040	1.02	.020	.51	.046	.068
-8	.845	21.46	.860	21.84	.830	21.08	.030	.76	.040	1.02	.020	.51	.050	.074
-9	.940	23.88	.955	24.26	.925	23.50	.030	.76	.040	1.02	.020	.51	.055	.081
-10	1.097	27.86	1.112	28.24	1.082	27.48	.030	.76	.040	1.02	.020	.51	.067	.099
-11	1.185	30.10	1.200	30.48	1.170	29.72	.030	.76	.040	1.02	.020	.51	.073	.108
-12	1.378	35.00	1.393	35.38	1.363	34.62	.030	.76	.040	1.02	.020	.51	.084	.124
-13	1.425	36.20	1.440	36.58	1.410	35.81	.030	.76	.040	1.02	.020	.51	.087	.129
-14	1.746	44.35	1.761	44.73	1.731	43.97	.030	.76	.040	1.02	.020	.51	.101	.150

- 1.1 **Usage:** Used as an outer protective cover on hose and/or hose assemblies to inhibit the detrimental effects of abrasion and other environmental conditions, thereby increasing service life.
- 1.2 **Materials:** The following codes shall apply to the types and colors of teflon sleeving covered in this standard.
 - 1.2.1 **Code A:** White, extruded, seamless polytetrafluoroethylene (TFE) tubing.
 - 1.2.2 **Code B:** Black, extruded, seamless polytetrafluoroethylene (TFE) tubing.
 - 1.2.3 **Code C:** Transparent, extruded, seamless fluorinated ethylene propylene (FEP) tubing.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."