

SAE Executive Standards Committee Rules provide that: " This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

REV. C
AS21154™

FEDERAL SUPPLY CLASS
3120

RATIONALE


THIS DOCUMENT HAS BEEN DECLARED "STABILIZED" BY SAE ACBG-PB (PLAIN BEARING) COMMITTEE AND WILL NO LONGER BE SUBJECTED TO PERIODIC REVIEWS FOR CURRENCY. USERS ARE RESPONSIBLE FOR VERIFYING REFERENCES AND CONTINUED SUITABILITY OF TECHNICAL REQUIREMENTS. NEWER TECHNOLOGY MAY EXIST.

STABILIZED NOTICE

THIS DOCUMENT HAS BEEN DECLARED "STABILIZED" BY THE SAE ACBG PLAIN BEARING COMMITTEE AND WILL NO LONGER BE SUBJECTED TO PERIODIC REVIEWS FOR CURRENCY. USERS ARE RESPONSIBLE FOR VERIFYING REFERENCES AND CONTINUED SUITABILITY OF TECHNICAL REQUIREMENTS. NEWER TECHNOLOGY MAY EXIST.

SAENORM.COM : Click to view the full PDF of as21154C

For more information on this standard, visit
<https://www.sae.org/standards/content/AS21154C/>



CUSTODIAN: ACBG PLAIN BEARING COMMITTEE



AEROSPACE STANDARD
BEARING, PLAIN, SELF-ALIGNING,
GROOVED OUTER RING

AS21154™

REV. C

ISSUED 1998-05 REVISED 2011-12 STABILIZED 2023-08




FIGURE 1 – PART CONFIGURATION

TABLE 1 - DIMENSIONS AND LOADS

DASH NO.	Ø B +.0000 -.0005	Ø D +.0000 -.0005	H ±.005	Ø K	L ±.005 (a)	Ø M MIN.	P +.000 -.015	Q° MIN.	Ø E +.000 -.010	RADIUS S	W +.000 -.002	ALLOY STEEL		ALUMINUM BRONZE	
												RADIAL STATIC LIMIT LOAD (b)	AXIAL STATIC LIMIT LOAD (c)	RADIAL STATIC LIMIT LOAD (b)	AXIAL STATIC LIMIT LOAD (c)
-03	.1900	.5625	.218	.047	.062	.293	.030	10	.502	.005	.281	4600	2100	2800	850
-04	.2500	.6562	.250			.364			.596		.343	7080	2800	4300	1100
-05	.3125	.7500	.281			.419			.662		.375	8500	3550	5200	1400
-06	.3750	.8125	.312	.062	.078	.475	.040	9	.714	.010	.406	11050	4400	6750	1760
-07	.4375	.9062	.343			.530			.808		.437	13900	5400	8500	2150
-08	.5000	1.0000	.390			.600			.878		.500	18850	7050	11500	2800
-09	.5625	1.0937	.437	.078	.093	.670	.060	8	.972	.020	.562	25500	8900	15600	3550
-10	.6250	1.1875	.500			.739			1.065		.625	31950	11700	19500	4650
-12	.7500	1.4375	.593			.920			1.315		.750	46750	16500	28500	6575
-14	.8750	1.5625	.703	.078	.093	.980	.060	9	1.440	.010	.875	62750	23300	38300	9300
-16	1.0000	1.7500	.797			1.118			1.628		1.000	83350	30000	51000	12000

- (a) RACE ID GROOVE (L DIMENSION) AND HOLE DIAMETER TO BE MEASURED BEFORE BEARING ASSEMBLY BUT SWAGING SHALL NOT PREVENT GREASE FLOW.
- (b) THESE BEARINGS MAY EXPERIENCE SOME METAL YIELDING AT THE RADIAL STATIC LIMIT LOADS LISTED.
- (c) THE LIMIT AND ULTIMATE AXIAL LOAD CAPACITY OF THE BEARING CAN BE ACHIEVED ONLY WHEN THE SIDE FACE INSIDE THE GROOVE IS SUPPORTED AS DEFINED IN AS8976.

TABLE 1 – DIMENSIONS AND LOADS (CONTINUED)

DASH NO.	R RADIUS (REF)	BALL DIA. MAX.	
		ALLOY STEEL	ALUM BRONZE
-03	.045	.407	.438
-04		.501	.501
-05	.065	.563	.594
-06		.657	.657
-07		.719	.719
-08		.814	.814
-09		.907	.907
-10	.088	.970	1.001
-12		1.188	1.251
-14		1.313	1.376
-16		1.501	1.563

REQUIREMENTS:

1. MATERIAL:

BALL - 52100 AMS6440, AMS6444, AMS-S-7420 OR 440C AMS5630

RACE - CODES: "S" ALLOY STEEL, AMS-S-5000, AMS-S-6758 OR AMS-S-6050.
 "B" ALUMINUM BRONZE PER ASTM B 124/B 124M, ASTM B 150, ASTM B 169/B 169M
 AND B 283-EXCEPT THE CHEMICAL COMPOSITION SHALL BE:

ELEMENT PERCENT	CU	AL	FE	NI	SI	MN	SN	ZN	SUM OF NAMED ELEMENTS MIN
	80.0 TO 93.0	6.5 TO 11.0	4.0 MAX	1.0 MAX ^(d)	2.2 MAX ^(d)	1.5 MAX	.60 MAX	1.0 MAX	99.5

(d) WHEN BOTH SILICON AND NICKEL ARE PRESENT, ONLY ONE SHALL BE IN EXCESS OF 0.25 PERCENT.

2. FINISH: BALL - CHROME PLATE AMS2460, CLASS 2D, 0.0002 INCH MINIMUM ON SPHERICAL SURFACES AND ON FACES, PLATING RUNOUT ON BALL ID CHAMFERS ALLOWED. DIMS APPLY AFTER PLATE. SHOT PEEN PRIOR TO PLATE NOT REQUIRED.

 FINISH: RACE - CADMIUM PLATE PER AMS-QQ-P-416, TYPE 1, CLASS 2 OR ZINC NICKEL PLATING PER AMS2417, TYPE 2. SEE REQUIREMENT 10 AND NOTE 4.
3. HARDNESS: BALL - HRC 56 MINIMUM.
 RACE - ALLOY STEEL, HRC 27-36, APPLIES PRIOR TO RACE ASSEMBLY (SWAGING).
4. LUBRICATION: PREPACKED WITH MIL-G-21164 GREASE.
5. SURFACE TEXTURE (μ INCHES): SPHERICAL SURFACE OF BALL 8 RA; BORE, BALL FACE AND OUTER RACE O.D. 32 RA. ALL OTHER SURFACES 125 RA, IN ACCORDANCE WITH ASME B 46.1.
6. TEMPERATURE RANGE: -65 TO +250 °F.
7. INTERNAL CLEARANCE MEASURED UNDER A ± 5.5 LB. MINIMUM GAGE LOAD:
 RADIAL CLEARANCE 0.0005 TO 0.0020 INCH
 AXIAL CLEARANCE 0.010 INCH MAXIMUM
8. BREAK SHARP EDGES AND CORNERS AND REMOVE ALL BURRS AND SLIVERS.
9. DIMENSIONS IN INCHES. UNLESS OTHERWISE SPECIFIED, TOLERANCES: DECIMALS ± 0.10 , ANGLES $\pm 1/2$ DEGREE.
10. OUTER RACE PLATING: BASE PART NUMBER, DEFAULT PLATING IS CADMIUM PLATE PER AMS-QQ-P-416, TYPE 1, CL. II ON ALL EXTERNAL SURFACES OF THE RACE, OR, AT THE OPTION OF THE MANUFACTURER, ZINC NICKEL PLATE PER AMS2417, TYPE 2, ON ALL EXTERNAL SURFACES OF THE RACE. FOR EITHER PLATING OPTION, RUNOUT (WHICH MAY BE INCOMPLETE AND MISSING) MAY OCCUR IN THE RACE ID CHAMFER/SETBACK REGION ON THE RACE. BASE PART NUMBER ALLOWS THE MANUFACTURER TO USE CADMIUM PLATE OR ZINC NICKEL PLATE ON THE OUTER RACE. ONLY WHEN THE "E" SUFFIX IS LISTED SHALL THE RACE PLATING ONLY BE ZINC NICKEL.

OUTER RACE: PLATING, WHEN SPECIFIED (AS DEFINED IN NOTE 4), SHALL BE ZINC-NICKEL PLATING PER AMS2417, TYPE 2, ON ALL EXTERNAL SURFACES OF THE RACE. PLATING RUNOUT (WHICH MAY BE INCOMPLETE AND MISSING) MAY OCCUR IN THE RACE ID CHAMFER/SETBACK REGION ON THE RACE.

	AEROSPACE STANDARD	AS21154™ SHEET 2 OF 3	REV. C
	BEARING, PLAIN, SELF-ALIGNING, GROOVED OUTER RING		