

NOTICE

THIS DOCUMENT HAS BEEN TAKEN DIRECTLY FROM U.S. MILITARY SPECIFICATION MIL-DTL-22759/80A AND CONTAINS ONLY MINOR EDITORIAL AND FORMAT CHANGES REQUIRED TO BRING IT INTO CONFORMANCE WITH THE PUBLISHING REQUIREMENTS OF SAE TECHNICAL STANDARDS. THE INITIAL RELEASE OF THIS DOCUMENT IS INTENDED TO REPLACE MIL-DTL-22759/80A. ANY PART NUMBERS ESTABLISHED BY THE ORIGINAL SPECIFICATION REMAIN UNCHANGED.

THE ORIGINAL MILITARY SPECIFICATION WAS ADOPTED AS AN SAE STANDARD UNDER THE PROVISIONS OF THE SAE TECHNICAL STANDARDS BOARD (TSB) RULES AND REGULATIONS (TSB 001) PERTAINING TO ACCELERATED ADOPTION OF GOVERNMENT SPECIFICATIONS AND STANDARDS. TSB RULES PROVIDE FOR (A) THE PUBLICATION OF PORTIONS OF UNREVISED GOVERNMENT SPECIFICATIONS AND STANDARDS WITHOUT CONSENSUS VOTING AT THE SAE COMMITTEE LEVEL, AND (B) THE USE OF THE EXISTING GOVERNMENT SPECIFICATION OR STANDARD FORMAT.


UNDER DEPARTMENT OF DEFENSE POLICIES AND PROCEDURES, ANY QUALIFICATION REQUIREMENTS AND ASSOCIATED QUALIFIED PRODUCTS LISTS ARE MANDATORY FOR DOD CONTRACTS. ANY REQUIREMENT RELATING TO QUALIFIED PRODUCTS LISTS (QPL'S) HAS NOT BEEN ADOPTED BY SAE AND IS NOT PART OF THIS SAE TECHNICAL DOCUMENT.

AS22759/80

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

SAENORM.COM : Click to view the full PDF of as22759 - SP

THIRD ANGLE PROJECTION



ISSUED 2000-06

PREPARED BY SAE SUBCOMMITTEE AE-8D




AEROSPACE STANDARD

WIRE, ELECTRICAL, POLYTETRAFLUOROETHYLENE/POLYIMIDE INSULATED, LIGHT WEIGHT, TIN COATED. COPPER CONDUCTOR, 150°C, 600 VOLTS

AS22759/80
SHEET 1 OF 7

THE REQUIREMENTS FOR ACQUIRING THE PRODUCT DESCRIBED HEREIN SHALL CONSIST OF THIS SPECIFICATION SHEET AND THE ISSUE OF THE FOLLOWING SPECIFICATION LISTED IN THAT ISSUE OF THE DEPARTMENT OF DEFENSE INDEX OF SPECIFICATIONS AND STANDARDS (DoDISS) SPECIFIED IN THE SOLICITATION: MIL-W-22759.

AS22759/80



FP - Fluorocarbon Polymer, modified Polytetrafluoroethylene (PTFE)

FIGURE I. GENERAL CONFIGURATION.

TABLE I. CONSTRUCTION DETAILS.

Part No. ^{1/}	Wire Size	Conductor			Finished Wire			Weight (lb./1000 Ft) (Max.)
		Stranding (number of strands x AWG gauge of strands)	Diameter (in.)		Resistance at 20° C (68°F) (ohms/ 1000 ft max.)	Diameter (in.)		
			MIN.	MAX.		Min.	Max.	
M22759/80-26-*	26	19 x 38	0.0175	0.0204	41.3	0.030	0.034	1.43
M22759/80-24-*	24	19 x 36	0.0225	0.0244	26.2	0.034	0.038	1.93
M22759/80-22-*	22	19 x 34	0.0285	0.0314	16.2	0.040	0.043	2.85
M22759/80-20-*	20	19 x 32	0.0365	0.0394	9.88	0.048	0.051	4.38
M22759/80-18-*	18	19 x 30	0.0455	0.0494	6.23	0.056	0.060	6.60
M22759/80-16-*	16	19 x 29	0.0515	0.0554	4.81	0.063	0.067	8.30
M22759/80-14-*	14	19 x 27	0.0645	0.0694	3.06	0.076	0.080	12.6
M22759/80-12-*	12	37 x 28	0.0835	0.0894	2.02	0.096	0.100	19.6
M22759/80-10-*	10	37 x 26	0.106	0.112	1.26	0.119	0.123	30.6

^{1/} Part Number: The asterisks in the part number column of Table I shall be replaced by color code designators in accordance with MIL-STD-681. Examples: M22759/80-20-93 is a 20 AWG white with orange stripe.

AS22759/80

TABLE II. WIRE INSULATION MATERIALS. 1/

Tape Code	Thickness (Nom)	Material
1	0.0012	.00045 (FP) / .00065 (Polyimide) / .0001 (FP)
2	0.0020	FP (Unsintered)
3	0.0025	FP (Unsintered)

1/ Physical properties of FP unsintered tapes shall be in accordance with MIL-W-22759 requirements.

TABLE III. PHYSICAL PROPERTIES OF FP/POLYIMIDE/FP TAPES.

Tensile Strength	20,000 lb./in sq. (average minimum)
Tensile Modulus	400,000 lb./in sq. (average minimum)
Elongation	40 percent (average minimum)
Dielectric Strength	4,000 volts/mil (average minimum)
0.00045 FP Layer	Distinguishable color (next to conductor)

TABLE IV. TAPE OVERLAP REQUIREMENTS. 1/

Wire Size	Tape Code	Wrap 1		Wrap 2		Nominal Wall Thickness (mils)	
		Percent Overlap		Percent Overlap			
		Min	Max	Min	Max		
26	1	50.5	54.0	2	50.5	54.0	5.8
24	1	50.5	54.0	2	50.5	54.0	5.8
22	1	50.5	54.0	2	50.5	54.0	5.8
20	1	50.5	54.0	2	50.5	54.0	5.8
18	1	50.5	54.0	2	50.5	54.0	5.8
16	1	50.5	54.0	2	50.5	54.0	5.8
14	1	50.5	54.0	2	50.5	54.0	5.8
12	1	50.5	54.0	3	50.5	54.0	6.7
10	1	50.5	54.0	3	50.5	54.0	6.7

1/ Wrap 1 is innermost tape which is in contact with the conductor with the .00045 inch FP side of the tape against the conductor.

TABLE V. FLUID TABLE.

Test Fluid	Test temperature (°C (°F))	Immersion time (hrs.)
A. MIL-A-8243 Anti - icing and Deicing Defrosting Fluid, undiluted	48 - 50 (118 - 122)	20
B. MIL-A-8243 Anti - icing and Deicing Defrosting Fluid, diluted 60/40 (fluid/water) ratio	48 - 50 (118 - 122)	20
C. MIL-C-43616, Cleaning Compound, Aircraft Surface, Type I	48 - 50 (118 - 122)	20
D. ASTM D1153, Methyl Isobutyl Ketone (For use in Organic Coatings)	20 - 25 (68 - 77)	168
E. SAE AS 1241, Fire Resistant Hydraulic Fluid for Aircraft	48 - 50 (118 - 122)	20
F. MIL-L-7808, Lubricating Oil, Aircraft Turbine Engine, Synthetic Base	118 - 121 (244 - 250)	30
G. MIL-C-87937, Cleaning Compound, Aerospace Equipment, Type II or Type IV, undiluted	63 - 68 (145 - 154)	20
H. MIL-C-87937, Cleaning Compound, Aerospace Equipment, Type II or Type IV, diluted 25/75 (fluid/water) ratio	63 - 68 (145 - 154)	20
I. TT-S-735, Standard Test Fluids: Hydrocarbon, Type I	20 - 25 (68 - 77)	168
J. TT-S-735, Standard Test Fluids: Hydrocarbon, Type II	20 - 25 (68 - 77)	168
K. TT-S-735, Standard Test Fluids: Hydrocarbon, Type IV	20 - 25 (68 - 77)	168
L. Dielectric - coolant Fluid Synthetic Silicate Ester Base, Monsanto Coolanol 25 or approved equivalent.	20 - 25 (68 - 77)	168
M. MIL-G-3056, Gasoline, Automotive, Combat	20 - 25 (68 - 77)	168

RATINGS:

Temperature rating: 150°C (320°F) maximum continuous conductor temperature.

Voltage rating: 600 volts (rms.) at sea level

ADDITIONAL REQUIREMENTS:

Wet arc propagation resistance (Test required for initial qualification only): Test in accordance with MIL-STD-2223 Method 3006. Measure the damage of the bundle along the axis. The wire is acceptable if the following criteria are met:

1. A minimum of 64 wires pass the dielectric test.
2. Three wires or less fail the dielectric test in any one bundle.
3. Actual damage to the wire is not more than 3 inches in any test bundle.

Dry arc propagation resistance (Test required for initial qualification only): Test in accordance with MIL-STD-2223 Method 3007. Measure the damage of the bundle along the axis. The wire is acceptable if the following criteria are met:

1. A minimum of 64 wires pass the dielectric test.
2. Three wires or less fail the dielectric test in any one bundle.
3. Actual damage to the wire is not more than 3 inches in any test bundle.

Blocking: 200°C ± 2°C (392°F ± 3.6°F)

Color: In accordance with MIL-STD-104, class 1; except as noted below. White preferred. Conformity of color to the limits of MIL-STD-104 shall not be required after oven exposure.

AS22759/80

Munsell color limits for UV laser markable wire

Color	Hue		Value		Chroma	
	From	To	From	To	From	To
Black	2.5RN	2.5RN	7	8.5	N/A	N/A
Blue	5PB	7.5B	7	8	4	6
Green	2.5G	7.5G	7	9	2	6
Red	10RP	5R	7	8	4	6
Yellow	5Y	10Y	8	9	4	6
Brown	2.5YR	7.5R	7	9	2	4
Orange	10R	2.5YR	6	7	8	10
Violet	2.5P	7.5R	7	8	4	8
Gray	Same as Black		Same as Black		Same as Black	

Color striping or banding durability: 125 cycles (250 strokes), 250 grams weight

Conductor strand adhesion: Required

Continuous lengths: Schedule B

Dynamic cut-through (Test required for initial qualification only): Test in accordance with ASTM D 3032, Section 22. Blade shall be the standard cutting blade except the cutting edge radius shall be $0.005 \pm .001$ inch. Minimum average dynamic cut-through (lbs.) shall be as shown in the following table:

Wire Size	23 ± 5°C	150 ± 5°C
26	10 lbs.	8 lbs.
20	25 lbs.	20 lbs.

Flammability: Test in accordance with MIL-STD-2223, Method 1006, Procedure A:

Requirements:

- Duration of after-flame 3 seconds (max.)
- Flame travel 3.0 inches (max.)
- No flaming of tissue

Forced Hydrolysis: (Test required for initial qualification only) 2000 hours at 70°C. Test 5 samples of AWG size 20 only in accordance with SAE AS4373 method 602. All 5 samples must pass the dielectric test as listed in method 602.

High frequency spark test: (When used in lieu of Impulse dielectric test) Test in accordance with MIL-STD-2223 Method 3008, 5.7 kilovolts (rms.) Test 100 percent of the wire.

Humidity resistance: After humidity exposure wire shall meet the requirements for initial insulation resistance.

Identification of product: Not required for size 26. Color code designator not required.

Identification durability: 125 cycles (250 strokes), 250 grams weight.

Immersion (Test required for initial qualification only): Test in accordance with MIL-STD-2223 Method 1001 including the additional fluids listed in Table V of this specification. Use mandrels and weights listed in Table VI for Bend testing.

Dielectric test, 2500 volts (rms), 60 Hz. For turbine fuel immersion test of MIL-STD-2223, either JP4 or MIL-T-83133 type JP-8 (NATO Type F-34) may be used.

Impulse dielectric test: 8.0 kilovolts (peak). Test 100 percent of the wire.