


RATIONALE

SPECIFICATION UPDATED TO INCLUDE AS29606 CONDUCTOR REQUIREMENTS, ROHS RESTRICTIONS AND AS22759 MODIFICATIONS.

NOTICE

THE COMPLETE REQUIREMENTS FOR PROCURING THE PRODUCT DESCRIBED HEREIN SHALL CONSIST OF THIS DOCUMENT AND THE LATEST ISSUE OF AS22759.

THIS SPECIFICATION IS NOT INTENDED FOR USE IN NAVAL AIRCRAFT OR NAVAL AIR SYSTEMS APPLICATIONS.



FP – FLUOROCARBON POLYMER MODIFIED POLYTETRAFLUOROETHYLENE (PTFE)  
CONDUCTOR – STRANDED TIN COATED COPPER

FIGURE 1 - AS22759/80 CONFIGURATION

TABLE 1 - CONSTRUCTION DETAILS FOR FINISHED WIRE


PART NO. 1/	WIRE SIZE	CONDUCTOR 3/				FINISHED WIRE				
		STRANDING (NUMBER OF STRANDS X SIZE GAUGE OF STRANDS)	DIAMETER (IN)		RESISTANCE AT 20 °C (68 °F) (OHMS/1000 FEET MAX)	DIAMETER (IN)		WEIGHT (LB/1000 FEET) 2/		
			MIN	MAX		MIN	MAX	MIN	TARGET	MAX
M22759/80-26-*	26	19 X 38	.0175	.0204	41.3	.030	.034	1.16	1.31	1.45
M22759/80-24-*	24	19 X 36	.0225	.0244	26.2	.034	.038	1.70	1.85	2.00
M22759/80-22-*	22	19 X 34	.0285	.0314	16.2	.040	.043	2.55	2.75	2.95
M22759/80-20-*	20	19 X 32	.0365	.0394	9.88	.048	.051	4.05	4.25	4.45
M22759/80-18-*	18	19 X 30	.0455	.0494	6.23	.056	.060	6.15	6.40	6.65
M22759/80-16-*	16	19 X 29	.0515	.0554	4.81	.063	.067	7.75	8.05	8.35
M22759/80-14-*	14	19 X 27	.0645	.0694	3.06	.076	.080	12.0	12.4	12.8
M22759/80-12-*	12	37 X 28	.0835	.0894	2.02	.096	.100	18.3	19.3	20.3
M22759/80-10-*	10	37 X 26	.106	.112	1.26	.119	.123	28.8	30.1	31.4

1/ PART NUMBER: THE ASTERISKS IN THE PART NUMBER COLUMN OF TABLE 1 SHALL BE REPLACED BY COLOR CODE DESIGNATORS IN ACCORDANCE WITH MIL-STD-681. EXAMPLES: M22759/80-20-93 IS A 20 AWG WHITE WITH ORANGE STRIPE.

2/ THE ACCEPTABLE VALUE FOR THE CPK FOR THE FINISHED WIRE WEIGHT LISTED SHALL BE 1.3, USING A NORMAL (GAUSSIAN) DISTRIBUTION TO OBTAIN THOSE CPK VALUES.

3/ CONDUCTOR SHALL CONFORM TO AS29606 TYPE TCC SMALL DIAMETER TIN COATED COPPER CONDUCTOR.

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AS22759/80C>



CUSTODIAN: AE-8/AE-8D

PROCUREMENT SPECIFICATION:



**AEROSPACE STANDARD**

(R) WIRE, ELECTRICAL, POLYTETRAFLUOROETHYLENE/ POLYIMIDE INSULATED, LIGHT WEIGHT, TIN COATED, COPPER CONDUCTOR, 150 °C, 600 VOLT, ROHS

**AS22759/80**  
SHEET 1 OF 4

**REV. C**

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

REV. C  
AS22759/80

ISSUED 2000-06 REAFFIRMED 2006-12 REVISED 2015-03

REQUIREMENT: ALL REQUIREMENTS SHALL CONSIST OF THIS DOCUMENT AND THE LATEST ISSUE OF AS22759.

1. WIRE CONSTRUCTION:

WIRE CONSTRUCTION SHALL BE IN ACCORDANCE WITH FIGURE 1 AND TABLES 1, 2, 3, AND 4.

**TABLE 2 - WIRE INSULATION MATERIALS**

TAPE CODE	THICKNESS (NOM)	MATERIAL
1	.0012	.00045 (FP)/.00065 (POLYIMIDE)/.0001 (FP)
2	.0020	FP (UNSINTERED)
3	.0025	FP (UNSINTERED)

**TABLE 3 - TAPE OVERLAP REQUIREMENTS 1/**

WIRE SIZE	WRAP 1				WRAP 2			NOMINAL WALL THICKNESS (MILS)
	TAPE CODE	PERCENT OVERLAP		TAPE CODE	PERCENT OVERLAP			
		MIN	MAX		MIN	MAX		
26	1	50.5	54.0	2	50.5	54.0	5.8	
24	1	50.5	54.0	2	50.5	54.0	5.8	
22	1	50.5	54.0	2	50.5	54.0	5.8	
20	1	50.5	54.0	2	50.5	54.0	5.8	
18	1	50.5	54.0	2	50.5	54.0	5.8	
16	1	50.5	54.0	2	50.5	54.0	5.8	
14	1	50.5	54.0	2	50.5	54.0	5.8	
12	1	50.5	54.0	3	50.5	54.0	6.7	
10	1	50.5	54.0	3	50.5	54.0	6.7	

1/ WRAP 1 IS INNERMOST TAPE WHICH IS IN CONTACT WITH THE CONDUCTOR. THAT INNERMOST TAPE SHALL HAVE THE .00045 INCH FP LAYER AGAINST THE CONDUCTOR.

2. WIRE PERFORMANCE RATING:

TEMPERATURE RATING: 150 °C (302 °F) MAXIMUM CONDUCTOR CONTINUOUS TEMPERATURE.

VOLTAGE RATING: 600 VOLTS (RMS) AT SEA LEVEL. THIS INSULATION SYSTEM HAS BEEN USED IN AEROSPACE APPLICATIONS USING 115 VOLTS (PHASE TO NEUTRAL), 400 HERTZ AC AND 28 VOLTS DC. VERIFICATION OF THE SUITABILITY OF THIS PRODUCT FOR USE IN OTHER ELECTRICAL SYSTEM CONFIGURATIONS IS THE RESPONSIBILITY OF THE USER.

3. MATERIALS AND PHYSICAL PROPERTIES:

SEE AS22759 FOR MATERIAL REQUIREMENT. MATERIALS USED IN THE MANUFACTURE OF THESE PRODUCTS SHALL COMPLY WITH THE RESTRICTION OF HAZARDOUS SUBSTANCES DIRECTIVE 2002/95/EC.

4. FINISH WIRE INSULATION PROPERTIES:

FINISH WIRE INSULATION PROPERTIES SHALL BE IN ACCORDANCE WITH TABLE 4.

SAENORM.COM : Only to view the full file of AS22759-80C

**TABLE 4 - FINISHED WIRE INSULATION PROPERTIES REQUIREMENTS**

INSULATION PROPERTIES	
IMPULSE TEST VOLTAGE	8.0 KILOVOLTS (PEAK)
HIGH FREQUENCY TEST VOLTAGE	5.7 KILOVOLTS (RMS)
INSULATION STATE OF SINTER	3.0 JOULES PER GRAM MAXIMUM
TAPE OVERLAP	TABLE 3
LAMINATION SEALING	260 °C ± 2 °C (500 °F ± 3.6 °F), 6 HOURS
INSULATION BLOCKING	200 °C ± 2 °C (392 °F ± 3.6 °F)
SHRINKAGE	230 °C ± 2 °C (446 °F ± 3.6 °F)
	MAXIMUM CHANGE .091 INCHES
ELECTRICAL RESISTANCE (IR)	5000 MEGOHMS (MIN)-1000 FEET
WET DIELECTRIC VOLTAGE	2500 VOLTS (RMS), 60 HERTZ
INSULATION STRIP FORCE	.25 - 6.0 POUNDS: WIRE SIZES 26 - 20
	.50 - 7.0 POUNDS: WIRE SIZES 18 - 14
UV LASER MARKING	55% MINIMUM AVERAGE
CONTINUOUS LENGTH SCHEDULE	B

5. FINISH WIRE IDENTIFICATION:

WIRE IDENTIFICATION EXCEPTIONS: NONE

WIRE IDENTIFICATION DURABILITY: 125 CYCLES (250 STROKES) WITH 250 GRAMS WEIGHT

STRIPE AND BAND DURABILITY: 125 CYCLES (250 STROKES) WITH 250 GRAMS WEIGHT

6. FINISH WIRE PERFORMANCE:

FINISH WIRE FIXTURES APPLICABLE TO EACH WIRE SIZE SHALL BE IN ACCORDANCE WITH TABLE 5.

**TABLE 5 - TEST MANDREL AND TEST LOAD REQUIREMENTS**

WIRE SIZE (AWG)	TEST MANDREL DIAMETER <sup>1/</sup> (INCHES)			TEST LOAD <sup>1/</sup> (LB)	
	COLD BEND	LIFE CYCLE/ BEND TEST	WRAP	COLD BEND	LIFE CYCLE/ BEND TEST
26	1.00	.375	.125	3.00	.50
24	1.00	.500	.125	3.00	.75
22	1.00	.500	.125	4.00	1.00
20	1.00	.500	.125	4.00	1.50
18	1.50	.750	.250	5.00	2.00
16	1.50	1.00	.250	5.00	2.00
14	2.00	1.00	.375	5.00	3.00
12	2.00	1.50	.375	5.00	3.00
10	3.00	2.00	.375	6.00	3.00

<sup>1/</sup> TOLERANCE SHALL BE ±3% OF THE GIVEN VALUES.