

REV.  
A

AS22759/85

NOTICE

FEDERAL SUPPLY CLASS  
6145


THIS DOCUMENT HAS BEEN TAKEN DIRECTLY FROM U.S. MILITARY SPECIFICATION MIL-DTL-22759/85A AND CONTAINS ONLY MINOR EDITORIAL AND FORMAT CHANGES REQUIRED TO BRING IT INTO CONFORMANCE WITH THE PUBLISHING REQUIREMENTS OF SAE TECHNICAL STANDARDS. THE INITIAL RELEASE OF THIS DOCUMENT IS INTENDED TO REPLACE MIL-DTL-22759/85A. ANY PART NUMBERS ESTABLISHED BY THE ORIGINAL SPECIFICATION REMAIN UNCHANGED.

THE ORIGINAL MILITARY SPECIFICATION WAS ADOPTED AS AN SAE STANDARD UNDER THE PROVISIONS OF THE SAE TECHNICAL STANDARDS BOARD (TSB) RULES AND REGULATIONS (TSB 001) PERTAINING TO ACCELERATED ADOPTION OF GOVERNMENT SPECIFICATIONS AND STANDARDS. TSB RULES PROVIDE FOR (A) THE PUBLICATION OF PORTIONS OF UNREVISED GOVERNMENT SPECIFICATIONS AND STANDARDS WITHOUT CONSENSUS VOTING AT THE SAE COMMITTEE LEVEL, AND (B) THE USE OF THE EXISTING GOVERNMENT SPECIFICATION OR STANDARD FORMAT.

UNDER DEPARTMENT OF DEFENSE POLICIES AND PROCEDURES, ANY QUALIFICATION REQUIREMENTS AND ASSOCIATED QUALIFIED PRODUCTS LISTS ARE MANDATORY FOR DOD CONTRACTS. ANY REQUIREMENT RELATING TO QUALIFIED PRODUCTS LISTS (QPL'S) HAS NOT BEEN ADOPTED BY SAE AND IS NOT PART OF THIS SAE TECHNICAL DOCUMENT.

SAENORM.COM : Click to view the full PDF of as22759\_85a

THIRD ANGLE PROJECTION



ISSUED 2000-06 REVISED 2004-10

CUSTODIAN: SAE AE-8/AE-8D

**SAE Aerospace**  
An SAE International Group

**AEROSPACE STANDARD**

WIRE, ELECTRICAL, POLYTETRAFLUOROETHYLENE/  
POLYIMIDE INSULATED, NORMAL WEIGHT, TIN  
COATED, COPPER CONDUCTOR, 150°C, 600-VOLT

**AS22759/85**  
SHEET 1 OF 6

**REV.  
A**

Copyright 2004 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.


TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Fax: 724-776-0790

Tel: 724-776-4970 (outside USA)  
Email: custsvc@sae.org

SAE WEB ADDRESS: <http://www.sae.org>

THE REQUIREMENTS FOR ACQUIRING THE PRODUCT DESCRIBED HEREIN SHALL CONSIST OF THIS SPECIFICATION SHEET AND THE ISSUE OF THE FOLLOWING SPECIFICATION LISTED IN THAT ISSUE OF THE DEPARTMENT OF DEFENSE INDEX OF SPECIFICATIONS AND STANDARDS (DODISS) SPECIFIED IN THE SOLICITATION: MIL-W-22759.

REVISION A IS EDITORIAL ONLY, FOR INSERTION OF THE FOLLOWING STATEMENT. "THIS SPECIFICATION IS NOT INTENDED FOR USE IN NAVAL AIRCRAFT OR NAVAL AIR SYSTEMS APPLICATIONS."



1/ Braid: Bright aromatic polyamide yarn, 200 Denier, 100 filaments, tightly formed, uniform in appearance, treated with a clear finisher coating. The finisher coating shall be compatible with the temperature rating and performance requirements of the insulated wire.

FIGURE 1. GENERAL CONFIGURATION.

SAENORM.COM : Click to view the full PDF of as22759-85a

TABLE I. CONSTRUCTION DETAILS.

| Part No. <sup>1/</sup> | Wire Size | Conductor   |                   |       | Finished Wire   |                   |       |                                      |
|------------------------|-----------|---|-------------------|-------|---|-------------------|-------|--------------------------------------|
|                        |           | Stranding<br>(number of<br>strands<br>x AWG<br>gauge of<br>strands) | Diameter<br>(in.) |       | Resistance<br>at 20° C<br>(68°F)<br>(ohms/ 1000<br>ft max.) | Diameter<br>(in.) |       | Weight<br>(lb./1000<br>Ft)<br>(Max.) |
|                        |           |   | MIN.              | MAX.  |   | Min.              | Max.  |                                      |
| M22759/85-2 -*         | 2         | 665 x 30  | 0.320             | 0.340 | 0.183   | 0.360             | 0.380 | 227.0                                |
| M22759/85-1 -*         | 1         | 817 x 30  | 0.366             | 0.380 | 0.149   | 0.400             | 0.420 | 295.0                                |
| M22759/85-01 -*        | 0         | 1045 x 30   | 0.395             | 0.425 | 0.116   | 0.442             | 0.462 | 351.0                                |
| M22759/85-02 -*        | 00        | 1330 x 30   | 0.440             | 0.475 | 0.091   | 0.498             | 0.528 | 432.0                                |
| M22759/85-03 -*        | 000       | 1665 x 30   | 0.500             | 0.540 | 0.071   | 0.554             | 0.584 | 542.0                                |
| M22759/85-04 -*        | 0000      | 2109 x 30   | 0.565             | 0.605 | 0.056   | 0.615             | 0.655 | 689.0                                |

<sup>1/</sup> Part Number: The preferred color is dark green with the color designator 5D. Example: Size 2 dark green - M22759/85-2-5D. White is an acceptable alternate with a color designator of 9.

TABLE II. WIRE INSULATION MATERIALS. <sup>1/</sup>

| Tape code | Thickness Nominal | Material                                       |
|-----------|-------------------|--|
| 1         | 0.0020            | 0.0005 (FPFP)/0.0010 (Polyimide)/0.0005 (FPFP) |
| 2         | 0.0020            | FP (Skived)                                    |
| 3         | 0.0030            | FP (Unsintered)                                |

<sup>1/</sup> Physical properties of FP tapes (skived and unsintered) shall be in accordance with MIL-W-22759 requirements.

TABLE III. PHYSICAL PROPERTIES OF FP/POLYIMIDE/FP TAPES.

|                          |   |
|--------------------------|---|
| Tensile Strength         | 19,000 lb/in sq. (average minimum)  |
| Tensile Modulus          | 350,000 lb/in sq. (average minimum)   |
| Elongation               | 40 percent (average minimum)  |
| Dielectric Strength      | 4,000 volts/mil (average minimum)   |
| 0.0005 FP Layer (bottom) | Distinguishable color (next to conductor)<br>May be used at manufacturer's option |

TABLE IV. TAPE OVERLAP REQUIREMENTS. 1/

| Wire Size | Wrap 1    |                 |      | Wrap 2    |                 |      | Wrap 3    |                 |      | Wrap 4    |                 |      | Nominal Wall Thickness (mils) <sup>2/</sup> |
|-----------|-----------|-----------------|------|-----------|-----------------|------|-----------|-----------------|------|-----------|-----------------|------|---|
|           | Tape Code | Percent Overlap |      | Tape Code | Percent Overlap |      | Tape Code | Percent Overlap |      | Tape Code | Percent Overlap |      |   |
|           |           | Min             | Max  |   |
| 2         | 2         | 20.5            | 35.0 | 1         | 50.5            | 55.0 | 3         | 50.5            | 54.0 | 3         | 50.5            | 54.0 | 16.2  |
| 1         | 2         | 20.5            | 35.0 | 1         | 50.5            | 55.0 | 3         | 50.5            | 54.0 | 3         | 50.5            | 54.0 | 16.2  |
| 1/0       | 2         | 20.5            | 35.0 | 1         | 50.5            | 55.0 | 3         | 50.5            | 54.0 | 3         | 50.5            | 54.0 | 16.2  |
| 2/0       | 2         | 20.5            | 35.0 | 1         | 50.5            | 55.0 | 3         | 50.5            | 54.0 | 3         | 50.5            | 54.0 | 16.2  |
| 3/0       | 2         | 20.5            | 35.0 | 1         | 50.5            | 55.0 | 3         | 50.5            | 54.0 | 3         | 50.5            | 54.0 | 16.2  |
| 4/0       | 2         | 20.5            | 35.0 | 1         | 50.5            | 55.0 | 3         | 50.5            | 54.0 | 3         | 50.5            | 54.0 | 16.2  |

<sup>1/</sup> Wrap 1 is innermost tape which is in contact with the conductor . Wraps 2, 3 and 4 are progressively further away from the conductor core.

<sup>2/</sup> Nominal wall thickness does not include the polyamide braid thickness.

TABLE V. FLUID TABLE.

| Test Fluid  | Test temperature (°C (°F)) | Immersion time (hrs.) |
|---|----------------------------|-----------------------|
| A. MIL-A-8243 Anti - icing and Deicing Defrosting Fluid, undiluted  | 48 - 50 (118 - 122)        | 20                    |
| B. MIL-A-8243 Anti - icing and Deicing Defrosting Fluid, diluted 60/40 (fluid/water) ratio                    | 48 - 50 (118 - 122)        | 20                    |
| C. MIL-C-43616, Cleaning Compound, Aircraft Surface, Type I   | 48 - 50 (118 - 122)        | 20                    |
| D. ASTM D1153, Methyl Isobutyl Ketone (For use in Organic Coatings)   | 20 - 25 (68 - 77)          | 168                   |
| E. SAE AS 1241, Fire Resistant Hydraulic Fluid for Aircraft   | 48 - 50 (118 - 122)        | 20                    |
| F. MIL-L-7808, Lubricating Oil, Aircraft Turbine Engine, Synthetic Base                                       | 118 - 121 (244 - 250)      | 30                    |
| G. MIL-C-87937, Cleaning Compound, Aerospace Equipment, Type II or Type IV, undiluted                         | 63 - 68 (145 - 154)        | 20                    |
| H. MIL-C-87937, Cleaning Compound, Aerospace Equipment, Type II or Type IV, diluted 25/75 (fluid/water) ratio | 63 - 68 (145 - 154)        | 20                    |
| I. TT-S-735, Standard Test Fluids: Hydrocarbon, Type I  | 20 - 25 (68 - 77)          | 168                   |
| J. TT-S-735, Standard Test Fluids: Hydrocarbon, Type II   | 20 - 25 (68 - 77)          | 168                   |
| K. TT-S-735, Standard Test Fluids: Hydrocarbon, Type IV   | 20 - 25 (68 - 77)          | 168                   |
| M. Dielectric - coolant Fluid Synthetic Silicate Ester Base, Monsanto Coolanol 25 or approved equivalent.     | 20 - 25 (68 - 77)          | 168                   |
| N. MIL-G-3056, Gasoline, Automotive , Combat  | 20 - 25 (68 - 77)          | 168                   |