


REV.
B


AS3320



NOTES:

- MATERIAL: STUD - CORROSION AND HEAT RESISTANT STEEL, AMS 5731, AMS 5732, AMS 5734 AND AMS 5737. (UNS S66286)
LOCKRING - CRES, AMS 5640. (UNS S30300)
- HEAT TREATMENT: STUD - SOLUTION AND PRECIPITATION HEAT TREATED. SEE PROCUREMENT SPECIFICATION.
- HARDNESS: 24-37 HRC, 247-344 HB, OR 260-363 HV.
- FINISH: STUD AND LOCKRING - CLEANED (PASSIVATED) PER PROCUREMENT SPECIFICATION.
- FLUORESCENT PENETRANT INSPECTION: ASTM E 1417, EXCEPT LOCKRING. ACCEPTANCE CRITERIA PER AS7482.
- PROCUREMENT SPECIFICATION: AS7482, EXCEPT STRESS RUPTURE TEST IS WAIVED, AND SPECIAL STUD END THREAD REQUIREMENTS OF AS3062 ARE NOT APPLICABLE. INCOMPLETE LEAD AND RUNOUT THREAD REQUIREMENTS ON BOTH THREADS SHALL BE AS SPECIFIED IN AS3062 FOR BOLTS.

AS AND AMS ARE SAE PUBLICATIONS
ANSI IS AMERICAN NATIONAL STANDARDS INSTITUTE PUBLICATION
ASME IS AMERICAN SOCIETY OF MECHANICAL ENGINEERS
ASTM IS AMERICAN SOCIETY FOR TESTING AND MATERIALS



CUSTODIAN: SAE E-25



AEROSPACE STANDARD

STUD - STRAIGHT, RING LOCKED,
CRES AMS 5731
.250-20UNJC X .250-28UNJF

AS3320
SHEET 1 OF 3

**REV.
B**

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

7. PERFORMANCE REQUIREMENTS WHEN INSTALLED PER NOTE 15:
 - a. STUD SHALL HAVE A MINIMUM RESISTANCE TO PULLOUT OF 5188 LBF BASED ON A MINIMUM PARENT MATERIAL SHEAR STRENGTH OF 25 KSI. TEST PROCEDURE PER NASM45909 AS APPLICABLE.
 - b. STUD SHALL PRODUCE A MINIMUM ROTATIONAL RESISTANCE VALUE OF 180 LBFxIN. TEST PROCEDURE PER NASM45909 AS APPLICABLE.
8. SURFACE TEXTURE: SYMBOLS PER ANSI Y14.36; REQUIREMENTS PER ASME B46.1. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 μ in Ra, EXCEPT SERRATIONS TO BE 250 μ in Ra, AND THREAD FLANKS AND ROOT TO BE 32 μ in Ra.
9. BREAK EDGES .003 TO .015, EXCEPT LOCKRING. NO BREAK EDGE ALLOWED ON ENTRY OF LOCKRING.
10. DIMENSIONING AND TOLERANCING: ANSI Y14.5M-1982 (ASME PUBLICATION).
- /11/ LOCKRING INTERNAL SERRATIONS TO HAVE FREE MOVEMENT ALONG STUD AXIS. DIMENSIONS APPLY WHEN LOCKRING IS AGAINST STOP TOWARD 0.250-28 THREAD.
12. DIMENSIONS IN INCHES.
13. MARK AEROSPACE STANDARD IDENTIFICATION NUMBER AND MANUFACTURER'S IDENTIFICATION ON CONTAINER.
14. DO NOT USE UNASSIGNED AEROSPACE STANDARD IDENTIFICATION NUMBERS.
15. STUD TO BE INSTALLED IN ACCORDANCE WITH AS1561 INTO HOLE PREPARATION PER AS1620.
16. THE CHANGE BAR (I) LOCATED IN THE LEFT MARGIN IS FOR THE CONVENIENCE OF THE USER IN LOCATING AREAS WHERE TECHNICAL REVISIONS, NOT EDITORIAL CHANGES, HAVE BEEN MADE TO THE PREVIOUS ISSUE OF THIS DOCUMENT. AN (R) SYMBOL TO THE LEFT OF THE DOCUMENT TITLE INDICATES A COMPLETE REVISION OF THE DOCUMENT.

SAENORM.COM : Click to view the full PDF of as3320b