


RATIONALE

THIS DOCUMENT HAS BEEN REAFFIRMED TO COMPLY WITH THE SAE 5-YEAR REVIEW POLICY.


AS3415

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.



1. FOR PART NUMBERS AS3415-04 THRU AS3415-19 **-B-** IN TOL NOTES SHALL BE CHANGED TO **-A-**.
2. MATERIAL: CORROSION AND HEAT RESISTANT NICKEL ALLOY AMS 5662.
3. MANUFACTURING SPECIFICATION: AMS 7467 EXCEPT ROLL THREAD AND COLD WORK FILLET RADIUS AFTER PRECIPITATION HARDENING.
4. FLUORESCENT PENETRANT INSPECTION PER AMS 2645.
5. SURFACE TEXTURE: SYMBOLS PER ANSI Y14.36-1978; REQUIREMENTS PER ANSI B46.1-1978. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICROINCHES Ra. EXCEPT UPSET HEAD TO BE 250 MICROINCHES Ra.
6. BREAK SHARP EDGES .003-.015 UNLESS OTHERWISE SPECIFIED.
7. DIMENSIONS IN INCHES.
8. DIMENSIONS AND TOLERANCING ANSI Y14.5M-1982.
9. DO NOT USE UNASSIGNED PART NUMBERS.

THIRD ANGLE PROJECTION



PREPARED BY SAE COMMITTEE E-25, GENERAL STANDARDS FOR AEROSPACE PROPULSION SYSTEMS



AEROSPACE STANDARD
BOLT, MACHINE - HEXAGON HEAD, PD SHANK,
AMS 5662, .3125-24UNJF-3A
(STRESS RUPTURE RESISTANT)

AS3415
SHEET 1 OF 2

ISSUED 1985-12 REAFFIRMED 2006-05