

FITTINGS, 37° FLARED, FLUID CONNECTION

1. SCOPE:

1.1 Scope:

This SAE Aerospace Standard (AS) establishes the requirements for 37° flared tube or machined cone fluid connection fittings (see Section 6) for use in all types of fluid systems.

1.2 Classification:

Fittings shall be furnished in the types and styles designated by the applicable AN, AS, MS, NAS, or other engineering standard drawings. This specification is the same as MIL-F-5509 as applicable to 37° flared tube fittings except for updated materials and process specifications and industry coordinated general improvements. It is intended to serve as a procurement specification for the fittings described herein and in Section 6.

2. REFERENCES:

2.1 Applicable Documents:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order. In the event of conflict between the text of this specification and references cited herein, the text of this specification takes precedence. Nothing in this specification, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

SAE100.COM: Click to view the full PDF of AS4841

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2005 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

SAE AS4841

2.1.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2486	Conversion Coating of Titanium Alloys, Fluoride Phosphate Type
AMS 2488	Anodic Treatment, Titanium and Titanium Alloys
AMS 4112	Aluminum Alloy Bars, Rods, and Wire, Rolled, Drawn, or Cold Finished 4.4Cu - 1.5Mg - 0.60Mn (2024-T6)
AMS 4124	Bars, Rods, and Wire, Rolled, Drawn or Cold Finished, 5.62N 2.5Mg 1.6Cu 0.23Cr
AMS 4134	Aluminum Alloy Die Forgings 4.4Cu - 0.85Si - 0.80Mn - 0.50Mg (2014-T4) Solution Heat Treated
AMS 4141	Forgings, Die, 5.6Zn - 2.6Mg - 7.6Cu - 0.23Cr, Solution and Precipitation Heat Treated
AMS 4610	Bars and Rods, Brass, Free Cutting 61.5Cu 3.1Pb 35Zn, Half Hard (H02)
AMS 4928	Titanium Alloy Bars and Forgings, 6Al-4V, Annealed, 120,000 psi (827 MPa) Yield
AMS 5639	Bars, Wire, Forgings, Tubing and Rings, 19Cr 10Ni Solution Heat Treated
AMS 5646	Bars, Forgings, Tubing and Rings, 18Cr 11Ni 0.60 (Cr + Ta), Solution Heat Treated
AMS 5648	Bars, Forgings, Tubing and Rings, 17Cr 12Ni 2.5Mo, Solution Heat Treated
AMS 6370	Steel Bars, Forgings and Rings, 0.95Cr 0.20Mo (0.28-0.30C)
AMS 6382	Steel Bars, Forgings and Rings, 0.95Cr 0.20Mo (0.38-0.43C)
AS478	Identification Marking Methods
AS1376	Alternate Dimensions, Center Body Section, Shape Fluid Fitting, Design Standard
AS1708	Fitting End, Flared, Female, Standard Dimensions for
AS4395	Fitting End - Flared Tube Connection, Design Standard
AS4396	Fitting End - Bulkhead Flared Tube Connection, Design Standard
ARP4784	Performance and Evaluation Criteria, Surface Defects, Requirements for

2.1.2 U.S. Government Publications: Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

P-C-437	Cleaning Compound, High Pressure (Steam) Cleaner
QQ-A-225/6	Aluminum Alloy Bar, Rod, and Wire; Rolled, Drawn, or Cold Finished, 2024
QQ-A-225/9	Aluminum Alloy Bar, Rod, Wire, and Special Shapes; Rolled, Drawn, or Cold Finished, 7075
QQ-A-367	Aluminum Alloy Forgings
QQ-P-35	Passivation Treatments for Corrosion-Resisting Steel
QQ-P-416	Plating, Cadmium (Electro-deposited)
QQ-S-763	Steel Bars, Wire, Shapes and Forgings, Corrosion-Resisting
MIL-S-5626	Steel: Chrome Molybdenum (4140) Bars, Rods and Forging Stock (For Aircraft Applications)
MIL-H-6083	Hydraulic Fluid, Petroleum Base, For Preservation and Operation
MIL-H-6088	Heat Treatment of Aluminum Alloys
MIL-S-6758	Steel, Chrome-Molybdenum (4130) Bars and Reforging Stock (Aircraft Quality)
MIL-H-6875	Heat Treatment of Steels (Aerospace Practice, Process For)
MIL-A-8625	Anodic Coatings, for Aluminum and Aluminum Alloys

SAE AS4841

2.1.2 (Continued):

MIL-S-8879 Screw Threads, Controlled Radius Root With Increased Minor Diameter: General Specification For

MIL-H-46170 Hydraulic Fluid, Rust Inhibited, Fire Resistant Synthetic Hydrocarbon Base

ANA Bulletin No. 431 Air Force-Navy Aeronautical Bulletin Fittings, Flared, Classification of Defects of

FED-STD-595 Colors Used in Government Procurement

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes

MS20819 Sleeve, Flared Tube Fitting

MS24385 Fitting End, Flared Tube Connection, Precision Type, Standard Dimensions

MS24386 Fitting End, Bulkhead Flared Tube Connection, Precision Type, Standard Dimensions

MS33583 Tubing End-double Flare, Standard Dimensions for

MS33584 Tubing End Standard Dimensions for Flared

MS33656 Fitting End, Standard Dimensions for Flared Tube Connection and Gasket Seal

MS33657 Fitting End, Standard Dimensions for Bulkhead Flared Tube Connection

AN818 Nut, Tube Coupling, Short

2.1.3 ANSI Publications: Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002.

ANSI/ASME B46.1 Surface Texture (Surface Roughness, Waviness, and Lay)

2.1.4 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 108 Steel Bars, Carbon, Cold-finished, Standard Quality

ASTM A 370 Steel Products, Mechanical Testing of

ASTM B 16 Specification for Free-Cutting Brass Rod, Bar and Shapes for Use in Screw Machines

ASTM B 154 Copper and Copper Alloys, Mercurous Nitrate Test for

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Fittings shall be fabricated of materials listed in Table 1 or as specified on the applicable part standard drawing.

SAE AS4841

TABLE 1 - Materials

Material	Type of Part	Form /1/	Specification	Alloy and Temper	Material Code			
Aluminum alloy	Straight fittings, nuts	Bars, rods	QQ-A-225/6	2024-T6 or T851	D			
			AMS 4112	2024-T6	D			
			QQ-A-225/9	7075-T73	W			
			AMS 4124	7075-T7351	W			
	Shape fittings, nuts	Forgings	QQ-A-367	2014-T6	D			
			AMS 4134	2014-T6	D			
			QQ-A-367	7075-T73	W			
			AMS 4141	7075-T73	W			
	Shape fittings	Bars	QQ-A-225/6	2024-T6 or T851	D			
			AMS 4112	2024-T6	D			
			QQ-A-225/9	7075-T73	W			
			AMS 4124	7075-T7351	W			
Carbon steel /2/	Fittings, nuts, sleeves	Bars, rods	ASTM A 108	1137	None			
			MIL-S-6758	4130	None			
			AMS 6370	4130	None			
			MIL-S-5626	4140	None			
			AMS 6382	4140	None			
	Shape fittings	Forgings	ASTM A 108 /3/	1137	None			
			MIL-S-6758 /3/	4130	None			
			AMS 6370	4130 Cold Finished	None			
			MIL-S-5626 /3/	4140	None			
			AMS 6382	4140 Cold Finished	None			
			Copper-base alloy, brass	Sleeves	Bars, rods	ASTM B 16	Alloy 360, half hard	B
						AMS 4610	Alloy 360, half hard	B
Corrosion-resistant steel	Fittings, nuts, sleeves	Bars	QQ-S-763	Class 304, Cond A	J			
			AMS 5639	Class 304, Cond A	J			
			QQ-S-763	Class 316, Cond A	K			
			AMS 5648	Class 316, Cond A	K			
			QQ-S-763	Class 321, Cond A	R			
			AMS 5645	Class 321, Cond A	R			
			QQ-S-763 /4/	Class 347, Cond A	S			
			AMS 5646 /4/	Class 347, Cond A	S			
			Shape fittings	Forgings	QQ-S-763	Class 304, Cond A	J	
					AMS 5639	Class 304, Cond A	J	
	QQ-S-763	Class 316, Cond A			K			
	AMS 5648	Class 316, Cond A			K			
	Titanium alloy	Fittings, nuts	Bars	AMS 4928	6Al-4V annealed	T		
				AMS 4928	6Al-4V annealed	T		
Shape fittings		Forgings	AMS 4928	6Al-4V annealed	T			
			AMS 4928	6Al-4V annealed	T			

/1/ The center body section of shape fittings machined from bar or oversized forgings shall conform to AS1376.

/2/ The hardness of finished carbon steel parts shall be 90 HRB to 31 HRC per 3.1.4. If the materials are procured with this requirement as a supplement to the specification, the purchase order shall specify that any heat treatment applied shall be per MIL-H-6875 (see 3.1.2.2).

/3/ This document is for bar from which forgings shall be made and only the chemical composition applies.

/4/ Type 347 corrosion-resistant steel shall not be used for new manufacture but type code "S" parts may be used until existing stocks are depleted.

SAE AS4841

3.1.2 Heat Treatment:

3.1.2.1 Aluminum Alloy: Aluminum alloy fittings and nuts shall be supplied in the final temper as shown in Table 1. When fitting material is purchased in other than the final temper, the process control shall be in accordance with MIL-H-6088.

3.1.2.2 Steel: When required additional processing is required to comply with the hardness requirements of 3.1.4, heat treatment shall be in accordance with MIL-H-6875.

3.1.3 Internal Strain of Copper-base Alloys: Fittings fabricated from copper-base alloys shall have no internal strain as revealed by the test specified in 4.4.2. After testing, the parts shall be examined, any evidence of cracks indicates internal strain and is not acceptable.

3.1.4 Additional Physical Properties: Unless otherwise specified on the applicable drawings, the hardness of the finished carbon steel parts with plating removed shall be 92 HRB to 31 HRC. For carbon steel fittings below a hardness of 20 HRC, hardness tests shall be made using the Rockwell B scale, in which case the hardness shall be within the range of 92 to 99 HRB.

3.2 Design and Fabrication:

The design and fabrication of the fittings shall be in accordance with the applicable drawings. The fitting and tube ends shall be in accordance with AS1708, AS4395, AS4396, MS24385, MS24386, MS33583, MS33584, MS33656, or MS33657 as applicable. Dimensional requirements are applicable after heat treatment and protective finishing. The center body section of shape fittings machined from bar or oversized forgings shall conform to AS1376.

3.2.1 Shape and Form Restrictions: Abrupt reductions of section shall be avoided. Small external sections adjoining relatively heavy body sections shall be transition into the heavier sections by means of ample fillets.

3.2.2 Passages:

3.2.2.1 Drill Offset: On straight fittings where the fluid passage is drilled from each end, the offset between the drilled holes at the meeting point of the drills shall not exceed .015 in. It shall be possible to pass through the fluid passage a ball whose diameter is .020 less than the minimum diameter specified for the passage. This does not mean that the drilled passage may be smaller than that required by the detail drawings.

3.2.2.2 Cross Section at Fluid Path Junction: On shape fittings, the cross-sectional area at the junction of fluid passages shall be such that it shall be possible to pass through the fitting from end to end, a ball whose diameter is not less than .7 times the minimum diameter specified for the smaller passage.


SAE AS4841

3.2.3 Threads: Straight threads shall be of unified form and shall conform to MIL-S-8879 unless otherwise specified. Steel, corrosion-resistant steel, and aluminum alloy threads may be cut, ground, or rolled (see 3.2.3.1). Copper alloy threads shall be cut or ground only.

3.2.3.1 Rolled External Threads: Laps and seams, whose depths are within the limits of Table 2, are acceptable on the crest, and the nonpressure thread flank above the pitch diameter. Laps and seams are not acceptable on any part of the pressure thread flank, in the thread root, or on the nonpressure thread flank extending from above to below the pitch diameter (see Figure 1). Stress cracks are unacceptable.

TABLE 2 - Depth of Laps, Seams, Surface Irregularities, and Discontinuities in Rolled Threads

Size Code	Depth, Inch, Max
02	.006
03	.006
04	.007
05	.007
06	.008
08	.009
10 through 32	.010



LAPS NOT EXCEEDING .0008 IN DEPTH ARE PERMISSIBLE IN THREAD RUNOUT AREA.

FIGURE 1 - Laps and Surface Irregularities in Threads

3.3 Finish:

3.3.1 Aluminum Alloy Fittings: Aluminum alloy fittings, sleeves, and nuts shall be anodized in accordance with MIL-A-8625, Type II, Class 2, dyed blue or brown as applicable (see 3.4.4) and shall be duplex sealed.

SAE AS4841

- 3.3.2 Carbon Steel Fittings: Carbon steel fittings, sleeves, and nuts shall be cadmium plated in accordance with QQ-P-416, Type II, Class 2, dyed black (see 3.4.4). All such carbon steel fittings, sleeves, and nuts shall be dipped in oil conforming to MIL-H-6083 or MIL-H-46170. Fluid passage holes, other openings, and internal threads shall not be subject to a plating thickness requirement and may exhibit bare areas provided that they are protected with a light film of oil.
- 3.3.3 Corrosion-Resistant Steel Fittings: Corrosion-resistant steel fittings, nuts, and sleeves shall be passivated per QQ-P-35, Type VI or VII.
- 3.3.4 Copper-base Alloy Fittings: Plating of copper-base alloy fittings in accordance with QQ-P-416, Type II, Class 3 is optional.
- 3.3.5 Titanium Alloy Fittings: Titanium alloy fittings and nuts shall be anodized per AMS 2488 Type 2 or shall be fluoride phosphated coated per AMS 2486, except that a pretreatment, a modification of the fluoride treatment, or a post treatment shall be applied so that the final color of the fittings shall be similar to colors 36076 through 36176 per FED-STD-595 (see 3.4.4).
- 3.4 Identification of Product:

All fittings, nuts, and sleeves shall be marked in accordance with the following instructions. The marking shall be applied per AS478 as specified on the applicable drawing in a location not detrimental to the performance of the fitting and not detrimental to the corrosion protection of the fitting. When items cannot be physically marked because of lack of space or because marking would have a deleterious effect, the package shall provide the identification per 5.4.

- 3.4.1 Manufacturer's Identification: Unless otherwise specified, all fittings and nuts shall be marked with the manufacturer's name, CAGE code or trademark and the letters AN, MS, AS, or NAS as applicable. Sleeves may be trademarked only.
- 3.4.2 Material Identification: Fittings, nuts, and sleeves shall be marked with the material code letter as shown in Table 1.
- 3.4.3 Marking for Part Number and Size: A numerical size code equivalent to the nominal tube size in .062 in increments is optional. All fittings and nuts larger than 06 fitting size code except cap assemblies, shall be marked with the basic part number, exclusive of size. Marking of part numbers on sleeves is optional. Fitting assemblies with assembled nuts shall be marked as above on the fitting body, but assembled nuts that have their own part number identification are acceptable. Fittings previously manufactured to AN, AS, MS, or NAS standards that meet all other requirements of this document and the applicable part standards may retain their identification in addition to the previous requirements.

SAE AS4841

3.4.4 Color Identification: In addition to the markings specified, the fittings, nuts, and sleeves shall be identified by the following colors:

- a. Aluminum alloys 2014 and 2024: Blue (see 3.3.1)
- b. Aluminum alloy 7075: Brown (see 3.3.1)
- c. Steel: Black (see 3.3.2)
- d. Copper-base alloys: Natural cadmium plate, if applicable (see 3.3.4)
- e. Corrosion-resistant steel: None
- f. Titanium alloy: Gray (see 3.3.5)

3.5 Carbon Steel Sleeve Expansion:

Sleeves per MS20819 or equivalent fabricated from carbon steel shall meet the load values shown in Table 3 when subjected to the expansion test of 4.4.3.

TABLE 3 - Expansion Test Load Values for Standard MS20819 or Equivalent Carbon Steel Sleeves

Size Code	Load lb ±10 lb	Size Code	Load lb ±10 lb
02	1700	12	7400
03	2200	16	8400
04	1950	20	11 700
05	1950	24	15 350
06	2050	28	16 950
08	4200	32	18 700
10	4100		

3.6 Workmanship:

Machined surfaces of fittings, sleeves, and nuts shall be as specified on the applicable drawings. Unmachined surfaces, such as forged surfaces and bar stock flats, shall be free from blisters, fins, folds, seams, laps, cracks, segregations, spongy areas, or other defects as specified in ARP4784. Surface defects may be explored by suitable etching and if they can be removed so that they do not appear on re-etching and the required section thickness can be maintained, they shall not be cause for rejection. The surface texture of unmachined surfaces, except forging parting lines, shall be 250 µin Ra per ANSI/ASME B46.1. The surface texture of forging parting planes shall be 500 µin Ra per ANSI/ASME B46.1.

SAE AS4841

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

Unless otherwise specified in the contract or purchase order, the supplier is responsible for performing the inspection and test requirements. Except as otherwise specified, the supplier may utilize their own facilities or any commercial laboratory acceptable to the purchaser for the performance of the inspection and test requirement. The purchaser reserves the right to perform any of the inspections and tests set forth in this document, whenever such inspections and tests are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection Lot:

A lot shall consist of all the fittings of a given part number, made from the same batch of material and processed at the same time.

4.2.1 Material Certification: Records of the chemical composition analysis and mechanical property tests showing conformance to the material requirements of this document shall be available to the procuring activity upon request for each lot of fittings except that for aluminum alloys a certificate of conformance to the chemical analysis requirement may be furnished in lieu of an actual chemical analysis test report.

4.3 Quality Conformance Inspection:

4.3.1 Sampling:

4.3.1.1 Sampling for Nondestructive Tests: Samples for heat treatment, threads, finish, dimensions, marking, surface defects, durability of finish, and workmanship shall be taken at random in accordance with MIL-STD-105, Inspection Level S-3 with an AQL of 4.0%, unless otherwise specified in ANA Bulletin No. 431. ANA Bulletin No. 431 will not be used for government purposes. Government acceptance will be based upon a sampling plan which accepts on zero defects.

4.3.1.2 Sampling for Destructive Tests: Sampling for hardness (4.4.1), internal strain of copper-base alloys (4.4.2), and expansion test of carbon steel sleeves (4.4.3) shall be performed in accordance with MIL-STD-105, Inspection Level S-3, with an AQL of 4.0%. Government acceptance will be based upon a sampling plan which accepts on zero defects.

4.3.2 Examination and Inspection Methods: Each lot of fittings shall be examined and inspected as specified in Table 4.

SAE AS4841

TABLE 4 - Quality Conformance Inspection

Examination or Inspection	Requirement Paragraph	Examination or Inspection Paragraph
Material requirements	3.1	4.2.1
Internal strain of copper-base alloys	3.1.3	4.4.2
Hardness of carbon steel fittings	3.1.4	4.4.1
Design and dimensions	3.2	4.3.2.1
Finish	3.3	4.3.2.1, 4.4.4
Identification of product	3.4	4.3.2.1
Expansion test of carbon steel sleeves	3.5	4.4.3
Workmanship	3.6	4.3.2.1

4.3.2.1 Examination of Product: Using the sampling of 4.3.1, each lot of fittings will be examined to determine conformance with this document and the applicable standard with respect to material, dimensions, passages, threads, wall thickness, surface defects, finish, marking, and workmanship.

4.4 Tests:

4.4.1 Hardness of Steel Fittings: The hardness of steel fittings shall be determined by hardness tests of the fittings. Rockwell hardness readings shall be taken on a smooth flat surface of any unthreaded portion of the fitting from which the plating has been removed. Hardness tensile strength relationships are specified in ASTM A 370. For this document, the hardness scale to scale conversions and hardness to tensile strength conversions of Tables 2A, 2B, 2C, and 2D of ASTM A 370 may be considered as equivalent.

4.4.2 Internal Strain of Copper-base Alloys: Fittings fabricated from copper-base alloys, as specified herein, shall be tested per ASTM B 154.

4.4.3 Expansion Test of Carbon Steel Sleeves: Sleeves shall be selected as required by 4.3.1 and submitted to an expansion test. The test shall be performed with a tapered arbor and a holding device as shown in Figure 2. The arbor shall be loaded as required by the values given in Table 3. The head of the sleeve shall be expanded by the load applied through the tapered arbor. The maximum expansion of the outside diameter shall be measured with the load applied. This measurement shall be taken in at least two places 90° apart on the diameter. The average measurement shall be recorded and compared with the minor diameter of the threads of the mating nut, AN818 or equivalent. The average expanded diameter shall not exceed the minimum minor diameter of the threads. This test is in addition to and does not supplant the required dimensional inspection of carbon steel sleeves, which shall be conducted prior to the expansion test.

SAE AS4841




FIGURE 2 - Fixture for Testing Sleeves
Dimensions in Inches, See Table 5

SAE AS4841

TABLE 5 - Dimensions, Sleeve Test Fixture

Size	A +.003/-.000	B Min	C Min
02	.180	.750	.460
03	.242	.750	.500
04	.305	.750	.560
05	.374	.750	.560
06	.440	1.250	.590
08	.570	1.250	.590
10	.698	1.250	.340
12	.834	1.750	.680
16	1.089	1.750	.750
20	1.347	2.000	.840
24	1.617	2.250	1.010
28	1.890	3.000	1.000
32	2.167	3.000	1.010

4.4.4 Durability of Finish: Dyed fittings shall withstand immersion in a cleaning solution containing 5 to 6 oz of a cleaner conforming to P-C-437 per gallon of solution at a temperature of 160 to 170 °F for 5 min. The color shall not rub off when wiped lightly with a clean cloth.

4.5 Rejection and Retest:

Rejected lots shall be resubmitted for retest and acceptance in accordance with MIL-STD-105. Those fittings subjected to individual examination other than tests (see 4.3.2.1) and failing to meet the requirements shall be rejected. Copper-base alloy fittings that have been subjected to the internal strain test (4.4.2) and steel fittings which have been subjected to the hardness test (4.4.1) or the expansion test (4.4.3) shall be discarded, whether they pass the test or not.

5. PREPARATION FOR DELIVERY:

5.1 Cleaning:

Surfaces of fittings shall be free of oil, grease, dirt, and other foreign material except as noted in 5.2.

5.2 Preservation Application:

No preservative compound shall be applied except that cadmium plated steel parts shall be dipped in oil as specified in 3.3.2.