



The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space®

**INTERNATIONAL**

400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE STANDARD

**SAE AS7110/3**

Rev  
A

Submitted for recognition as an American National Standard

Issued: 1995-03

Revised: 1997-11

## NATIONAL AEROSPACE AND DEFENSE CONTRACTORS ACCREDITATION PROGRAM REQUIREMENTS FOR ELECTRON BEAM WELDING

### 1. SCOPE

This Aerospace Standard (AS) is to be used to supplement AS7110. In addition to the requirements contained in AS7110, the requirements contained herein shall apply to suppliers seeking NADCAP accreditation for electron beam welding.

### 2. REFERENCES

#### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AS7110 National Aerospace and Defense Contractors Accreditation Program  
(NADCAP) - Requirements for Welding

### 3. REFERENCE REQUIREMENTS

3.1 Applicable customer specifications shall be available at the facility.

### 4. MATERIAL/MATERIALS CONTROL

4.1 Base materials shall be as specified in applicable part drawings.

4.2 When required, filler metals shall be as specified on part drawings or customer specifications.

4.3 Cleaning materials, chemical solvents, or etching solutions shall be as specified on part drawings or certified/qualified welding procedures/schedules.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1997 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A

**QUESTIONS REGARDING THIS DOCUMENT:** (412) 772-8510 FAX (412) 776-0243  
**TO PLACE A DOCUMENT ORDER:** (412) 776-4970 FAX (412) 776-0790

## SAE AS7110/3 Revision A

- 4.4 Unless otherwise approved by procedure certification, all back-up materials used to absorb residual electron beam energy shall be the same alloy as the part being welded.
5. EQUIPMENT CONTROL
- 5.1 The electron beam (EB) equipment shall be capable of producing welds meeting customer specifications.
- 5.2 Equipment shall be qualified in accordance with applicable customer specifications if required.
- 5.3 All holding fixtures shall be capable of maintaining the desired configuration and tolerances during welding, providing back-up as required, and allowing the required work space between the workpiece and the gun.
- 5.4 Magnetic materials and tooling, prior to welding, shall be degaussed to a level established by procedure certification.
6. QUALIFICATION OF WELD PROCEDURE/SCHEDULE
- 6.1 Weld procedures/schedules shall:
- a. Identify those parameters specified by appropriate customer specifications
  - b. Be qualified in accordance with applicable customer specifications prior to production welding
  - c. Be requalified after failed test welds
  - d. Be requalified when a change is made in essential parameters
7. PROCESS CONTROL
- 7.1 Preparation
- 7.1.1 Joints shall be prepared in accordance with applicable specifications, drawings, or work instructions.
- 7.1.2 Edges shall be machined and parallel to each other to assure proper fit-up.
- 7.1.3 Joints shall be deburred after machining without rounding off the edges.
- 7.1.4 When specified, witness lines or features shall be applied in accordance with part drawings.

## SAE AS7110/3 Revision A

- 7.1.5 When run-on/run-off tabs are used, they shall be the same alloy as the part being welded.
- 7.1.6 When run-on/run-off tabs are used, they shall be removed after welding in such a manner as to prevent damage.
- 7.1.7 Surfaces of parts to be welded shall be prepared using chemical and/or mechanical cleaning or combinations thereof as applicable in accordance with customer requirements to the alloy being welded.
- a. Welding shall commence within customer specified time limits.
  - b. After surface preparation, parts shall be handled in the joint area with clean, lint-free gloves and covered or otherwise protected to prevent contamination.
- 7.1.8 Jigs, fixtures, and measuring devices shall be free of scale, grease, protective coatings, oxides, dust, oil, and other foreign matter detrimental to the welding process.
- 7.1.9 Gaps for production welds shall be equal to or less than those used for procedure/schedule certification.
- 7.1.10 When required, process control tests shall be performed per customer requirements (coupons/part cut-up).
- 7.2 Production Welding
- 7.2.1 EB welding shall be performed by operators qualified in accordance with applicable customer specifications.
- 7.2.2 EB welding shall be performed in a vacuum of  $10^{-4}$  TORR or better.
- 7.2.3 Each weld shall be traceable to the date of welding and the welding operator.
- 7.2.4 For each arc-out, the location and reason (if known) shall be recorded, when required by customer.
- 7.2.5 When required, tack welding of details shall be accomplished by EB welding only.
- 7.2.6 When tack welding is permitted and performed using a process other than electron beam, the tack personnel shall be qualified in accordance with customer requirements.
- 7.2.7 Tack welds shall be totally consumed by the finished weld.