

AS81820/2

NOTICE

THIS DOCUMENT HAS BEEN TAKEN DIRECTLY FROM U.S. MILITARY SPECIFICATION MIL-B-81820/2A AND CONTAINS ONLY MINOR EDITORIAL AND FORMAT CHANGES REQUIRED TO BRING IT INTO CONFORMANCE WITH THE PUBLISHING REQUIREMENTS OF SAE TECHNICAL STANDARDS. THE INITIAL RELEASE OF THIS DOCUMENT IS INTENDED TO REPLACE MIL-B-81820/2A. ANY PART NUMBERS ESTABLISHED BY THE ORIGINAL SPECIFICATION REMAIN UNCHANGED.

THE ORIGINAL MILITARY SPECIFICATION WAS ADOPTED AS AN SAE STANDARD UNDER THE PROVISIONS OF THE SAE TECHNICAL STANDARDS BOARD (TSB) RULES AND REGULATIONS (TSB 001) PERTAINING TO ACCELERATED ADOPTION OF GOVERNMENT SPECIFICATIONS AND STANDARDS. TSB RULES PROVIDE FOR (A) THE PUBLICATION OF PORTIONS OF UNREVISED GOVERNMENT SPECIFICATIONS AND STANDARDS WITHOUT CONSENSUS VOTING AT THE SAE COMMITTEE LEVEL, AND (B) THE USE OF THE EXISTING GOVERNMENT SPECIFICATION OR STANDARD FORMAT.

UNDER DEPARTMENT OF DEFENSE POLICIES AND PROCEDURES, ANY QUALIFICATION REQUIREMENTS AND ASSOCIATED QUALIFIED PRODUCTS LISTS ARE MANDATORY FOR DOD CONTRACTS. ANY REQUIREMENTS RELATING TO QUALIFIED PRODUCTS LISTS (QPL'S) HAS NOT BEEN ADOPTED BY SAE AND IS NOT PART OF THIS TECHNICAL REPORT.

SAENORM.COM : Click to view the full PDF of as81820-2

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

ISSUED 1998-04

PREPARED BY COMMITTEE ACBG

SAE The Engineering Society
For Advancing Mobility
INTERNATIONAL
Land Sea Air and Space®
400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE STANDARD

BEARING, PLAIN, SELF-ALIGNING, SELF-LUBRICATING,
LINED BORE, LOW SPEED, WIDE, CHAMFERED
OUTER RING, -65° TO 325° F

AS81820/2
SHEET 1 OF 4

THE REQUIREMENTS FOR ACQUIRING THE PRODUCT(S) DESCRIBED HEREIN SHALL CONSIST OF THIS SPECIFICATION SHEET AND THE ISSUE OF THE FOLLOWING SPECIFICATION LISTED IN THAT ISSUE OF THE DODISS SPECIFIED IN THE SOLICITATION: MIL-B-81820.




TABLE I. DIMENSIONS AND STRENGTHS

DASH NO.	ØB +.0000 -.0010	ØD +.0000 -.0005	H ±.005	Q' (REF)	W +.000 -.002	STATIC LIMIT LOAD		OSCILLATING LOAD LB	NO-LOAD ROTATIONAL BREAKAWAY TORQUE IN-LB		WT LB MAX (REF)
						RADIAL LB	AXIAL LB		STANDARD	"K" TYPE*	
-5	.3135	.6875	.317	14	.437	9250	1640	4450	1.0-15.0	0-1.0	.035
-6	.3760	.8125	.406	8	.500	13000	2630	6200			.060
-7	.4385	.9375	.442	10	.562	17250	3650	8250			.080
-8	.5010	1.0000	.505	9	.625	21400	4970	10600			.100
-9	.5635	1.1250	.536	10	.687	26600	5370	13200			.135
-10	.6260	1.1875	.567	12	.750	29000	6130	16150			.160
-12	.7510	1.3750	.630	13	.875	37000	7730	24800	.240		
-14	.8760	1.6250	.755	6	.875	56000	10800	26750	1.0-25.0	0-2.0	.350
-16	1.0010	2.1250	1.005	12	1.375	103300	19300	49300			.970

* SEE REQUIREMENT 5 "NO-LOAD TORQUE" AND NOTE 5.

TABLE II. OVERSIZE BEARING DIMENSIONS 1/ 2/

RESTRICTED USAGE FOR REPAIR WORK ONLY

.010 AND .020 OVERSIZE OUTSIDE DIAMETER FOR
REPLACEMENT OF BEARINGS SHOWN ON SHEET 2

DASH NO.	NOMINAL SIZE	1st OVERSIZE (.010) ϕ D
-5	.3125	.6975
-6	.3750	.8225
-7	.4375	.9475
-8	.5000	1.0100
-9	.5625	1.1350
-10	.6250	1.1975
-12	.7500	1.3850
-14	.8750	1.6350
-16	1.0000	2.1350

DASH NO.	NOMINAL SIZE	2nd OVERSIZE (.020) ϕ D
-5	.3125	.7075
-6	.3750	.8325
-7	.4375	.9575
-8	.5000	1.0200
-9	.5625	1.1450
-10	.6250	1.2075
-12	.7500	1.3950
-14	.8750	1.6450
-16	1.0000	2.1450

- 1/ BEFORE INITIATING A REPAIR PROCEDURE TO USE AN OVERSIZE BEARING, APPROVAL FOR MODIFYING AND REIDENTIFYING THE BEARING HOUSING MUST BE OBTAINED FROM THE COGNIZANT ENGINEERING AUTHORITY.
- 2/ REFER TO NAS0331 FOR INSTALLATION PROCEDURE AND STAKING FORCES.

REQUIREMENTS:

- MATERIAL: BALL: PH13-8 Mo STEEL ALLOY PER AMS-5629, CONDITION H1000.
OUTER RING: 17-4 PH STEEL ALLOY PER AMS-5643.
LINER: POLYTETRAFLUOROETHYLENE (PTFE) SHALL BE INCLUDED IN THE LINER.
- SURFACE TEXTURE: BALL DIA. Ra 8; BALL FACES, Ra 16; OUTER RACE DIA Ra 32; ALL OTHER METALLIC SURFACES Ra 125. LINER SURFACES ARE EXEMPT FROM SURFACE TEXTURE MEASUREMENTS.
- SURFACE FINISH:
OUTER RACE: PLATING, WHEN SPECIFIED, SHALL BE ZINC-NICKEL PLATING PER AMS-2417, TYPE 2 OR CADMIUM PLATING PER QQ-P-416, TYPE II, CLASS 2 WITH A THICKNESS RANGE OF 0.0003 TO 0.0006 INCHES.
PLATE ON THE OUTSIDE DIAMETER SURFACE AND ON THE CHAMFER.
PLATING RUNOUT SHALL OCCUR IN THE SIDE FACE AREA BETWEEN THE CHAMFER AND THE BALL.
THE PTFE LINER IN THE OUTER RACE INSIDE DIAMETER AND IN THE BALL BORE SHALL BE PROTECTED FROM EXPOSURE TO PLATING SOLUTIONS DURING PROCESSING.
BALL: PASSIVATE PER MIL-S-5002.
- HARDNESS: BALL: Rc 43 MIN; OUTER RING: Rc 28 MIN, Rc 37 MAX BEFORE SWAGING.
- NO-LOAD TORQUE: WHEN THE LETTER "K" IS PRESENT IN THE PART NUMBER, LOWER VALUES OF NO-LOAD TORQUE ARE SPECIFIED PER TABLE I. IF THE MEASURED TORQUE OF A "K" TYPE BEARING IS LESS THAN 0.1 INCH-POUND, THE INTERNAL RADIAL CLEARANCE SHALL BE MEASURED AND SHALL NOT EXCEED THE VALUES IN TABLE III. THESE REQUIREMENTS APPLY TO THE TORQUE AND INTERNAL PLAY BETWEEN THE SPHERICAL BALL AND THE OUTER RING. THIS STANDARD DOES NOT DEFINE REQUIREMENTS FOR TORQUE OR INTERNAL PLAY BETWEEN THE BEARING BORE AND SHAFT.