

RATIONALE

THIS DOCUMENT COMPLETELY REVISED, INCLUDING RE-FORMATTING TO AN AEROSPACE STANDARD (AS) UNDER THE JURISDICTION OF SAE AE8-C1 FROM AN AEROSPACE MATERIAL SPECIFICATION UNDER THE JURISDICTION OF SAE AMS 'P' COMMITTEE, TO PROPERLY CLASSIFY AND SUPERSEDE AMS-T-81914/4 MATERIAL SPECIFICATION INCLUDING THE INCORPORATION OF COMMENTS RECEIVED FROM GOVERNMENT AND INDUSTRY, UP-DATE SPECIFICATION REFERENCES, ALIGN WITH SAE GUIDELINES AS NEEDED, INCORPORATE MATERIAL UPDATES, CLARIFY PART NUMBERING, ADD METRICS AND REVIEW FOR KNOWN TECHNICAL PROBLEMS.

NOTICE

THE REQUIREMENTS FOR ACQUIRING THE TUBING DESCRIBED HEREIN SHALL CONSIST OF THIS DOCUMENT AND THE LATEST ISSUE IN EFFECT OF SAE AS81914.





FIGURE 1 - DIMENSIONS AND CONSTRUCTION

SAENORM.COM : Click to view the full PDF of as81914-4

**SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AS81914/4>**

THIRD ANGLE PROJECTION



CUSTODIAN: AE-8/AE-8C1

PROCUREMENT SPECIFICATION: AS81914

**SAE Aerospace**  
An SAE International Group

**AEROSPACE STANDARD**

TUBING, PLASTIC, EXTRA FLEXIBLE, CONVOLUTED, HELICAL, FLUORINATED ETHYLENE PROPYLENE (FEP), CLOSE CONVOLUTION

**SAE AS81914/4**  
SHEET 1 OF 4

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

**SAE AS81914/4**

ISSUED 2011-01

TABLE 1 - FIGURE 1 DIMENSIONS

Dash Number	MAX Inside Dia. (I.D.)	MIN Inside Dia. (I.D.)	MAX Outer Dia. (O.D.)	MAX Wall Thickness	Convolutions Per Inch (CPI) ± 1	Approx. Weight Lbs (kg) Per 100 feet (30.5 m) Ref.	MIN Bend Radius
01	.188 (4.78)	.181 (4.60)	.320 (8.13)	.018 (0.46)	10	1.7 (0.77)	.31 (7.9)
02	.281 (7.14)	.273 (6.93)	.414 (10.52)	.018 (0.46)	10	2.0 (0.91)	.41 (10.4)
03	.312 (7.92)	.306 (7.77)	.450 (11.43)	.018 (0.46)	10	2.1 (0.95)	.41 (10.4)
04	.375 (9.53)	.359 (9.12)	.510 (12.95)	.018 (0.46)	10	2.5 (1.13)	.50 (12.7)
05	.437 (11.10)	.427 (10.85)	.571 (14.50)	.018 (0.46)	10	3.9 (1.77)	.50 (12.7)
06	.500 (12.70)	.480 (12.19)	.650 (16.51)	.023 (0.58)	9	4.6 (2.09)	.75 (19.1)
07	.625 (15.88)	.603 (15.32)	.770 (19.56)	.023 (0.58)	9	5.5 (2.49)	.75 (19.1)
08	.750 (19.05)	.725 (18.42)	.930 (23.62)	.023 (0.58)	8	6.9 (3.13)	.93 (23.6)
09	.875 (22.23)	.860 (21.84)	1.073 (27.25)	.023 (0.58)	7	8.9 (4.04)	1.25 (31.8)
10	1.000 (25.40)	.970 (24.64)	1.226 (31.14)	.023 (0.58)	7	9.5 (4.31)	1.25 (31.8)
11	1.125 (28.58)	1.105 (28.07)	1.390 (35.31)	.023 (0.58)	7	10.5 (4.76)	1.43 (36.3)
12	1.250 (31.75)	1.205 (30.61)	1.539 (39.09)	.023 (0.58)	6.5	11.2 (5.08)	1.43 (36.3)
13	1.500 (38.10)	1.437 (36.50)	1.832 (46.53)	.023 (0.58)	5.5	12.0 (5.44)	1.75 (44.5)
14	1.750 (44.45)	1.688 (42.88)	2.082 (52.88)	.023 (0.58)	5.5	13.5 (6.12)	2.00 (50.8)
15	2.000 (50.80)	1.937 (49.20)	2.332 (59.23)	.023 (0.58)	5.5	15.5 (7.03)	2.25 (57.2)

## NOTES:

1. DIMENSIONS ARE IN INCHES.
2. UNLESS OTHERWISE SPECIFIED TOLERANCES SHALL BE: .XX = ± .010 (0.25 MM), .XXX = ± .005 (0.13 MM).
3. METRIC EQUIVALENTS ARE GIVEN FOR GENERAL INFORMATION ONLY AND ARE BASED ON 25.4 MM = 1 INCH.
4. METRIC DIMENSIONS IN PARENTHESES ARE SHOWN IN MILLIMETERS.

## REQUIREMENTS:

1. DIMENSIONS AND CONFIGURATION: SEE FIGURE 1 AND TABLE 1.
2. CONVOLUTION TYPE: HELICAL.
3. LENGTHS SHALL BE SPECIFIED IN FEET BY THE PROCURING ACTIVITY AND DOES NOT FORM A PART OF THE IDENTIFYING PART NUMBER. MINIMUM ORDER LENGTH SHALL BE 3 FEET (0.914 M) AND THE TUBING ORDER LENGTH TOLERANCES SHALL BE AS SPECIFIED BELOW. TUBING SHALL BE PROCURED AS COILS.
4. CONTINUOUS OPERATING TEMPERATURE: -67°C (-88 °F) TO +200°C (392 °F)
5. COLOR: UNLESS OTHERWISE SPECIFIED, THE SUPPLIED COLOR SHALL BE CLEAR, NATURAL.

 An SAE International Group	<b>AEROSPACE STANDARD</b>	<b>SAE AS81914/4</b> SHEET 2 OF 4
	TUBING, PLASTIC, EXTRA FLEXIBLE, CONVOLUTED, HELICAL, FLUORINATED ETHYLENE PROPYLENE (FEP), CLOSE CONVOLUTION	

TABLE 2 - ORDER LENGTH TOLERANCE

Order Length Range	
Length in feet (meters)	Tolerance in inches (mm)
3 – 12 (0.914 m – 3.66 m)	+ 2.0 / - 0.0 (+ 50.8 mm / - 0.0 mm)
13 – 50 (3.96 m – 15.24 m)	+ 4.0 / - 0.0 (+ 101.6 mm / - 0.0 mm)
51 and up (15.55 m and up)	+ 6.0 / - 0.0 (+ 152.4 mm / - 0.0 mm)

6. PHYSICAL PROPERTIES: GENERAL PHYSICAL REQUIREMENT VALUES ALONG WITH ASSOCIATED TEST CONDITIONS ARE LOCATED IN TABLE 3.
7. SHELF LIFE: THE STORAGE/SHELF LIFE SHALL BE 20 YEARS. SEE SAE AS81914

TABLE 3 – PHYSICAL REQUIREMENTS

PROPERTY	REQUIREMENT
CONSTRUCTION DETAILS	IN ACCORDANCE WITH TABLE 1
STRESS IN PSI @ 10% STRAIN	250 TO 700
SPECIFIC GRAVITY	2.18 MAX
CRUSH RESISTANCE, HORIZONTAL	10 LBS (4.54KG) MIN.
LOW TEMPERATURE FLEXIBILITY	10 000 CYCLES, NO CRACKING
HEAT SHOCK	176/174 °C (349/345 °F) FOR 4 HOURS. 15% MAX LONGITUDINAL CHANGE. NO DRIPPING, FLOWING OR CRACKING
HEAT AGING	STRESS IN PSI @10% STRAIN, 80% OF INITIAL VALUE. 176/174 °C (351/343 °F) FOR 96 HOURS.
FLUID RESISTANCE	STRESS IN PSI @ 10% STRAIN 80% OF INITIAL VALUE
FLAMMABILITY	NON-FLAMMABLE 1/
FUNGUS RESISTANCE	NON-NUTRIENT 1/
DIELECTRIC BREAKDOWN	12 000 VOLTS, NO BREAKDOWN

1/ PROPERTIES NOT TESTED.

SAENORM.COM : Click to view the PDF of as81914-4