

**REV.
B**

AS85421/11

RATIONALE

THIS DOCUMENT IS REVISED TO INCLUDE PRI-QPL REQUIREMENTS AND REFORMATTED TO BE IN ACCORDANCE WITH SAE GUIDELINES.





FIGURE 1

SAENORM.COM : Click to view the full PDF of as85421-11b



CUSTODIAN: SAE G-3

PROCUREMENT SPECIFICATION: AS85421 /4/

SAE Aerospace
An SAE International Group

AEROSPACE STANDARD

(R) FITTING, UNION, BEAM SEAL,
3000/4000 PSI, MALE ENDS

AS85421/11
SHEET 1 OF 3

**REV.
B**

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

ISSUED 2002-01 REVISED 2006-08

TABLE 1 - DIMENSIONAL DATA

DASH NO.	TUBE O.D.	T THREAD AS8879	A	B (REF)	C (REF)	ØE (MIN)	WT. LB (MAX)	
							TI	CRES
-03	.188	.3750-28UNJS-3A	.637	.375	.156	.350	.017	.030
-04	.250	.4375-24UNJS-3A	.727	.438	.162	.413	.018	.031
-05	.312	.5000-24UNJS-3A	.739	.500	.174	.475	.021	.037
-06	.375	.5625-20UNJS-3A	.793	.562	.188	.537	.025	.045
-08	.500	.7188-20UNJS-3A	.873	.750	.242	.725	.041	.072
-10	.625	.8438-18UNJS-3A	1.051	.875	.292	.850	.073	.130
-12	.750	1.0000-16UNJ-3A	1.139	1.000	.300	.975	.102	.180
-14	.875	1.1250-16UNJ-3A	1.181	1.125	.306	1.100	.113	.200
-16	1.000	1.2500-14UNJS-3A	1.307	1.250	.372	1.225	.138	.244
-20	1.250	1.5781-14UNJS-3A	1.341	1.625	.412	1.600	.178	.316
-24	1.500	1.8438-14UNJS-3A	1.537	1.875	.438	1.850	.262	.463

NOTES:

/1/ MATERIAL:

- a. CODE LETTER P - TYPE 17-4PH CORROSION RESISTANT STEEL PER AMS 5643.
- b. CODE LETTER T - TYPE 6AL-4V TITANIUM ALLOY BAR PER AMS 4928 OR AMS 4965.
- c. CODE LETTER V - TYPE 15-5PH, CORROSION RESISTANT STEEL PER AMS 5659.

2. HEAT TREATMENT:

- a. MATERIAL CODE LETTER P - CONDITION H1075 PER AMS 2759/3.
- b. MATERIAL CODE LETTER T - NONE.
- c. MATERIAL CODE LETTER V - AGE TO CONDITION H 1075 PER AMS-H-6875 OR AMS 2759/3.

3. FINISH:

- a. MATERIAL CODE LETTER P - PASSIVATE PER AMS-QQ-P-35, TYPE VI OR VII.
- b. MATERIAL CODE LETTER T - NONE.
- c. MATERIAL CODE LETTER V - PASSIVATE PER AMS-QQ-P-35, TYPE VI OR VII.

/4/ PROCUREMENT SPECIFICATION: AS85421 EXCEPT AS SPECIFIED ON THIS STANDARD. THIS PRODUCT SHALL BE QUALIFIED IN ACCORDANCE WITH SPECIFICATION AS85421. USERS OF THIS STANDARD SHALL PROCURE THE PRODUCT FROM ACCREDITED MANUFACTURER(S), OR ACCREDITED DISTRIBUTOR(S), AS LISTED IN THE PERFORMANCE REVIEW INSTITUTE (PRI) QUALIFIED PRODUCTS LIST (QPL) PRI-QPL-AS85421 FOR THIS STANDARD. SEE <http://www.pri.sae.org/QPLas85421/> FOR CURRENT QPL ON LINE.

/5/ IDENTIFICATION AT LOCATION SHOWN: MARK PER AS578 CLASS C OR D, OR METHOD 7A3, 15A3, OR 15B.

- a. FOR SIZES 06 AND SMALLER: MANUFACTURER'S NAME, CAGE CODE OR TRADEMARK, LETTERS "AS" AND MATERIAL CODE LETTER, AND FORGING MANUFACTURER'S IDENTIFICATION WHEN MADE FROM FORGING.
- b. FOR SIZES 08 AND LARGER: MANUFACTURER'S NAME, CAGE CODE OR TRADEMARK, BASIC PART NUMBER AND MATERIAL CODE LETTER, AND FORGING MANUFACTURER'S IDENTIFICATION WHEN MADE FROM FORGING.

6. INVENTORIED PARTS CONFORMING TO THE PREVIOUS "LETTER CHANGE" MAY BE USED TO DEPLETION.