

NOTICE

THIS DOCUMENT HAS BEEN TAKEN DIRECTLY FROM U.S. MILITARY SPECIFICATION MS9847, NOTICE 1 AND CONTAINS ONLY MINOR EDITORIAL AND FORMAT CHANGES REQUIRED TO BRING IT INTO CONFORMANCE WITH THE PUBLISHING REQUIREMENTS OF SAE TECHNICAL STANDARDS. THE INITIAL RELEASE OF THIS DOCUMENT IS INTENDED TO REPLACE MS9847, NOTICE 1. ANY PART NUMBERS ESTABLISHED BY THE ORIGINAL SPECIFICATION REMAIN UNCHANGED.

THE ORIGINAL MILITARY SPECIFICATION WAS ADOPTED AS AN SAE STANDARD UNDER THE PROVISIONS OF THE SAE TECHNICAL STANDARDS BOARD (TSB) RULES AND REGULATIONS (TSB 001) PERTAINING TO ACCELERATED ADOPTION OF GOVERNMENT SPECIFICATIONS AND STANDARDS. TSB RULES PROVIDE FOR (A) THE PUBLICATION OF PORTIONS OF UNREVISED GOVERNMENT SPECIFICATIONS AND STANDARDS WITHOUT CONSENSUS VOTING AT THE SAE COMMITTEE LEVEL, AND (B) THE USE OF THE EXISTING GOVERNMENT SPECIFICATION OR STANDARD FORMAT.


UNDER DEPARTMENT OF DEFENSE POLICIES AND PROCEDURES, ANY QUALIFICATION REQUIREMENTS AND ASSOCIATED QUALIFIED PRODUCTS LISTS ARE MANDATORY FOR DOD CONTRACTS. ANY REQUIREMENT RELATING TO QUALIFIED PRODUCTS LISTS (QPL'S) HAS NOT BEEN ADOPTED BY SAE AND IS NOT PART OF THIS TECHNICAL REPORT.

SAENORM.COM : Click to view the full PDF of as9847

AS9847

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

THIRD ANGLE PROJECTION



ISSUED 1998-10 REAFFIRMED 2003-10

PREPARED BY COMMITTEE E-25

PROCUREMENT SPECIFICATION: NONE



AEROSPACE STANDARD

PIN, STRAIGHT, HEADED,
.3749 DIAMETER,
AMS 5616

AS9847
SHEET 1 OF 3

AS9847




FIGURE 1

TABLE 1

PART NO.	A	L	APPROX WEIGHT LB/100	PART NO.	A	L	APPROX WEIGHT LB/100	PART NO.	A	L	APPROX WEIGHT LB/100
				MS9847-16	.954	1.041	3.350	MS9847-31	1.892	1.959	6.250
				MS9847-17	1.017	1.104	3.550	MS9847-32	1.954	2.041	6.470
				MS9847-18	1.079	1.166	3.740	MS9847-33	2.017	2.104	6.660
				MS9847-19	1.142	1.229	3.940	MS9847-34	2.079	2.166	6.850
				MS9847-20	1.204	1.291	4.130	MS9847-35	2.142	2.229	7.050
				MS9847-21	1.267	1.354	4.330	MS9847-36	2.204	2.291	7.240
				MS9847-22	1.329	1.416	4.520	MS9847-37	2.267	2.344	7.420
				MS9847-23	1.392	1.479	4.710				
MS9847-09	.517	.604	1.990	MS9847-24	1.454	1.541	4.900				
MS9847-10	.579	.666	2.190	MS9847-25	1.517	1.604	5.100				
MS9847-11	.642	.729	2.360	MS9847-26	1.579	1.666	5.300				
MS9847-12	.704	.791	2.580	MS9847-27	1.642	1.729	5.490				
MS9847-13	.767	.864	2.770	MS9847-28	1.704	1.791	5.690				
MS9847-14	.829	.916	2.960	MS9847-29	1.767	1.854	5.860				
MS9847-15	.892	.979	3.170	MS9847-30	1.829	1.916	6.080				

NOTES:

1. MATERIAL: AMS 5616.
2. HARDNESS: ROCKWELL C45-50.
3. FLUORESCENT PENETRANT INSPECTION PER AMS 2645.
4. HEAD DIA. TO BE CONCENTRIC WITH SHANK DIA. WITHIN .003 FIR.
5. SURFACE TEXTURE: ASA B46.1-1962. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICROINCHES.
6. BREAK SHARP EDGES .003-.015.