

RATIONALE

AS9880 HAS BEEN REAFFIRMED TO COMPLY WITH THE SAE FIVE-YEAR REVIEW POLICY.

NOTICE

THIS DOCUMENT HAS BEEN TAKEN DIRECTLY FROM U.S. MILITARY SPECIFICATION MS9880, NOTICE 1 AND CONTAINS ONLY MINOR EDITORIAL AND FORMAT CHANGES REQUIRED TO BRING IT INTO CONFORMANCE WITH THE PUBLISHING REQUIREMENTS OF SAE TECHNICAL STANDARDS. THE INITIAL RELEASE OF THIS DOCUMENT IS INTENDED TO REPLACE MS9880, NOTICE 1. ANY PART NUMBERS ESTABLISHED BY THE ORIGINAL SPECIFICATION REMAIN UNCHANGED.


THE ORIGINAL MILITARY SPECIFICATION WAS ADOPTED AS AN SAE STANDARD UNDER THE PROVISIONS OF THE SAE TECHNICAL STANDARDS BOARD (TSB) RULES AND REGULATIONS (TSB 001) PERTAINING TO ACCELERATED ADOPTION OF GOVERNMENT SPECIFICATIONS AND STANDARDS. TSB RULES PROVIDE FOR (A) THE PUBLICATION OF PORTIONS OF UNREVISED GOVERNMENT SPECIFICATIONS AND STANDARDS WITHOUT CONSENSUS VOTING AT THE SAE COMMITTEE LEVEL, AND (B) THE USE OF THE EXISTING GOVERNMENT SPECIFICATION OR STANDARD FORMAT.

UNDER DEPARTMENT OF DEFENSE POLICIES AND PROCEDURES, ANY QUALIFICATION REQUIREMENTS AND ASSOCIATED QUALIFIED PRODUCTS LISTS ARE MANDATORY FOR DOD CONTRACTS. ANY REQUIREMENT RELATING TO QUALIFIED PRODUCTS LISTS (QPL'S) HAS NOT BEEN ADOPTED BY SAE AND IS NOT PART OF THIS SAE TECHNICAL DOCUMENT.

SAENORM.COM : Click to view the full PDF of as9880

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AS9880>

THIRD ANGLE PROJECTION



CUSTODIAN: E-25

PROCUREMENT SPECIFICATION: NONE



AEROSPACE STANDARD


WASHER, CUP, LOCK – CRES AMS5510

SAE AS9880
SHEET 1 OF 3

ISSUED 1999-12 REAFFIRMED 2012-11

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

SAE AS9880



PART NUMBERS	NOM SIZE	A +.005 -.000	B		C +.005 -.000	D +.000 -.010	E +.010 -.000	F $\pm .010$	G $\pm .005$	T		N	APPROX WEIGHT LB/100
			MIN	MAX						MIN	MAX		
MS9880-09	.190	.110	.230	.237	.377	.170	.095	.140	.226	.019	.025	.347	.15
MS9880-10	.250	.110	.290	.299	.440	.205	.100	.165	.270	.028	.036	.410	.30
MS9880-11	.312	.140	.352	.361	.502	.235	.100	.165	.330	.028	.036	.472	.34
MS9880-12	.375	.140	.415	.425	.564	.265	.140	.165	.370	.028	.036	.534	.38

1. DIAMETERS B & C SHALL BE CONCENTRIC WITHIN .005 FIR.
2. MATERIAL: CORROSION RESISTANT STEEL AMS 5510
3. SURFACE TEXTURE: USAS B46.1-1962. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICROINCHES.
4. REMOVE BURRS AND SHARP EDGES.
5. DIMENSIONS IN INCHES UNLESS OTHERWISE SPECIFIED.
6. HEAT TREATMENT: FORMED WASHERS SHALL BE ANNEALED AT 1925°F TO 1975°F FOR 5 TO 10 MINUTES AND COOLED IN STILL AIR. WASHERS TO BE DESCALED.