



SURFACE VEHICLE RECOMMENDED PRACTICE	J1058	APR2015
	Issued	1976-02
	Reaffirmed	2015-04
Superseding J1058 DEC1999		
Standard Sheet Steel Thickness and Tolerances		

RATIONALE

J1058 has been reaffirmed to comply with the SAE five-year review policy.

1. Scope—This SAE Recommended Practice provides an orderly series for designating the thickness of uncoated and coated hot-rolled and cold-rolled sheet and strip. This document also provides methods for specifying thickness tolerances.

1.1 Requirements of industry permit leeway in the choice of thickness in some instances, but it is recognized that for many applications, particularly the tonnage requirements of the mass production industries, thickness is normally determined by critical engineering design or manufacturing considerations. However, for general applications or where requirements permit some latitude in the selection of thickness, the preferred thickness given in Table 1 will facilitate interchangeability of different metals in design, reduce inventory, and increase the availability in warehouse stocks of thicknesses commonly required for general applications.

1.2 All of the thicknesses listed are not necessarily produced in all metals and grades. Producers or distributors must be consulted to determine availability of a particular thickness for a given metal product.

2. References

2.1 Applicable Publications—The following publications form a part of this specification to the extent specified herein. Unless otherwise indicated, the latest issue of SAE publications shall apply.

2.1.1 ASTM PUBLICATIONS—Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

- ASTM A 463-88—Steel Sheet, Cold-Rolled, Aluminum-Coated, Type 1 and Type 2
- ASTM A 568-91—Steel Sheet, Carbon and High Strength, Low Alloy, Hot-Rolled and Cold-Rolled
- ASTM A 591-91—Sheet Steel, Electrolytic Zinc-Coated, for Light Coating Mass Applications
- ASTM A 635-91—Steel Sheet and Strip, Heavy-Thickness Coils, Carbon, Hot-Rolled
- ASTM A 792-85—Steel Sheet, Aluminum-Zinc Alloy-Coated by the Hot-Dip Process
- ASTM A 924-94—Steel Sheet, Metallic Coated by the Hot Dip Process

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback on this Technical Report, please visit
http://www.sae.org/technical/standards/J1058_201504

2.2 Related Publications—The following publications are provided for information purposes only and are not a required part of this document.

2.2.1 SAE PUBLICATIONS—Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

SAE J1562—Selection of Zinc and Zinc-Alloy (Hot Dipped and Electrodeposited) Coated Steel Sheet

SAE J2329—Categorization and Properties of Low Carbon Automotive Sheet Steels

SAE J2340—Categorization and Properties of Dent Resistant, High Strength, and Ultra High Strength Automotive Sheet Steels

2.2.2 ASTM PUBLICATIONS—Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 525-91—Steel Sheet, Zinc Coated (Galvanized) by the Hot Dip Process

ASTM A 653-94—Steel Sheet, Zinc-Coated (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot Dip Process

ASTM A 879-92—Steel Sheet, Zinc Coated by the Electrolytic Process for Applications Requiring Designation of the Coating Mass on Each Surface

ASTM A 917-93—Steel Sheet, Coated by the Electrolytic Process for Applications Requiring Designation of the Coating Mass on Each Surface

2.2.3 ISO AND ANSI PUBLICATIONS—Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002.

ISO 3574—Cold-reduced carbon steel sheet of commercial and drawing qualities

ANSI Z1.1

ANSI B32.3-1977

3. **Specifying Thickness**

3.1 Method I—Ordering to Minimum Thickness—This is the preferred method used today and is the most common because it provides the design engineer with a minimum thickness for design calculations and a specification system where they can select a minimum thickness without regard to tolerance due to ordered width. When material is ordered to minimum thickness, the tolerance is all plus as shown in Table 1.

3.2 Method II—Ordering to Nominal Thickness—Sheet steel can be ordered to specified nominal thickness with the tolerances shown in Table 1 being half over and half under the specified nominal thickness.

3.3 Location of Thickness Measurement—The specified thickness range will be maintained throughout the coil or sheet at all points not less than 25 mm from the edge.

4. **Recommended Thickness and Thickness Tolerances**

4.1 Recommended thickness and thickness tolerances for steel sheet for automotive applications are shown in Table 1. Thickness and tolerances for sizes or applications other than shown in Table 1 are covered by appropriate ASTM standards for each product.

TABLE 1—(METRIC)—PREFERRED THICKNESS AND THICKNESS TOLERANCES OF UNCOATED OR COATED STEEL SHEET WITH COLD-ROLLED OR HOT-ROLLED SUBSTRATES IN WIDTHS TO 1850 mm

Preferred Specified Thickness in mm	Total Thickness Tolerance - mm			
	Cold-Rolled Substrate Uncoated and/or Electro galvanized Coated Carbon Steel, HSS, HSLA, and Stainless Steel	Cold-Rolled Substrate Hot Dip Zinc, Aluminum Aluminum-Zinc, and Terne Coated Carbon Steel, HSS, HSLA, and Stainless Steel	Hot-Rolled Substrate Uncoated and Hot Dip and Electro galvanized, Aluminum and Aluminum-Zinc Coated Carbon Steel	Hot-Rolled Substrate Uncoated and Hot Dip and Electro galvanized, Aluminum and Aluminum-Zinc Coated HSS and HSLA Steel
0.50	0.06	0.10		
0.55	0.08	0.10		
0.60	0.08	0.10		
0.65	0.08	0.10		
0.70	0.08	0.10		
0.75	0.08	0.10		
0.80	0.08	0.10		
0.85	0.08	0.10		
0.90	0.08	0.10		
0.95	0.08	0.10		
1.00	0.08	0.10	0.08	0.10
1.05	0.10	0.12	0.10	0.12
1.10	0.10	0.12	0.10	0.12
1.20	0.10	0.12	0.10	0.12
1.40	0.10	0.12	0.10	0.12
1.50	0.10	0.12	0.10	0.12
1.60	0.12	0.14	0.14	0.16
1.70	0.12	0.14	0.18	0.20
1.80	0.12	0.14	0.22	0.26
1.90	0.12	0.14	0.22	0.26
2.00	0.12	0.20	0.22	0.26
2.10	0.12	0.20	0.26	0.30
2.20	0.12	0.20	0.26	0.30
2.30	0.12	0.20	0.26	0.30
2.40	0.12	0.20	0.26	0.30
2.50	0.12	0.20	0.26	0.30
2.60	0.14	0.22	0.30	0.38
2.80	0.14	0.22	0.30	0.38
3.00	0.14	0.22	0.30	0.38
3.20	0.14	0.22	0.30	0.38
3.40	0.14	0.22	0.30	0.38
3.50	0.14	0.22	0.30	0.38
3.60	0.14	0.22	0.30	0.38
3.80		0.22	0.30	0.38

TABLE 1—(METRIC)—PREFERRED THICKNESS AND THICKNESS TOLERANCES OF UNCOATED OR COATED STEEL SHEET WITH COLD-ROLLED OR HOT-ROLLED SUBSTRATES IN WIDTHS TO 1850 mm (continued)

Preferred Specified Thickness in mm	Total Thickness Tolerance - mm	Total Thickness Tolerance - mm	Total Thickness Tolerance - mm	Total Thickness Tolerance - mm
	Cold-Rolled Substrate Uncoated and/or Electrogalvanized Coated Carbon Steel, HSS, HSLA, and Stainless Steel	Cold-Rolled Substrate Hot Dip Zinc, Aluminum Aluminum-Zinc, and Terne Coated Carbon Steel, HSS, HSLA, and Stainless Steel	Hot-Rolled Substrate Uncoated and Hot Dip and Electrogalvanized, Aluminum and Aluminum-Zinc Coated Carbon Steel	Hot-Rolled Substrate Uncoated and Hot Dip and Electrogalvanized, Aluminum and Aluminum-Zinc Coated HSS and HSLA Steel
4.00		0.22	0.30	0.38
4.20			0.30	0.38
4.50			0.30	0.38
4.80			0.34	0.38
5.00			0.34	0.38
5.50			0.34	0.38
5.80			0.34	0.38
6.00			0.34	0.38
6.50			0.34	0.38
7.00			0.34	0.38
7.50			0.34	0.38
8.00			0.38	0.38
9.00			0.38	0.38
10.00			0.40	0.40
11.00			0.40	0.40
12.00			0.40	0.40

5. Notes

- 5.1 Note 1**—Thickness is measured at any point across the width not less than 25 mm in from a longitudinal edge. The width of the sheet is the dimension perpendicular to the sheet rolling direction.
- 5.2 Note 2**—The thickness tolerance for a specified thickness also applies when sheet is specified to a nominal thickness except the tolerances are divided equally (and rounded up), over and under.
- 5.3 Note 3**—Thickness tolerances shown for cold-rolled substrates are one half and those shown for hot-rolled substrates are three quarters of those shown in ASTM specifications.
- 5.4 Note 4**—Thickness tolerances apply to widths produced by slitting from a wider sheet.
- 5.5 Note 5**—Table 1 is based on the following:

Electrolytic Zinc Coated: ASTM A 51, Table 3
 Hot Dip Zinc Coated: ASTM A 924, Table 2
 ASTM A 568, Table 4
 ASTM A 635, Table 4
 Hot Dip Aluminum Coated: ASTM A 463, Table 3
 Hot Dip Aluminum-Zinc Coated: ASTM A 792, Table 6