

	SURFACE VEHICLE RECOMMENDED PRACTICE	SAE J1389 AUG2011
		Issued 1982-05 Stabilized 2011-08 Superseding J1389 OCT2001
Corrosion Test for Insulation Materials		

RATIONALE

The technical report covers technology, products, or processes which are mature and not likely to change in the foreseeable future.

STABILIZED NOTICE

This document has been declared "Stabilized" by the SAE Acoustical Materials Committee and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of J1389_201108

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
 Tel: +1 724-776-4970 (outside USA)
 Fax: 724-776-0790
 Email: CustomerService@sae.org
 SAE WEB ADDRESS: http://www.sae.org

**SAE values your input. To provide feedback
on this Technical Report, please visit**
http://www.sae.org/technical/standards/J1389_201108

Foreword—This Document has not changed other than to put it into the new SAE Technical Standards Board Format.

1. **Scope**—This SAE Recommended Practice applies to various insulation materials used in vehicles for control of heat and noise and other applications.
 - 1.1 **Purpose**—The purpose of this test is to provide a means to evaluate and compare the corrosiveness of insulation materials. Three panelists compare a sample insulation material to a standard (inert fibrous material). The rationale for the test is that the corrosion of steel should not be greater for the insulation material than for an inert fibrous material.
2. **References**—There are no referenced publications specified herein.
3. **Apparatus**
 - 3.1 **Steel Test Plates**—The plates shall be 2.5 cm (1.0 in) wide, 10 cm (4.0 in) long, and 0.05 cm (0.020 in) thick. The steel shall be SAE grade number 1010, cold-rolled, strip steel. The steel shall have bright No. 2 finish and No. 3 temper—quarter hard.
 - 3.2 **Wire Mesh**—The wire mesh shall be type 304 stainless steel wire cloth with 1.25 cm (0.5 in) mesh. The mesh should be cut to 3.8 cm (1.5 in) wide by 11.5 cm (4.5 in) long.
 - 3.3 **Humidity Chamber**—The humidity chamber shall be clean and maintain a temperature of $49\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ($120\text{ }^{\circ}\text{F} \pm 3\text{ }^{\circ}\text{F}$) and $95\% \pm 3\%$ relative humidity.
 - 3.4 **Inert Fibrous Standard Material**—Any fibrous material free from chemical contaminants is satisfactory as a standard material. Two materials that have been shown to be satisfactory are:
 - a. Unbonded, unlubricated fibrous glass.
 - b. Sterile cotton, extracted in acetone for 48 h and vacuum dried at low heat. Because cotton has variable amounts of oil on it, it must be extracted in solvent to obtain reproducible results.
 - 3.5 **Rubber Bands**—Rubber bands shall be No. 12.

4. **Test Specimens and Conditioning**

- 4.1 Test specimens should be representative of the material being evaluated. Test specimens should be 3.8 cm (1.5 in) wide by 11.5 cm (4.5 in) long by 1.3 cm (0.5 in) thick. Two specimens are required for each sample.
- 4.2 Prior to the test, the specimens must be brought to room temperature.

5. **Procedure**

- 5.1 Clean the steel plates until they are free of water breaks. Breaks are characterized by uneven cling or coating on the surface of the metal. First, wash the plates with a laboratory-grade detergent and rinse with distilled water. Then place the plates in a hot caustic (not boiling) of 15% potassium hydroxide.

CAUTION—Potassium hydroxide can cause severe burns and damage eyes. The caustic bath should be done under a laboratory hood.

Rinse in distilled water and check for water breaks. If there are none, dry immediately with laboratory-type paper wipe. Repeat procedure if necessary.

- 5.2 Boil the No. 12 rubber bands in distilled water for 30 min to remove contamination.
- 5.3 Place one steel panel between two specimens, per Figure 1. Both specimens must be cut from the same sample. Place wire mesh on both sides of assembly and secure with two No. 12 rubber bands.
- 5.4 Prepare standard panel in same manner as in 5.2, except use inert fibrous standard material.
- 5.5 Suspend test assemblies vertically in the humidity chamber that has been preset to $49\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$ ($120\text{ }^{\circ}\text{F} \pm 3\text{ }^{\circ}\text{F}$) and $95\% \pm 3\%$ RH. The samples must be left in the humidity chamber for 96 h. (Since the test compares sample material to a standard, other test conditions may be chosen provided they produce acceptable rates of corrosion.)
- 5.6 Remove the samples and grade the test panels according to the scale in Figure 2 using the control panel for comparison:
- Surface blush or stain rust should be ignored. Heavy rust, flaking, and pitting should be weighed heavily in the ratings.
- 5.7 Repeat 5.6 for at least two other knowledgeable panelists.
- 5.8 Report for each sample:
- Median and all numerical ratings.
 - Type of rust and description of pattern observed per 5.5.
 - Complete description of sample insulation material including generic composition, manufacturing, material identification, thickness, and weight.