

Steel, High Strength, Hot Rolled
Sheet and Strip, Cold Rolled
Sheet, and Coated Sheet —
SAE J1392 MAY82

SAE Recommended Practice
Approved May 1982

S. A. E.
LIBRARY

THIS IS A PREPRINT WHICH IS
SUBJECT TO REVISIONS AND
CORRECTIONS. THE FINAL
VERSION WILL APPEAR IN THE
1983 EDITION OF THE SAE
HANDBOOK.

SAE *The Engineering
Resource For
Advancing Mobility*

PREPRINT

SAENORM.COM : Click to view the full PDF of J1392-198205

SAENORM.COM : Click to view the full PDF of J1392_198205

STEEL, HIGH STRENGTH, HOT ROLLED SHEET AND STRIP, COLD ROLLED SHEET, AND COATED SHEET¹—SAE J1392 MAY82

SAE Recommended Practice

Report of the Iron and Steel Technical Committee, prepared by Division 32, approved May 1982.

NOTE: Sheet and Strip products formerly were included in J410c, but are now included in this separate recommended practice as a result of the revision of SAE J410 currently (1982) underway.

1. Scope—This recommended practice covers seven levels of high strength carbon and low-alloy hot rolled sheet and strip, cold rolled sheet, and coated sheet steels. The strength is achieved through chemical composition and special processing.

2. Introduction—High strength steel discussed in this recommended practice involves hot rolled sheet and strip and cold rolled sheet as dimensionally described in ASTM A568 (A568M) latest revision (Steel, Carbon and High-Strength Low-Alloy Hot-Rolled Sheet, Hot-Rolled Strip and Cold-Rolled Sheet, General Requirements). It also includes coated sheet, that is, sheet coated by hot dipping, electroplating, or vapor deposition of zinc, terne, aluminum, and organic compounds normally applied by coil coating. Public specifications related to these coated products are the latest revisions of ASTM A525 (Steel Sheet, Zinc-Coated (Galvanized) by the Hot-Dip Process, General Requirements), A591 (Steel Sheet, Cold Rolled, Electrolytic Zinc-Coated), A463 (Steel Sheet, Cold-Rolled, Aluminum-Coated Type 1), and A308 (Steel, Sheet, Cold-Rolled, Long Terne Coated).

The strength is achieved through chemical composition and special processing. Special processing includes mechanical rolling techniques, and temperature control in hot rolling and subsequent heat treatments. The primary use of high strength steel is based on the increased yield and tensile properties which are higher than those of conventional sheet and strip for which minimum mechanical properties are not normally specified.

The seven strength levels are 35 (240), 40 (280), 45 (310), 50 (340), 50 (410), 70 (480) and 80 (550) ksi (MPa) minimum yield strength. Different chemical compositions are normally used to achieve the specified mechanical properties. These compositions are significantly different at the same strength level depending on additional material requirements, that is, weldability, formability, toughness, fatigue life, atmospheric corrosion resistance, and economics. The correct type of high strength sheet or strip should be specified to establish compatibility of the producers' chemical composition with the fabrication and application requirements.

Because high strength steel is characterized by special mechanical properties, consultation of producer and user in grade selection is recommended to insure compatibility of the strength and forming requirements. Care must be taken in designing parts, tooling, and fabrication processes to obtain the greatest benefit from the high strength sheet and strip steels. It is advisable that the purchaser furnish information to the producer relating the individual requirements of an identified part; this may be accomplished by visual examination of the part, by prints, through a description, or a combination of these. Also, it is highly desirable for the producer to observe the fabricating practices, or at least be provided with a detailed description of the operations.

The steels discussed in this practice are characterized by their special mechanical properties achieved through chemical composition and special processing. They normally are not intended for any heat treatment by the purchaser. Subjecting these steels to such heat treatments will modify the original mechanical properties. For certain applications these steels may be annealed, normalized, or stress relieved with some effect on the mechanical properties. It is recommended that prior to such heat treatments the producer and purchaser consult to determine the need for a heat treatment and its effect on mechanical properties.

All grades and chemical compositions in this practice are weldable despite the differences in carbon, manganese, and alloying additions. However, as variations in composition from one producer to another do exist, it is advisable to discuss with the producers the features of their chemical composition relative to specific types of welding and any special considerations for each application.

These steels, because of their high strength-to-weight ratio, may be adapted for use in mobile equipment and other structures where substantial weight savings are generally desirable.

3. General Information—The specific grades are identified by a six character code that describes the strength level, general chemical composition, general carbon level, and deoxidation/sulfide inclusion control system, as follows:

3.1 First, Second and Third Characters—Minimum yield strength expressed in kips per square inch (ksi): 35, 40, 45, 50, 60, 70, and 80, expressed as 035, 040, 045, 050, 060, 070, and 080 respectively, or as megapascals (MPa): 240, 280, 310, 340, 410, 480, and 550.

3.2 Fourth Character—General chemical composition:

A—C and Mn only

B—C, Mn, N

C—C, Mn, P

S—C, Mn, (N and/or P added at producer option)

W—Weathering composition (Si, P, Cu, Ni, and Cr in various combinations)

X—High Strength Low Alloy (HSLA), that is, Cb, Cr, Cu, Mo, Ni, Si, Ti, V, Zr either singly or in combination, with a 10 ksi (70 MPa) spread between the specified minima of the yield and tensile strengths. N and P may be used in combination with any of the aforementioned elements.

Y—Same as X with a 15 ksi (100 MPa) spread between the specified minima of the yield and tensile strengths.

Z—Same as X with a 20 ksi (140 MPa) spread between the specified minima of the yield and tensile strengths.

3.3 Fifth Character—General carbon level:

H—Maximum carbon as shown in Tables 3 and 4

L—0.13% carbon max. except as indicated in Table 4

3.4 Sixth Character—Deoxidation/sulfide inclusion control practices:

K—Killed, made to a fine grain practice

F—Sulfide inclusion controlled, killed, made to a fine grain practice

O—Other than K and F

3.5 A material grade corresponding to every combination of numbers and letters is not available. Therefore, it is recommended that the purchaser consult with the producers to determine that the desired grade is available before releasing engineering approved prints and specifications, and before purchase orders are placed.

These steels are generally produced as semi-killed or killed steel, although rimmed and capped practices may be used in certain situations. When selecting a deoxidation practice, the following items should be considered. Rimmed and capped steels are less homogeneous than killed steels. Therefore, the producer must plan his processing to compensate for variations in chemical composition and maintain mechanical strength properties specified. With the greater range in chemical composition of rimmed and capped steels, variations in fabrication, such as maintaining part dimensions, springback, and breakage, on complex parts can result. If these material variations are not compatible with specific part designs and tooling, a deoxidation practice resulting in a more homogeneous steel should be considered.

4. Mechanical Properties—The mechanical properties of these high strength sheet and strip steels are shown in Tables 1 (hot rolled) and 2 (cold rolled and coated). Current steel industry practice is to determine the yield point of these materials by the drop of beam, half of pointer, dividers, 0.2% offset, or 0.5% extension under load method. In cases involving dispute between two or more parties, the yield strength shall be determined by the 0.2% offset method as described in ASTM A370, Paragraph 13.2.1, which describes yield strength.

Because of the different rates of heat transfer in the various parts of a coil of hot rolled sheet steel, and to a lesser degree, the variation in chemical composition, especially when deoxidation practices other than killed are employed, mechanical properties will vary in a coil or cut lengths which are sheared from a coil. Because of the faster cooling rates that may occur on the outside and inside (eye) wraps of a coil, the leading and trailing ends of a coil tend to be harder and higher in yield and tensile strength than the material from the interior of the coil. Cooling is generally faster as the thickness decreases, thus the strength tends to increase as the thickness decreases. For a specified grade and thickness, both coils and cut lengths will be produced to the same mill practices. Testing within the body of the coil cannot be performed by the producer.

¹ The values stated in U. S. customary units are to be regarded as the standard recommended practice.

TABLE 1—MECHANICAL PROPERTIES—HOT ROLLED

Grade	Yield Strength, ksi (MPa) min.	Tensile Strength, ksi (MPa) min.	% Elongation ^b (2 in or 50 mm) min.
035 A, B, C, S	35 (240)	*	21
035 X, Y, Z	35 (240)	*	28
040 A, B, C, S	40 (280)	*	20
040 X, Y, Z	40 (280)	*	27
045 A, B, C, S	45 (310)	*	18
045 W	45 (310)	65 (450)	25
045 X	45 (310)	55 (380)	25
045 Y	45 (310)	60 (410)	25
045 Z	45 (310)	65 (450)	25
050 A, B, C, S	50 (340)	*	16
050 W	50 (340)	70 (480)	22
050 X	50 (340)	60 (410)	22
050 Y	50 (340)	65 (450)	22
050 Z	50 (340)	70 (480)	22
060 X	60 (410)	70 (480)	20
060 Y	60 (410)	75 (520)	20
070 X	70 (480)	80 (550)	17
070 Y	70 (480)	85 (590)	17
080 X	80 (550)	90 (620)	14
080 Y	80 (550)	95 (650)	14

* Minimum tensile strength normally does not apply.

^b Elongation values are dependent upon specimen geometry (cross-sectional area). Thicker and wider specimens normally result in higher percentages.

TABLE 2—MECHANICAL PROPERTIES—COLD ROLLED AND COATED

Grade	Yield Strength, ksi (MPa) min.	Tensile Strength, ksi (MPa) min.	% Elongation ^b (2 in or 50 mm) min.
035 A, B, C, S	35 (240)	*	22
035 X, Y, Z	35 (240)	*	27
040 A, B, C, S	40 (280)	*	20
040 X, Y, Z	40 (280)	*	25
045 A, B, C, S	45 (310)	*	18
045 W	45 (310)	65 (450)	22
045 X	45 (310)	55 (380)	22
045 Y	45 (310)	60 (410)	22
045 Z	45 (310)	65 (450)	22
050 A, B, C, S	50 (340)	*	16
050 X	50 (340)	60 (410)	20
050 Y	50 (340)	65 (450)	20
050 Z	50 (340)	70 (480)	20

* Minimum tensile strength normally does not apply.

^b Elongation values are dependent upon specimen geometry (cross-sectional area). Thicker and wider specimens normally result in higher percentages.

thus producer testing is limited practically to coil ends and random pieces sheared from coils for cut length orders. Considering this practical limitation on testing, the producer has specific knowledge of material properties only at the test location. Therefore, the mechanical properties in the body of a coil may vary from those at the ends.

Based on the data developed from above, each producer establishes testing procedures and frequency to ensure that the processes designed to produce the specified mechanical properties are under control. These procedures also provide knowledge of the product properties and guidance in evaluating the product for the intended application. Since the local manufacturing conditions vary from one producer location to another, and the characteristics of the grades within the scope of this report vary, there is no one testing frequency plan. If the purchaser requires any special testing program it should be discussed with the producer at the time of evaluating the steel grades for the intended application.

5. Chemical Composition—The chemical composition of the steels in this recommended practice may vary from one producing facility to another for the same strength level. Therefore, it is not practical to list all the combinations for each strength level and general chemical composition. While all producers comply with the carbon and manganese content shown in Tables 3 and 4, a more precise value or range is dependent on the alloys, if used, and their specific amounts, the thickness of the steel being produced on a given unit, and the special characteristics of

TABLE 3—CHEMICAL COMPOSITION (HEAT OR CAST ANALYSIS) HOT ROLLED (All maximums unless otherwise noted)

Grade	Carbon ^a		Manganese	Additional
	H	L		
035 A	0.25	0.13	0.60	None
035 B	0.25	0.13	0.60	Nitrogen
035 C	0.25	0.13	0.60	Phosphorus
035 S	0.25	0.13	0.60	Producer option, i.e., A or B or C
035 X, Y, Z	—	0.13	0.60	Microalloy ^b
040 A, B, C, S	0.25	0.13	0.90	Same as 035 A, B, C, S above
040 X, Y, Z	—	0.13	0.60	Microalloy ^b
045 A, B, C, S	0.25	0.13	0.90	Same as 035 A, B, C, S above
045 W	0.22	—	1.25	Various combinations of Si, P, Cu, Ni, Cr
045 X	—	0.13	1.35	Microalloy ^b
045 Y, Z	0.22	—	1.35	Microalloy ^b
050 A, B, C, S	0.25	—	1.35	Same as 035 A, B, C, S above
050 W	0.22	—	1.25	Various combinations of Si, P, Cu, Ni, Cr
050 X	—	0.13	0.90	Microalloy ^b
050 Y, Z	0.23	—	1.35	Microalloy ^b
060 X	—	0.13	0.90	Microalloy ^b
060 Y, Z	0.26	—	1.50	Microalloy ^b
070 X	—	0.13	1.65	Microalloy ^b
070 Y, Z	0.26	—	1.65	Microalloy ^b
080 X	—	0.13	1.65	Microalloy ^b
080 Y	0.18	—	1.65	Microalloy ^b

* Lower levels are available upon inquiry.

^b Cb, V, and Ti are commonly used singly or in combination. Combinations of the following elements are sometimes used with or without Cb, V, and Ti: Cr, Cu, Mo, Ni, Si and Zr. P and/or N may be added to any of the foregoing.

TABLE 4—CHEMICAL COMPOSITION (HEAT OR CAST ANALYSIS) COLD ROLLED AND COATED (All maximums unless otherwise noted)

Grade	Carbon ^a		Manganese	Additional
	H	L		
035 A	0.20	0.13	0.60	None
035 B	0.20	0.13	0.60	Nitrogen
035 C	0.20	0.13	0.60	Phosphorus
035 S	0.20	0.13	0.60	Producer option, i.e., A or B or C
035 X, Y, Z	0.18	0.13	0.60	Microalloy ^b
040 A, B, C, S	0.24	0.15	0.90	Same as 035 A, B, C, S above
040 X, Y, Z	0.20	0.13	0.90	Microalloy ^b
045 A, B, C, S	0.25	0.17	1.20	Same as 035 A, B, C, S above
045 W	0.22	—	1.35	Various combinations of Si, P, Cu, Cr, Ni
045 X, Y, Z	0.22	0.15	1.20	Microalloy ^b
050 A, B, C, S	0.25	0.20	1.35	Same as 035 A, B, C, S above
050 X, Y, Z	0.23	0.17	1.35	Microalloy ^b

* Lower levels are available upon inquiry.

^b Cb, V, and Ti are commonly used singly or in combination. Combinations of the following elements are sometimes used with or without Cb, V, and Ti: Cr, Cu, Mo, Ni, Si, and Zr. P and/or N may be added to any of the foregoing.

the producing unit. Chemical composition is important for achieving the specified minimum mechanical properties. Chemical composition also affects other properties such as weldability, formability, toughness, and fatigue. When these are critical, the fabricator should discuss the details with the producer so that the material selected will be compatible with the fabrication and application requirements.

The following provides a brief description and comparison of the eight compositional systems.

5.1 A—Carbon/Manganese—Only carbon and manganese are used to meet the minimum strength requirements. No other elements that significantly add to strength and hardness are intentionally added. As the carbon and/or manganese are increased, the strength and hardness are increased, but ductility and weldability are decreased. Carbon has a greater effect on these properties than manganese.

5.2 B—Nitrogenized—Nitrogen is used to increase strength and