



SURFACE VEHICLE RECOMMENDED PRACTICE	J175™	DEC2023
	Issued 1970-07 Reaffirmed 2003-09 Revised 2023-12	
Superseding J175 JUL2021		
Wheels - Lateral Impact Test Procedure - Road Vehicles		

RATIONALE

This revision includes an update to the set-up procedure and schematic in Appendix D to correct the starting datum for the drop height for velocity measurement to set the adjusted drop height.

1. SCOPE

The SAE Recommended Practice establishes minimum performance requirements and related uniform laboratory test procedures for evaluating lateral (curb) impact collision resistance of all wheels intended for use on passenger cars and light trucks.

2. REFERENCES

2.1 Applicable Documents

The following publications form a part of this specification to the extent specified herein. Unless otherwise indicated, the latest issue of SAE publications shall apply.

2.1.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA); www.sae.org.

SAE J393 Nomenclature - Wheels, Hubs, and Rims for Commercial Vehicles

SAE J1982 Nomenclature - Wheels for Passenger Cars, Light Trucks, and Multipurpose Vehicles

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit
https://www.sae.org/standards/content/J175_202312

2.2 Related Publications

The following publications are provided for information purposes only and are not a required part of this SAE Technical Report.

2.2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

SAE J2530 Aftermarket Wheels - Passenger Cars and Light Truck - Performance Requirements and Test Procedures

SAE J3204 Aftermarket Composite Wheels Made of Matrix Material and Fiber Reinforcement Intended for Normal Highway Use - Test Procedures and Performance Requirements

2.2.2 ISO Publications

Copies of these documents are available online at <https://webstore.ansi.org/>.

ISO 3911 Wheels and Rims for Pneumatic Tyres - Vocabulary, Designation and Marking

ISO 7141:1981 Road Vehicles - Wheels - Impact Test Procedure

3. DEFINITIONS

The terminology used herein follows the standard definitions found in SAE J393 with the following addition:

3.1 ADJUSTED DROP HEIGHT (ADH)

The height, in millimeters (mm), that a mass must be dropped from to replicate free fall from 230 mm, as measured by time of 12.31 ms +0.3/-0 ms to pass through a distance of 25.4 mm prior to tire contact. Tests are to be conducted at adjusted drop height. See Appendix D for a recommended procedure for measuring mass velocity and adjusting drop height.

4. TEST PROCEDURES

4.1 Wheels for Test

Only fully processed new wheels, which are representative of wheels intended for passenger car and light truck applications, shall be used for each test. Tires and wheels used for test should not be used subsequently on a vehicle.

4.2 Equipment

The test machine shall be one in which an impact loading is applied to the rim flange of a wheel complete with tire. The wheel shall be mounted with its axis at an angle of 13 degrees \pm 1 degree to the vertical so that its highest point is presented to the vertically acting striker. The impacting face of the striker system shall be at least 125 mm wide and at least 375 mm long (see Figure 1).

The width of the support beam is 200 mm minimum, to prevent permanent deformation, and is recommended to be made of 400 MPa minimum yield material. All pivot joints in the wheel mount fixture should be free to rotate. The lateral spacing of the rubber mounts must be a minimum of 200 mm on center. Shoulder bolts are recommended to prevent binding. The wheel mount fixture dimensions are shown in Figure 1.

- 4.2.1 An alternate construction includes a rotating adapter that allows circumferential alignment. Rubber mounts are recommended to be constrained perpendicular to direction of drop, as seen in Figure 3. Jounce travel is limited per alternate construction defined in Figure 4.
- 4.2.2 Each piece of equipment has friction unique to that machine. Friction is compensated for by calibrating to determine the ADH at which 230 mm of freefall is accomplished on that machine.

4.3 Test Setup and Procedure

- a. Adjust the striker mass.

$$D = 0.6W + 180 \quad (\text{Eq. 1})$$

where:

D = mass of striker $\pm 2\%$, expressed in kilograms

W = maximum static wheel loading as specified by wheel and/or vehicle manufacturer, expressed in kilograms

- b. Rigidly constrain any weights added to the striker mass so that it acts as one mass.
- c. Mount wheel to the hub adapter through the bolt circle using representative fasteners.
- d. Torque lugnuts to $115 \text{ N}\cdot\text{m} \pm 7 \text{ N}\cdot\text{m}$, or the torque recommended by the vehicle or wheel manufacturer.
- e. Select tubeless tire of the smallest nominal section width tire intended for use with the wheel by the vehicle or wheel manufacturers.
- f. Inflate tire pressure, as specified by the vehicle manufacturer. In the absence of such specification, use 200 kPa for all passenger car applications. Tire pressure is to be 380 kPa for light truck applications at and above 1120 kg load rating and temporary spare applications.
- g. Align the front edge of the striker to be $25 \text{ mm} \pm 1 \text{ mm}$ overlapping the rim flange of the wheel. The tire section must not overlap the striker plate in both radial and lateral directions during the impact.
- h. Raise mass from the flange tip the adjusted drop height as found at last calibration.
- i. Conduct the tests at temperatures between $10 \text{ }^\circ\text{C}$ and $38 \text{ }^\circ\text{C}$.
- j. Drop mass on wheel tire assembly.
- k. Measure tire pressure (kPa) within 1 minute of impact.
- l. Inspect wheels for cracks, take digital image if cracks are present.
- m. Fill out test datasheet (see Appendix A for example).

- 4.3.1 Repeat impacts to ensure that the integrity of the wheel is evaluated in the presence of varying design features. One impact location to be at the valve hole. A separate wheel shall be used for each test.




Figure 1 - Impact loading test machine

4.4 Calibration of Rubber Mounts

- 4.4.1 With the test calibration adapter located at the mid-span of the beam, a mass of 1000 kg shall be applied to the center of the wheel mount, as shown in Figure 2. The deflection of the test fixture shall be $7.5 \text{ mm} \pm 0.75 \text{ mm}$ when measured at the center of the beam, as shown in Figure 2.

- 4.4.2 As an alternative to the calibration procedure noted in Figure 2, rubber mounts can be calibrated in a traceable load versus deflection device. Load all four rubber mounts in parallel to 1000 kg with an added 70 kg to replicate the weight of the pedestal. Deflection criteria of 4.4.1 is applicable.

4.5 Calibration of Drop Height

- 4.5.1 Friction in the slides can be compensated for by adjusting the drop height (ADH) until a velocity is measured that replicates 230 mm of free fall. A velocimeter and a light curtain are used in combination to measure the velocity of the drop mass just prior to striking the tire. The calibrator is to start at 230 mm and increment in 2 mm increases of drop height until the time it takes to go through a 25.4 mm light curtain is $12.31 \text{ ms} +0.3/-0 \text{ ms}$. As an example: the ADH to be noted on the calibration certificate and sticker as ADH equal to 234 mm. All tests on specific machine to be dropped at the ADH until the next calibration. ADH to be displayed on calibration certificate and calibration sticker on the mass.

Calibration should include all the fields found in Calibration Data Sheet noted in Appendix B.




Figure 2 - Calibration of rubber mounts




Figure 3 - Alternate construction with pinned rubber mounts and rotating adapter




Figure 4 - Jounce travel

4.6 Acceptance Criteria (Metallic Structures Only)

- 4.6.1 No visible fracture(s) (not by dye penetrant) penetrating through a section of the center member of the wheel assembly. See Appendix C for examples of acceptable and non-acceptable fractures.
- 4.6.2 No separation of the center member from the rim.
- 4.6.3 No total loss of the air pressure within 1 minute after impact.

NOTE 1: Fractures in the area of the rim under the striker (including separation of the flange) does not constitute failure to meet the acceptance criteria.

NOTE 2: If it is suspected that one of the acceptance criteria is not met due to subsequent impacts caused by the mass rebounding or the mass resting on the tire, means should be employed to capture the mass after first impact. Only one impact is intended.

NOTE 3: Non-structural materials (e.g., claddings), additional styling, and aero elements will not be considered in evaluating acceptance.

5. NOTES

5.1 Revision Indicator

A change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this document. An (R) symbol to the left of the document title indicates a complete revision of the document, including technical revisions. Change bars and (R) are not used in original publications, nor in documents that contain editorial changes only.

APPENDIX A - TEST DATA SHEET
DATA SHEETS SPECIFY INFORMATION REQUIRED, NOT FORMAT

Name or logo approved test provider	Test facility name, location of tester
Test Number	
Test Type	
Test Requester	
Part Number Tested	
Test parameters	
Specification	SAE J175
Wheel Size	
Fastener Size	
Tire Size	
Bolt Pattern	
Specified Test Load (kg)	
Tire Pressure (kPa)	
Adjusted Drop Height (mm)	
Test data	
ID of Wheel Tested	
Test Date	
Test Technician	
Test Machine ID	
Last Calibration Date	
Actual Test Load (kg)	
Location of Impact	
Digital Image Supplied (if cracks present)	
Acceptance criteria	
Air pressure after 1 minute (kPa)	
1. Did the wheel sustain air pressure?	YES/NO
2. Are there cracks through a section in center?	YES/NO
3. Is there separation between the center and the rim?	YES/NO
4. Does the test meet or exceed acceptance criteria?	YES/NO
Technician Certifying Results	
Comments	

APPENDIX B - CALIBRATION DATA SHEET

Customer: _____ Calibrator: _____
 Location: _____ Name: _____
 Machine Station: _____ Company: _____
 Manufacturer: _____ Date: _____
 Model Number: _____
 Serial Number: _____

Calibration Information:

Description:	Manufacturer:	Serial #	Calibration by:	Date:	Traceability to NIST:
Load Cell					
Signal Conditioner					
Deflection Meter					
Velocimeter					

Technique Used:

- A. Deflection of rubber mounts measured in test machine
- B. Deflection of rubber mounts measured in load/deflection press. All four rubber mounts loaded to 1000 kg + 70 kg (approximate mass of apparatus above rubber mounts)
- C. Traceable velocimeter gate type with VSDI optical sensor (comparable to GHI VS200)
- D. Load cell and signal conditioner traceable to within ± 2 kg at 1000 kg
- E. Deflection meter traceable to within ± 0.75 mm

Acceptance Criteria:

- A. Adjusted Drop Height (ADH) at which $12.31 \text{ ms} \pm 0.2 \text{ ms}$ of gate time is achieved through 25.4 mm of travel: _____ mm
- B. The deflection of four rubber mounts under load as per A or B: _____ mm


*Adjusted drop height to be noted on sticker on machine

Calibration Date: _____ Signature of Calibrator: _____

Next Calibration Due: _____

Certificate not to be reproduced except in full, without the written approval of calibrator noted above.

APPENDIX C - EXAMPLES OF VISIBLE FRACTURE FOR CLARIFICATION



SAENORM.COM : Click to view the full PDF of J175-202312