



SURFACE VEHICLE RECOMMENDED PRACTICE

J1830

OCT2013

Issued 1987-05
Reaffirmed 2013-10

Superseding J1830 MAY1987

Size Classification and Characteristics of Ceramic Shot for Peening

RATIONALE

J1830 has been reaffirmed to comply with the SAE five- year review policy.

1. **Scope**—This specification covers characteristics for chemistry, microstructure, density, hardness, size, shape and appearance of zirconium oxide based ceramic shot, suitable for peening surfaces of parts by impingement.

2. References

2.1 **Applicable Publications**—The following publication forms a part of the specification to the extent specified herein.

2.1.1 ASTM PUBLICATION—Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 11-70—Specification for Wire-Cloth Sieves for Testing Purposes

3. **Chemistry**—This specification includes the nominal chemistry of zirconium oxide based ceramic shot and the amount of free iron particles.

3.1 **Oxide Analysis**—Ceramic shot shall be manufactured from zirconium oxide and silica. The main constituents shall be:

- Zirconium Oxide 60 to 70 weight per cent
- Silica 28 to 33 weight per cent
- Alumina less than 10 weight per cent

The total of other constituent contents shall not exceed 3 weight per cent. Analysis method is X-Ray Fluorescence or any other method acceptable to purchaser.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback
on this Technical Report, please visit
http://www.sae.org/technical/standards/J1830_201310

- 3.2 Free Iron Content**—The free iron content of the ceramic shot sample shall not exceed 0.10 weight per cent. It is determined by slowly sprinkling 500 g of the sample ceramic bead shot on an inclined aluminum tray that is 1.6 mm (0.062 in) deep by 152 mm (6 in) wide by 305 mm (12 in) long. The tray is supported by a nonmagnetic frame so that it is inclined with a 152 mm (6 in) rise from end to end, (30 degrees from horizontal). Four 25 x 25 x 152 mm (1 x 1 x 6 in) bar magnets are positioned against the under surface and crosswise to the inclined tray about the middle of its length. Magnets shall be not less than 10 000 Gauss magnetic field each and arranged so that the magnetic north and south poles alternate. The magnetic particles (iron) that accumulate on the tray as the beads roll down are carefully brushed into a preweighed dish. The procedure is repeated with the same 500 g sample until all visible magnetic particles are collected. The dish is then reweighed and the magnetic particle content is calculated as a percentage of the total original sample.
- 4. Microstructure**—Ceramic shot are manufactured by electric fusion of oxides to form a closely bonded internal structure of a crystalline zirconia phase within an amorphous silica phase.
- 5. Specific Gravity**—This characteristic is closely related to chemical analysis. It ranges between 3.60 and 3.95 g/cm³.
- Specific gravity is measured at 31 °C by a pycnometric method.
- 6. Hardness**—Unless otherwise specified, the ceramic shot shall have the following hardness:
- 623-785 DPH (1Kgf)
or 660-812 KHN (500 gf)
(for reference only approximately 57–63 HRC)
- 7. Size**—Unless otherwise specified, the ceramic shot shall conform to Table I.
- 7.1 Testing**—This is conducted by screening a 250 g sample with sieves conforming to ASTM E 11–70.
- 8. Shape**—Sphericity and roundness are measured by an actual counting of a one layer field of a minimum of 200 ceramic beads, at a magnification of 20X.
- 8.1 Sphericity**—It refers to the ratio of short to long axes of the hypothetical ellipse that would contain the actual image of the ceramic bead as seen through a microscope. Unless otherwise specified, Table I gives the maximal number of ceramic shot having a sphericity less than 0.5 and the minimum percentage of ceramic shot having a sphericity of 0.8 and greater.
- 8.2 Roundness**—It refers to the relative angularity of grain corners, the ceramic shot having round and smooth surfaces. Scored, broken or angular particles are those that would present sharp or angular surfaces when impacted, causing metal removal or unsatisfactory or irregular finishes. An actual count shall be made of a field of 1 cm² at a 20X magnification. Maximum number of permissible broken or angular beads is shown on column 11 of Table I. This number shall never exceed 3%.
- 9. Appearance**—Ceramic shot is constant in color, free flowing, free of defects and free of foreign matter.
- 10. Quality Assurance**—Ceramic shot quality is checked by lots of 1,000 kg maximum. A representative sample of the shipped lot shall be tested for conformance to all requirements of this specification. Lot number and this specification number shall be marked on each container unit. All control data will be available from manufacturer on request for two (2) years after shipment.