



SURFACE VEHICLE RECOMMENDED PRACTICE

J1830™

OCT2023

Issued 1987-05
Reaffirmed 2013-10
Revised 2023-10

Superseding J1830 OCT2013

Size Classification and Characteristics of Ceramic Shot for Peening

RATIONALE

SAE J1830 is updated and adjusted to count particle defects as a percentage.

1. SCOPE

This specification covers characteristics for chemistry, microstructure, density, hardness, size, shape, and appearance of zirconium oxide-based ceramic shot, suitable for peening surfaces of parts by impingement.

2. REFERENCES

2.1 Applicable Documents

The following publications form a part of this specification to the extent specified herein. Unless otherwise indicated, the latest issue of SAE publications shall apply.

2.1.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096 -0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2431/7 Peening Media Ceramic Shot

2.1.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E11 Standard Specification for Woven Wire Test Sieve Cloth and Test Sieves

ASTM D1214 Standard Test Method for Sieve Analysis of Glass Spheres

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit
https://www.sae.org/standards/content/J1830_202310/

3. CHEMISTRY

This specification includes the nominal chemistry of zirconium oxide-based ceramic shot and the amount of free iron particles.

3.1 Oxide Analysis

Ceramic shot shall be manufactured from zirconium oxide and silica. The main constituents shall be:

- Zirconium oxide 60 to 70 weight percent
- Silica 28 to 33 weight percent
- Alumina less than 10 weight percent

The total of other constituent contents shall not exceed 3 weight percent. Analysis method is x-ray fluorescence or any other method acceptable to purchaser.

3.2 Free Iron Content

The free iron content of the ceramic shot sample shall not exceed 0.10 weight percent. It is determined by slowly sprinkling 500 g of the sample ceramic shot on an inclined aluminum tray that is 0.062 inch (1.6 mm) deep by 6 inches (152 mm) wide by 12 inches (305 mm) long. The tray is supported by a nonmagnetic frame so that it is inclined with a 6-inch (152-mm) rise from end to end (30 degrees from horizontal). Four 1 x 1 x 6 inches (25 x 25 x 152 mm) bar magnets are positioned against the under surface and crosswise to the inclined tray about the middle of its length. Magnets shall be not less than 10000 Gauss magnetic field each and arranged so that the magnetic north and south poles alternate. The magnetic particles (iron) that accumulate on the tray as the shots roll down are carefully brushed into a preweighed dish. The procedure is repeated with the same 500 g sample until all visible magnetic particles are collected. The dish is then reweighed and the magnetic particle content is calculated as a percentage of the total original sample.

4. MICROSTRUCTURE

Ceramic shots are manufactured by electric fusion of oxides to form a closely bonded internal structure of a crystalline zirconia phase within an amorphous silica phase.

5. SPECIFIC GRAVITY

Specific gravity shall be from 3.60 to 3.95 g/cm³ measured at temperature at 70 °F ± 20 °F (21 °C ± 11 °C) by pycnometric method.

6. HARDNESS

Unless otherwise specified, the ceramic shot shall have the following hardness:

623-785 DPH (1 Kgf)
or 660-812 KHN (500 gf)
(for reference, only approximately 57 to -63 HRC)

7. SIZE

Unless otherwise specified, the ceramic shot shall conform to Table 1. Sieve analysis shall be determined in accordance with ASTM D1214. Screens shall be in accordance with U.S. Standard Series, described in ASTM E11.

7.1 Testing

This is conducted by screening a 250 g sample with sieves conforming to ASTM E11.

8. SHAPE

Refer to AMS2431/7.

8.1 Sphericity

Refer to AMS2431/7.

8.2 ANGULARITY

Refer to AMS2431/7.

8.2.1 Appearance

Ceramic shot is constant in color, free flowing, free of defects, and free of foreign matter.

9. QUALITY ASSURANCE

Ceramic shot quality is checked by lots of 1000 kg maximum. A representative sample of the shipped lot shall be tested for conformance to all requirements of this specification. Lot number and this specification number shall be marked on each container unit. All control data will be available from manufacturer on request for 2 years after shipment.

10. NOTES

10.1 Revision Indicator

A change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this document. An (R) symbol to the left of the document title indicates a complete revision of the document, including technical revisions. Change bars and (R) are not used in original publications, nor in documents that contain editorial changes only.

SAENORM.COM : Click to view the full PDF of J1830-202310