

	SURFACE VEHICLE RECOMMENDED PRACTICE	J2081	REV. MAY2007
		Issued 1991-06 Revised 2007-05	
		Superseding J2081 AUG1997	
Test Procedure for Determining the Resistance of Safety-Glazing Materials, of which One Surface is Plastic, to Simulated Weathering			

RATIONALE

Modifications to the Recommended Practice are made for purposes of clarification and format.

1. SCOPE

This SAE Recommended Practice determines whether plastic and glass-plastic safety glazing materials will successfully withstand exposure to simulated weathering conditions.

2. REFERENCES

2.1 Applicable Publications

The following publications form a part of the specification to the extent specified herein. Unless otherwise indicated the latest revision of SAE publications shall apply.

2.1.1 ANSI Publication

Available from ANSI, 25 West 43rd Street, New York, NY 10036-8002, Tel: 212-642-4900, www.ansi.org.

ANSI Z26.1-1996 Glazing Materials for Glazing Motor Vehicles and Motor Vehicle Equipment Operating on Land Highways, Safety Standard

2.1.2 ISO Publications

Available from ANSI, 25 West 43rd Street, New York, NY 10036-8002, Tel: 212-642-4900, www.ansi.org.

ISO 3537-93 Road vehicles—Safety glazing materials—Test methods for mechanical properties

ISO 3538-78 Road vehicles—Safety glazing materials—Test methods for optical properties

ISO 3917-92 Road vehicles—Safety glazing materials—Test methods for resistance to radiation, high temperature, humidity, fire, and simulated weathering

ISO 4892 Plastics—Methods of exposure to laboratory light sources—Part 1: General guidance

ISO 4892-2 Plastics—Methods of exposure to laboratory light sources—Part 2: Xenon-arc sources

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
 Tel: 724-776-4970 (outside USA)
 Fax: 724-776-0790
 Email: CustomerService@sae.org

SAE WEB ADDRESS:

<http://www.sae.org>

2.1.3 CIE Publication

Available from Commission Internationale de l'Eclairage, CIE Central Bureau, Kegelgasse 27, A-1030 Wien, Austria, Tel: +43-1-714-31-87-0, www.cie.co.at.

CIE Publication No. 15.2 (1986) Colorimetry

3. EXPOSURE APPARATUS

The light source included in this document is the long-arc xenon lamp.

3.1 Long-Arc Xenon Lamp

The exposure apparatus¹ shall utilize a long-arc xenon lamp as the source of irradiation, which shall comply with ISO 4892, Part 2.2, Section 4 (artificial weathering).

The long-arc xenon lamp is advantageous in that it can, when correctly filtered and maintained, yield a spectrum most closely approximating that of natural sunlight. To this end, the quartz xenon burner tube, shall be fitted with suitable borosilicate glass optical filter(s)². The xenon lamps employed shall be operated from a suitable 50 or 60 Hz power supply through suitable reactance transformers and electrical equipment.

The UV radiation distribution shall be as specified in ISO 4892-2.2, Section 4.1.2, Table 1, Relative spectral irradiance for artificial weathering (Method A).

The exposure apparatus shall include equipment necessary for measuring and/or controlling the following:

- a. Irradiance
- b. Black panel temperature
- c. Water spray
- d. Operating schedule or cycle

The exposure apparatus shall be made from inert materials which do not contaminate the water employed in the test.

Irradiance shall be measured at the test specimen surface and shall be controlled according to the recommendations of the manufacturer.

Total ultraviolet³ radiant exposure (Joules per square meter) shall be measured or computed and shall be considered the primary measure of test specimen exposure.

4. TEST SPECIMENS

The dimensions of the test specimen shall normally be those specified in the appropriate test method for the property or properties to be measured after exposure.

The number of test specimens for each test condition or exposure stage shall be determined, in addition to those required for visual evaluations as referenced in Section 6 of this document, by the number required by the test methods.

It is recommended that visual evaluations be conducted on the largest test specimens tested.

¹ Such as Atlas Ci, Xenotest® Series, or equivalent.

² Such as Corning 7740, Atlas Type S, Atlas Suprax, or equivalent.

³ Total ultraviolet is considered to be all radiation of wavelength less than 400 nm.

5. PROCEDURE

Measure according to ANSI Z26.1 (1996) or ISO 3538, the luminous transmission of the test specimen(s) to be exposed. (It is not necessary to condition specimens prior to exposure in this test, as the test itself includes special conditions.) Measure, according to ANSI Z26.1 (1996) or ISO 3537, the resistance to abrasion of the plastic surface(s) (whether coated or uncoated) of the control specimen(s).

The face of each test specimen, which would represent the exterior surface when mounted on a road vehicle, shall face the lamp.

Other exposure conditions shall be as follows:

- 5.1 In accordance with ISO 4892, the irradiance shall not vary more than $\pm 10\%$ over the whole test specimen area.
- 5.2 At appropriate intervals, clean lamp filters by washing with detergent and water. Xenon-arc filters shall be replaced according to the recommendations of the equipment manufacturer.
- 5.3 The temperature within the exposure apparatus during the dry portion of the cycle shall be controlled by circulation of sufficient air to maintain a constant black standard temperature. This temperature shall be $70\text{ }^{\circ}\text{C} \pm 3\text{ }^{\circ}\text{C}$ as indicated by a Black Standard Thermometer⁴ or equivalent.
- 5.4 The thermometer is preferably mounted on a support for a test panel in such a way that it receives the same radiation and cooling conditions as a flat test panel surface on the same support. It may also be located at a fixed distance position different from the specimen distance and calibrated for temperature at the specimen distance.
- 5.5 The relative humidity within the exposure apparatus shall be controlled at $50\% \pm 5\%$ during the dry portions of the cycle.
- 5.6 The deionized water used in the spray cycle shall contain less than 1 ppm silicon dioxide solids and shall leave no permanent deposit or residue on the test specimens which would interfere with subsequent measurements.
- 5.7 The pH of the water shall be between 6.0 and 8.0, and the conductivity shall be less than 5 microsiemens.
- 5.8 The temperature of the water in the line where it enters the exposure apparatus shall be at the ambient water temperature.
- 5.9 The water shall strike the test specimens in the form of a fine spray in sufficient volume to wet the test specimens uniformly, immediately upon impact. Water spray will be directed only against the test specimen surface facing the light source. No recirculation of the spray water or immersion of the test specimens in the water shall be permitted.
- 5.10 The test specimens shall be rotated about the arc in order to provide uniform distribution of the light. All positions in the exposure apparatus shall be filled with test specimens or surrogates to ensure that a uniform temperature distribution is maintained. Test specimens shall be held in frames with backs exposed to the cabinet environment. However, reflections from cabinet walls shall not be permitted to strike the back surface of specimens. If necessary, samples may be backed to block such reflections; the backing must not be in direct contact with the specimen and must not impede the free circulation of air at the specimen surface.
- 5.11 The exposure apparatus shall be operated to provide continuous light and intermittent water spray in 2 hour cycles. Each 2 hour cycle, in accordance with ISO 4892, shall be divided into periods during which the test specimens are exposed to light without water spray for 102 minutes and to light with water spray for 18 minutes.

⁴ The Black Standard Thermometer (BST) is defined by ISO 4892, Part 1, Section 4.1.5.