

Submitted for recognition as an American National Standard

## Intrusion Resistance of Safety Glazing Systems for Road Vehicles

**Foreword**—Installation of enhanced protective side and rear glazing systems to provide improved intrusion resistance is growing rapidly. With this growth comes an industry need for a standardized intrusion resistance test to insure that vehicle glazing systems provide a defined minimum level of performance.

1. **Scope**—This SAE Recommended Practice specifies an intrusion resistance test method for glazing systems installed in motor vehicles.

Intrusion resistance performance is determined not solely by the glazing but also by the glazing attachment to the vehicle and by the vehicle structure. Therefore, the glazing/ attachment /vehicle structure must be tested as a single unit.

This test determines intrusion resistance only. The test applies to those materials that meet the requirements for use as safety glazing materials as specified in Safety Standard ANSI/SAE Z26.1 or other applicable standards. The test applies to all installation locations.

2. **References**

- 2.1 **Applicable Publications**—The following publications form a part of this specification to the extent specified herein.

- 2.1.1 SAE PUBLICATION—Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

ANSI/SAE Z26.1—American National Standard for Safety Glazing Materials for Glazing Motor Vehicles and Motor Vehicle Equipment Operating on Land Highways—Safety Standard

- 2.1.2 BSI PUBLICATIONS—Available from British Standards Institution, Customer Services, Sales Dept., 389 Chiswick High Road, London W4 4AL United Kingdom.

BS AU 209-4a:1995—Vehicle Security. Specification for security glazing for passenger cars and car derived vehicles. (This version of the procedure is required. Any future versions are not to be followed.)

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

TO PLACE A DOCUMENT ORDER: (724) 776-4970 FAX: (724) 776-0790  
SAE WEB ADDRESS <http://www.sae.org>

**2.2 Related Publications**—The following publications are provided for information purposes only and are not a required part of this document.

2.2.1 SAE PUBLICATIONS—Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

SAE Paper No. 1999-01-3159—Intrusion Resistance Test Development for Automotive Glazing, by Esposito

SAE Paper No. 982319—Evaluating the Intrusion Resistance of Installed Motor Vehicle Glazing, by Chlastawa and Horaney

SAE Paper No. 982320—Laminated Sidelights and Asymmetrical Windshields for Cars, by Jourdain et al

SAE Paper No. 2000-01-2693—System Design Parameters in Determining Automotive Sidelite Glazing Performance, by Smith

### 3. Definitions

**3.1 Intrusion Resistant Glazing**—Glazing which deters unauthorized entry into or theft of motor vehicles.

**3.2 Daylight Opening**—Aperture in the vehicle through which daylight enters the passenger compartment, usually covered with transparent glazing.

### 4. Technical Requirements

#### 4.1 Test Apparatus

4.1.1 A spring-loaded center punch or a hammer of about 75 g, each with a point having a radius of curvature of  $0.2 \text{ mm} \pm 0.05 \text{ mm}$  shall be used for initial fracture test.

4.1.2 A pendulum device as specified in BS AU 209-4a: 1995 (ref. 2.1.2) shall be used for the exterior impact testing.

4.1.3 A ram capable of applying and measuring a force of up to at least 400 N at an accuracy of  $\pm 5\%$ , with a  $76.2 \text{ mm} \pm 3.8 \text{ mm}$  radius hemispherical headform and traveling at a rate of  $102 \text{ mm/min} \pm 5 \text{ mm/min}$  shall be used for the pushout test, pushing from the interior of the vehicle towards the exterior. The ram will be positioned normal to the interior surface of the glazing. The headform will not crush or otherwise significantly deform during the test.

**4.2 Test Specimens**—All test specimens will be production parts and mounted into the vehicle structure according to the manufacturer's recommendations. They shall be held at laboratory conditions for at least 4 h prior to testing. Tests shall be carried out under the following conditions: temperature:  $20 \text{ }^\circ\text{C} \pm 5 \text{ }^\circ\text{C}$ ; pressure:  $960 \text{ mbar} \pm 100 \text{ mbar}$ ; relative humidity:  $60\% \pm 20\%$ . All testing will be conducted with specimens installed on a vehicle or a vehicle subsection (such as installed on a door).

**4.3 Procedure**—The following three-test sequence will be performed on a single test specimen. This test sequence simulates typical attacks on glazing, including: an attempt to shatter the glazing with a sharp-tipped implement; blunt impacts on the exterior of the glazing to penetrate the glazing; an attempt to pull outward on the glazing to remove it from the vehicle (simulated in this test by pushing outward with a ram).

4.3.1 Center punch or hammer attack on exterior of glazing. At location No. 3 (ref. 2.1.2), the exterior of the glazing will be subjected to one impact by a spring-loaded center punch or by a hammer.

4.3.2 Five pendulum impacts on the exterior glazing surface, as specified in ref. 2.1.2, will be performed.

- 4.3.3 Centered on location No. 3, a ram, as specified in 4.1.3, will be traversed in the direction from the interior towards the exterior, normal to the interior surface of the glazing, at a rate of 102 mm/min, until a force of 400 N is applied or until the test specimen fails.
- 4.3.4 For test specimens in which the glazed area is too small to accommodate the entire pendulum impact pattern, first perform the center punch or hammer attack on the exterior of the glazing at a central point. Next, carry out a single pendulum impact on the exterior of the glazing at any point that is further than 100 mm from the daylight opening. Then conduct the ram push-out test at the same location as the pendulum impact. If the glazing area is too small for the pendulum and the ram tests to be conducted, only the center punch or hammer attack will be performed.

#### **4.4 Interpretation of Results**

- 4.4.1 After center punch or hammer attack, there shall be no separation either within the glazing material or between the glazing and the vehicle body which allows free passage of a sphere  $40 \text{ mm} \pm 2 \text{ mm}$  in diameter.
- 4.4.2 After the five exterior impacts, there shall be no separation either within the glazing material or between the glazing and the vehicle body which allows free passage of a sphere  $40 \text{ mm} \pm 2 \text{ mm}$  in diameter.
- 4.4.3 During the ram test, there shall be no separation either within the glazing material or between the glazing and the vehicle body which allows free passage of a sphere  $40 \text{ mm} \pm 2 \text{ mm}$  in diameter. Separation shall be measured while the ram is applying a force of 400 N. For a separation within the glazing material located at or near the face of the ram, where passage of the 40 mm sphere will be hindered by the ram, the size of the separation will be measured with calipers. In this case, the measured separation must be less than a circle of 40 mm diameter while the applied force is 400 N.

#### **5. Marking of Intrusion Resistant Glazing Systems**

- 5.1 Glazing systems which pass the series of three attack tests may be labeled by the car maker as Enhanced Protective Glazing (EPG). Location and nature of the marking will be determined by the car maker.

PREPARED BY THE SAE GLAZING MATERIALS STANDARDS COMMITTEE