

**SAE** The Engineering Society  
For Advancing Mobility  
Land Sea Air and Space®

A Product of the  
Cooperative Engineering Program

**SAE J402 DEC88**

**SAE Numbering  
System for Wrought  
or Rolled Steel**

SAE Standard  
Reaffirmed December 1988

SAENORM.COM : Click to view the full PDF of J402-198812

**S. A. E.  
LIBRARY**

Submitted for Recognition as  
an American National Standard

SAENORM.COM : Click to view the full PDF of j402\_198812

No part of this publication may be reproduced in any form, in an electronic retrieval system or otherwise, without the prior written permission of the publisher.

**Copyright 1989 Society of Automotive Engineers, Inc.**

**SAE NUMBERING SYSTEM FOR WROUGHT OR ROLLED STEEL**

1. This SAE Standard is intended to supply a uniform means of designating wrought ferrous materials reported in SAE Standards and Recommended Practices.

A numeral index system is used to identify the compositions of the SAE steels. This system makes it possible to use numbers on shop drawings and blueprints to describe partially the composition of the material. A four-numeral series is usually used to designate standard alloy and carbon steels specified to chemical composition ranges. There are certain types of alloy steels which are designated by five numerals. The prefix E is used to designate steels which are made by the basic electric furnace process with special practices. The suffix H is used to designate standard hardenability steels. The last two digits of the four-numeral series and the last three digits of the five-numeral series are intended to indicate the approximate mean of the carbon range. For example, in the Grade 1035, 35 represents a carbon range of 0.32 to 0.38% and in Grade E52100, 100 represents a carbon range of 0.98 to 1.10%. It is necessary, however, to deviate from this system and to interpolate numbers in the case of some carbon ranges, and for variations in manganese, sulfur, or other elements with the same carbon range. The first two digits of the SAE numeral series for the various grades of alloy and carbon steel are given in Table 1.

The Unified Numbering System (UNS) is described in greater detail in SAE J1086 and ASTM E 527.

The basic numerals of the various types of standard and formerly standard SAE steels are given in the table.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

TABLE 1

Numerals and Digits		Type of Identifying Elements	Refer to SAE Standard or Information Report - JXXX for Composition Limits
UNS	SAE		
G10XX0	10XX <sup>a</sup>	CARBON STEELS Nonresulfurized, Manganese 1.00% maximum	403 and 1249
G11XX0	11XX	Resulfurized	403 and 1249
G12XX0	12XX	Rephosphorized and Resulfurized	403
		ALLOY STEELS	
G13XX0	13XX	Manganese Steels	404 and 1249
G23XX0	23XX	Nickel Steels	1249
G25XX0	25XX	Nickel Steels	1249
G31XX0	31XX	Nickel-Chromium Steels	1249
G32XX0	32XX	Nickel-Chromium Steels	1249
G33XX0	33XX	Nickel-Chromium Steels	1249
G34XX0	34XX	Nickel-Chromium Steels	1249
G40XX0	40XX	Molybdenum Steels	404 and 1249
G41XX0	41XX	Chromium-Molybdenum Steels	404 and 1249
G43XX0	43XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G44XX0	44XX	Molybdenum Steels	404 and 1249
G46XX0	46XX	Nickel-Molybdenum Steels	404 and 1249
G47XX0	47XX	Nickel-Chromium-Molybdenum Steels	404
G48XX0	48XX	Nickel-Molybdenum Steels	404 and 1249
G50XX0	50XX	Chromium Steels	404 and 1249
G51XX0	51XX	Chromium Steels	404 and 1249
G50XX6	50XXX	Chromium Steels	404
G51XX6	51XXX	Chromium Steels	404
G52XX6	52XXX	Chromium Steels	404
G61XX0	61XX	Chromium-Vanadium Steels	404 and 1249
G71XX0	71XXX	Tungsten-Chromium Steels	1249
G72XX0	72XX	Tungsten-Chromium Steels	1249
G81XX0	81XX	Nickel-Chromium-Molybdenum Steels	404
G86XX0	86XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G87XX0	87XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G88XX0	88XX	Nickel-Chromium-Molybdenum Steels	404
G92XX0	92XX	Silicon-Manganese Steels	404 and 1249
G93XX0	93XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G94XX0	94XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G97XX0	97XX	Nickel-Chromium-Molybdenum Steels	1249
G98XX0	98XX	Nickel-Chromium-Molybdenum Steels	1249
		CARBON AND ALLOY STEELS	
GXXXX1	XXBXX	B denotes Boron Steels	403 and 404
GXXXX4	XXLXX	L denotes Leaded Steels	403 and 404
		STAINLESS STEELS	
S2XXXX	302XX	Chromium-Nickel Steels	405
S3XXXX	303XX	Chromium-Nickel Steels	405
S4XXXX	514XX	Chromium Steels	405
S5XXXX	515XX	Chromium Steels	405
		EXPERIMENTAL STEELS	
None	EX--	SAE Experimental Steels	1081

<sup>a</sup>SAE J403 describes UNS G 15XX0 and SAE 15XX as applicable only to semi-finished products for forging, for hot-rolled and cold-finished bars, for wire rods, and for seamless tubing.

RATIONALE:

Not applicable.

RELATIONSHIP OF SAE STANDARD TO ISO STANDARD:

Not applicable.

REFERENCE SECTION:

SAE J1086 APR83, Numbering Metals and Alloys

ASTM E 527

APPLICATION:

This SAE Standard is intended to supply a uniform means of designating wrought ferrous materials reported in SAE Standards and Recommended Practices.

COMMITTEE COMPOSITION:

DEVELOPED BY THE SAE DIVISION 1 - CARBON AND ALLOY STEELS:

P. A. Speer, Inland Steel Co., Chicago, IL - Chairman  
G. A. Beaudoin, Stelco Steel, Hamilton, Ontario, Canada  
L. W. Bella, USX Corp., Lorain, OH  
R. Binoniemi, Eaton Corporation, Kalamazoo, MI  
J. A. Carosiello, Timken Company, Canton, OH  
R. H. Cobbett, Matco Tools, Stow, OH  
M. E. Dilley, Chrysler Corp., Detroit, MI  
M. L. Frey, Leesburg, FL  
G. G. Hoeft, Caterpillar, Inc., E. Peoria, IL  
C. J. Keith, Navistar Intl. Transport Corp., Ft. Wayne, IN  
T. G. Oakwood, Inland Steel Co., E. Chicago, IL  
J. E. Tripp, Dana Corp., Ottawa Lake, MI

SPONSORED BY THE SAE IRON AND STEEL TECHNICAL COMMITTEE:

G. G. Witt, Ford Motor Company, Dearborn, MI - Chairman  
F. J. Arabia, General Motors Corp., Warren, MI  
R. J. Belz, Bloomfield Hills, MI  
R. D. Bennett, White Farm Equip. Co., Charles City, IA  
F. P. Bens, Kolene Corp., Detroit, MI  
E. T. Bittner, Brookfield, WI  
H. N. Bogart, Traverse City, MI