

**SAE NUMBERING SYSTEM FOR WROUGHT OR ROLLED STEEL**

1. **Scope**—This SAE Standard is intended to supply a uniform means of designating wrought ferrous materials reported in SAE Standards and Recommended Practices.

A numerical index system is used to identify the compositions of the SAE steels. This system makes it possible to use numbers on shop drawings and blueprints to describe partially the composition of the material. A four-numeral series is usually used to designate standard alloy and carbon steels specified to chemical composition ranges. There are certain types of alloy steels which are designated by five numerals. The prefix E is used to designate steels which are made by the basic electric furnace process with special practices. The suffix H is used to designate standard hardenability steels. The last two digits of the four-numeral series and the last three digits of the five-numeral series are intended to indicate the approximate mean of the carbon range. For example, in the Grade 1035, 35 represents a carbon range of 0.32 to 0.38% and in Grade E52100, 100 represents a carbon range of 0.98 to 1.10%. It is necessary, however, to deviate from this system and to interpolate numbers in the case of some carbon ranges, and for variations in manganese, sulfur, or other elements with the same carbon range. The first two digits of the SAE numeral series for the various grades of alloy and carbon steel are given in Table 1.

The Unified Numbering System (UNS) is described in greater detail in SAE J1086 and ASTM E 527.

The basic numerals of the various types of standard and formerly standard SAE steels are given in Table 1.

2. **References**

- 2.1 **Applicable Documents**—The following publications form a part of this specification to the extent specified herein. Unless otherwise specified, the latest issue of SAE publications shall apply.

- 2.1.1 SAE PUBLICATIONS—Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

SAE J403—Chemical Compositions of SAE Carbon Steels  
SAE J404—Chemical Compositions of SAE Alloy Steels  
SAE J405—Chemical Compositions of SAE Wrought Stainless Steels  
SAE J1081—Potential Standard Steels  
SAE J1086—Numbering Metals and Alloys  
SAE J1249—Former SAE Standard and Former SAE Ex-Steels

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

QUESTIONS REGARDING THIS DOCUMENT: (412) 772-8512 FAX: (412) 776-0243  
TO PLACE A DOCUMENT ORDER; (412) 776-4970 FAX: (412) 776-0790  
SAE WEB ADDRESS <http://www.sae.org>

SAE J402 Revised MAY97

TABLE 1—VARIOUS GRADES OF ALLOY AND CARBON STEEL

Numerals and Digits UNS	Numerals and Digits SAE	Type of Identifying Elements	Refer to SAE Standard or Information Report - JXXX for Composition Limits
CARBON STEELS			
G10XX0	10XX	Nonresulfurized, Manganese 1.00% maximum	403 and 1249
G11XX0	11XX	Resulfurized	403 and 1249
G12XX0	12XX	Rephosphorized and Resulfurized	403
G15XX0	15XX	Nonresulfurized, Manganese Maximum over 1.00%	403 and 1249
ALLOY STEELS			
G13XX0	13XX	Manganese Steels	404 and 1249
G23XX0	23XX	Nickel Steels	1249
G25XX0	25XX	Nickel Steels	1249
G31XX0	31XX	Nickel-Chromium Steels	1249
G32XX0	32XX	Nickel-Chromium Steels	1249
G33XX0	33XX	Nickel-Chromium Steels	1249
G34XX0	34XX	Nickel-Chromium Steels	1249
G40XX0	40XX	Molybdenum Steels	404 and 1249
G41XX0	41XX	Chromium-Molybdenum Steels	404 and 1249
G43XX0	43XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G44XX0	44XX	Molybdenum Steels	404 and 1249
G46XX0	46XX	Nickel-Molybdenum Steels	404 and 1249
G47XX0	47XX	Nickel-Chromium-Molybdenum Steels	404
G48XX0	48XX	Nickel-Molybdenum Steels	404 and 1249
G50XX0	50XX	Chromium Steels	404 and 1249
G51XX0	51XX	Chromium Steels	404 and 1249
G50XX6	50XXX	Chromium Steels	404
G51XX6	51XXX	Chromium Steels	404
G52XX6	52XXX	Chromium Steels	404
G61XX0	61XX	Chromium-Vanadium Steels	404 and 1249
G71XX0	71XXX	Tungsten-Chromium Steels	1249
G72XX0	72XX	Tungsten-Chromium Steels	1249
G81XX0	81XX	Nickel-Chromium-Molybdenum Steels	404
G86XX0	86XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G87XX0	87XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G88XX0	88XX	Nickel-Chromium-Molybdenum Steels	404
G92XX0	92XX	Silicon-Manganese Steels	404 and 1249
G93XX0	93XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G94XX0	94XX	Nickel-Chromium-Molybdenum Steels	404 and 1249
G97XX0	97XX	Nickel-Chromium-Molybdenum Steels	1249
G98XX0	98XX	Nickel-Chromium-Molybdenum Steels	1249
CARBON AND ALLOY STEELS			
GXXXX1	XXBXX	B denotes Boron Steels	403 and 404
GXXXX4	XXLXX	L denotes Leaded Steels	403 and 404
-----	XXVXX	V denotes Vanadium Steels	J403 <sup>(1)</sup>
STAINLESS STEELS			
S2XXXX	302XX	Chromium-Nickel Steels	405
S3XXXX	303XX	Chromium-Nickel Steels	405
S4XXXX	514XX	Chromium Steels	405
S5XXXX	515XX	Chromium Steels	405
POTENTIAL STANDARD STEELS			
None	PS--	SAE Experimental Steels	1081

1. Applies to carbon steels only.

SAE J402 Revised MAY97

2.1.2 ASTM PUBLICATION—Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 527—Practice for Numbering Metals and Alloys (UNS)

**3. Notes**

**3.1 Marginal Indicia**—The change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions have been made to the previous issue of the report. An (R) symbol to the left of the document title indicates a complete revision of the report.

PREPARED BY THE SAE IRON AND STEEL TECHNICAL COMMITTEE DIVISION 1—  
CARBON AND ALLOY STEELS

SAENORM.COM : Click to view the full PDF of J402\_199705