

Issued 1962-03
Cancelled 1998-06

Superseding J815 JAN94

Load Deflection Testing of Urethane Foams for Automotive Seating

1. **Scope**—Cellular foam products have been traditionally checked for load deflection by determining the load required to effect a 25% deflection. In seating, on the other hand, the interest is in determining how thick the padding is under the average passenger load (a measurement of padding left for "ride" and seated height), a second measurement to give an indication of initial softness, and a final figure to indicate resiliency. To most easily fulfill these requirements, load deflection on flexible urethane foams for automotive seating is determined here by measuring the thickness of the pad under fixed loads of 1 lb, 25 lb, and 50 lb on a 50 in² circular indenter foot.
2. **References**
 - 2.1 **Applicable Publication**—The following publication forms a part of the specification to the extent specified herein.
 - 2.1.1 **ASTM PUBLICATION**—Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM D 1564—Specifications and Methods of Test for Flexible Urethane Foam
 3. **Test Conditions**—Material must be at least 96 h old before testing. Tests shall be conducted under known conditions of temperature and humidity with 73.4 °F ± 2 °F and 50% ± 2% relative humidity for a minimum of 16 h, the standard in case of disputes, ASTM D 1564.
 4. **Test Specimens**—When possible, the completed manufactured product shall be used with top and bottom skins, if present, intact. In the case of tapered pads, location of area for measurement is to be agreed upon by parties concerned. In the case a finished part is not feasible for test, by mutual agreement, 15 in x 15 in x average pad thickness specimens may be used. In the case of tapered or irregularly surfaced pads, by mutual agreement, 15 in x 15 in pieces may be cut to uniform thickness and plied up (no cement is to be used).
 5. **Apparatus**—An apparatus having a flat circular indenter foot 50 in² in area, and dead weight loaded through a swivel joint with loads of 1 lb, 25 lb, 50 lb, and 75 lb is mounted over a level horizontal platform (which is perforated with 1/4 in holes on 3/4 in centers to allow for rapid escape of air during test). The distance between indenter foot and platform is variable to compress sample under test (at a speed of 2 in/min for deflection measurements, 4 in/min for preflexing) and is equipped with a device for measuring distance between plates.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

QUESTIONS REGARDING THIS DOCUMENT: (724) 772-8512 FAX: (724) 776-0243
TO PLACE A DOCUMENT ORDER: (724) 776-4970 FAX: (724) 776-0790
SAE WEB ADDRESS <http://www.sae.org>

6. Procedure

- a. One specimen is sufficient for a test. Sample to be checked is placed in machine with distance from edge of indenter foot to edge of sample not less than the pad thickness. Sample is deflected twice with a 75 lb load on a 50 in² indenter foot (at 4 in/min) and allowed to rest 5 min ± 1 min. It is advisable to mark test area (around indenter foot) with a ball point pen.
- b. Indenter foot is brought into contact with previously preflexed area and height of specimen determined with 1 lb load on the 50 in² indenter foot.
- c. The 25 lb load is applied to indenter foot and specimen compressed at 2 in/min until load is carried by pad. Thickness is then determined after maintaining load for 1 min.
- d. The 50 lb load is applied to indenter foot and after 1 min under load, thickness of pad is determined.
- e. Finally the weight is reduced to 25 lb (at a rate of 2 in/min) and after maintaining the load for 1 min the thickness is measured.

PREPARED BY THE SAE TEXTILE/FLEXIBLE PLASTICS COMMITTEE

SAENORM.COM : Click to view the full PDF of J815 - 199806