

TEST METHOD FOR MEASURING THICKNESS OF AUTOMOTIVE TEXTILES AND PLASTICS

Foreword—This Document has not changed other than to put it into the new SAE Technical Standards Board Format.

1. **Scope**—This test is designed to measure the thickness of relatively flat textiles, plates, and similar materials.
2. **References**—There are no referenced publications specified herein.
3. **Apparatus Required**
 - 3.1 A dead weight type of dial micrometer capable of accurately measuring to 0.025 mm. The pressure foot shall have a diameter of:
 - a. 76.2 mm for testing tufted floor covering
 - b. 28.7 mm for testing felts and other nonwovens
 - c. 6.35 mm for testing bodycloth¹
 - d. 6.35 mm for testing unsupported vinyl film and covered fabrics
 - 3.2 The pressure foot and connected parts shall be weighted to apply to a total load of:
 - a. 340 g for testing tufted floor coverings
 - b. 283 g for testing felts and other nonwovens
 - c. 85 g for testing bodycloth¹
 - d. 85 g for testing unsupported vinyl film and covered fabrics
4. **Test Specimens**—Cut three test specimens approximately 100 x 100 mm from the center and two opposite sides of the roll. Unless otherwise specified, samples shall be taken no nearer the selvage edge than one-tenth of the width of the material, or nearer than 300 mm from either end of the roll. If the material does not come in rolls, the sample should be taken from the most representative areas.
5. **Procedure**—Condition the samples at 21 °C ± 2 °C and 50% ± 5% relative humidity for 24 h. Raise the pressure foot of the thickness gage and place the sample on the base. Gently lower the pressure foot and after 10 s read the thickness of the dial micrometer. Repeat in two additional areas and record the average thickness of all three test specimens.

1. When measuring the overall thickness of three-dimensional materials, the thickness shall be determined by calculating the average of three readings taken on the high points of the material.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

QUESTIONS REGARDING THIS DOCUMENT: (412) 772-8512 FAX: (412) 776-0243
TO PLACE A DOCUMENT ORDER; (412) 776-4970 FAX: (412) 776-0790
SAE WEB ADDRESS <http://www.sae.org>

6. **Notes**

- 6.1 **Marginal Indicia**— The change bar (I) is for the convenience of the user in locating areas where technical revisions have been made to the previous issue of the report. If the symbol is next to the report title, it indicates a complete revision of the report.

PREPARED BY THE SAE TEXTILES AND FLEXIBLE PLASTICS COMMITTEE

SAENORM.COM : Click to view the full PDF of j882_199408