

**PINS, COTTER, STEEL, CORROSION AND HEAT RESISTANT
18Cr-10.5Ni-0.40Ti, Metric
PROCUREMENT SPECIFICATION FOR**

FSC 5315

1. SCOPE:

1.1 Type:

This procurement specification covers split cotter pins made to metric dimensions and made from a corrosion and heat resistant steel of the type identified under the Unified Numbering System as UNS S32100.

1.2 Application:

Primarily for use where a corrosion and heat resistant cotter pin is required for locking parts in applications up to 815 °C.

2. REFERENCES:

2.1 Applicable Documents:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other documents shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

SAE MA7211

2.1.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1.1 Aerospace Material Specifications:

AMS 2248 Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly Alloyed Steels, and Iron Alloys

2.1.1.2 Aerospace Standard:

MA3259 Pin - Cotter, Cres AMS 7211, Metric Series

2.1.2 U.S. Government Publications: Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

2.1.2.1 Military Standards:

MIL-STD-1312 Fasteners, Test Methods

MIL-STD-2073-1 DoD Materiel, Procedures for Development and Application of Packaging Requirements

2.1.3 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 262 Standard Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels

ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.2 Definitions:

DEFECTIVE: A unit of product which contains one or more defects.

PRODUCTION INSPECTION LOT: Shall be all finished parts of the same part number, made from a single heat of alloy, heat treated at the same time to the same specified condition, produced as one continuous run, and submitted for vendor's inspection at the same time.

2.3 Unit Symbols:

% - percent (1% = 1/100)

°C - degree Celsius

HV10 - hardness, Vickers, measured under a 10 kg load

HR15N - hardness, Rockwell, 15N scale

kg - kilogram

mm - millimeter

sp gr - specific gravity

3. TECHNICAL REQUIREMENTS:

3.1 Material:

The cotter pins shall be made from half-round wire conforming to the following requirements:

- 3.1.1 Composition: Shall conform to the percentages by weight specified in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Material Composition

Element	% by Weight	
	Min	Max
Carbon	--	0.08
Manganese	--	2.00
Silicon	0.40	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	17.00	19.00
Nickel	8.00	12.00
Titanium	5x(C+N)	0.70
Molybdenum	--	0.75
Copper	--	0.75
Nitrogen	--	0.10
Iron	remainder	

- 3.1.2 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

- 3.1.3 Condition: Wire shall be solution heat treated free from continuous carbide network (determined in accordance with ASTM A 262, Practice E) and cold finished.

- 3.1.4 Tolerances: Permissible variations in cross-sectional dimensions of the half-round wire for manufacture of cotter pins shall be ± 0.05 mm for major axis and ± 0.025 mm for the minor axis.

3.2 Design:

Unless otherwise specified on the part drawing, cotter pins furnished to this specification shall conform to the design, dimensions, and other requirements specified on the MA3259 standard part drawing, having ends slightly rounded, beveled, or pointed with one end slightly extended beyond the other to permit easy assembly (see Figure 1).




FIGURE 1 - Optional Cotter Pin Ends

3.3 Cleaning:

Parts, after finishing, shall be degreased and immersed in one of the following solutions for the time and temperature shown:

- a. One volume of nitric acid (sp gr 1.42) and 9 volumes of water for not less than 20 minutes at room temperature.
- b. One volume of nitric acid (sp gr 1.42) and 4 volumes of water for 30 to 40 minutes at room temperature.
- c. One volume of nitric acid (sp gr 1.42) and 4 volumes of water for 10 to 15 minutes at 60 to 70 °C.

3.4 Properties:

Cotter pins shall conform to the following requirements:

- 3.4.1 **Hardness:** Shall have hardness in conformance with Table 2, unless otherwise specified on the part drawing and determined in accordance with MIL-STD-1312-6.

TABLE 2 - Hardness of Cotter Pins

Nominal Pin Diameter mm	Vickers Hardness HV10	Rockwell Hardness HR15N
1.6 and less	200 to 350	65 to 78
2.0 and 2.5	170 to 350	60 to 78
3.2 and larger	140 to 220	55 to 67

- 3.4.2 **Bending:** Either prong of any cotter pin shall withstand bending flat on itself, without cracking; the flat of the prong shall form the outside of the bend.

3.5 Quality:

Cotter pins, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the parts. The ends of the prongs shall not be spread open.

4. QUALITY ASSURANCE PROVISIONS:**4.1 Responsibility for Inspection:**

The vendor of parts shall supply all samples for vendor's test and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the parts conform to the requirements of this specification.

4.2 Responsibility for Compliance:

The manufacturer's system for parts production shall be based on preventing product defects, rather than detecting the defects at final inspection and then requiring corrective action to be invoked. An effective manufacturing in-process control system shall be established, subject to the approval of the purchaser, and used during production of parts.

4.3 Production Acceptance Tests:

The purpose of production acceptance tests is to check, as simply as possible, using a method which is inexpensive and representative of the part usage, with the uncertainty inherent in random sampling, that the parts comprising a production inspection lot satisfy the requirements of this specification.

4.3.1 Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each production inspection lot. A summary of acceptance tests is specified in Table 3.

TABLE 3 - Summary of Acceptance Tests

TABLE 3A - Nondestructive Tests

Characteristic	Req. Para.	Sample Size	Test Method
Design & dimensions	3.2	4.4.2	Conventional measuring methods
Quality	3.5	4.4.2	Visual

TABLE 3B - Destructive Tests

Characteristic	Req. Para.	Sample Size	Test Method
Material composition	3.1	4.4.1	ASTM E 353
Hardness	3.4.1	4.4.3	MIL-STD-1312-6
Bending	3.4.2	4.4.4	Per 3.4.2

4.4 Acceptance Tests Sampling:

4.4.1 Material: One sample of wire, from which cotter pins were made, from each heat of alloy.