

**AEROSPACE
MATERIAL
SPECIFICATION**

Issued JUL 1982
Reaffirmed OCT 1999
Noncurrent MAR 2003

Superseding MAM 2221B

Tolerances, Metric
Copper and Copper Alloy Bars and Rods

NONCURRENCY NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of March, 2003. It is recommended, therefore, that this specification not be specified for new designs.

AMS 2221 covers the same requirements.

"NONCURRENT" refers to those materials which have been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs.

"NONCURRENT" specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of MAM 2221C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 Society of Automotive Engineers, Inc.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

1. SCOPE:

This specification covers established metric manufacturing tolerances applicable to bars and rods of copper and copper alloys ordered to metric dimensions. These tolerances apply to all conditions, unless otherwise noted. The term "exclusive" is used to apply only to the higher figure of a specified range.

- 1.1 If the tolerance is expressed as a percentage of a specified dimension, the tolerance so calculated shall be rounded to the nearest 0.02 mm to obtain the permissible tolerance.
- 1.2 AMS 2221 is the inch/pound version of this MAM.

2. DIAMETER OR THICKNESS:**2.1 Cold Finished:**

2.1.1 Rods; Rounds, Hexagons, and Octagons: See Table 1.

2.1.2 Bars; Squares, and Rectangles: Shall be as follows

2.1.2.1 Copper: See Table 2.

2.1.2.2 Nonrefractory Alloys: See Table 3.

2.1.2.3 Refractory Alloys: See Table 4.

2.2 Extruded Round, Hexagonal, Octagonal, Square, and Rectangular Shapes:

See Table 5.

2.3 Hot Finished Rounds:

See Table 6.

3. WIDTH:

See Rectangles, Not Including Squares: See Table 7.

4. LENGTH:

Shall be as shown in Table 8, 4.1, and 4.2.

4.1 Full length pieces specific and stock lengths with or without ends.

4.2 No length tolerances are established for extruded and hot rolled bar.

5. STRAIGHTNESS:**5.1 Cold Finished Rods; Hexagons, Octagons:**

See Table 9.

5.2 Bars; Squares and Rectangles:

When supplied in straight lengths, in rolls, or on bucks, shall be of such straightness that the maximum edgewise curvature (depth of arc) shall be not greater than 12.5 mm in any 1800 mm or 2.0 mm x length in 300 mm for shorter lengths.

6. FLATNESS:

No requirements specified.

7. SPECIAL TOLERANCES:

7.1 If tolerances specified herein are plus and minus and if all plus or all minus are desired, use the sum of the plus and minus values specified, neglecting the signs.

7.2 If tolerances specified herein are all plus and if all minus are desired, use the same values specified.

7.3 If tolerances specified herein are all plus and if plus and minus are desired, halve the values specified.

8. NOTES:

8.1 The change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this specification. An (R) symbol to the left of the document title indicates a complete revision of the specification.

8.2 Similar Specifications:

FED-STD-146 is listed for information only and shall not be construed as an acceptable alternate unless all requirements of this MAM are met.

8.3 Tolerances meeting the requirements of this specification have been classified under Federal Supply Classification (FSC) 95GP.

TABLE 1 - Diameter or Thickness Tolerances, Cold Finished Rods

Specified Diameter or Distance Between Parallel Surfaces mm	Tolerance, mm	Tolerance, mm	Tolerance, mm	Tolerance, mm
	Plus and Minus Nonrefractory Round	Plus and Minus Nonrefractory Hexagonal Octagonal	Plus and Minus Refractory Round	Plus and Minus Refractory Hexagonal Octagonal
Up to 3.8, incl	0.035	0.06	0.050	
Over 3.8 to 12, incl	0.04	0.08	0.05	0.10
Over 12 to 25, incl	0.05	0.10	0.08	0.13
Over 25 to 50, incl	0.06	0.13	0.10	0.15
Over 50	0.15%	0.30%	0.20%	0.40%

TABLE 2 - Thickness Tolerances, Copper, Square and Rectangular Bars

Specified Thickness mm	Thickness Tolerance mm				
	Plus and Minus Width Ranges mm				
Up to 12, incl	Up to 12, incl	Over 12 to 30, incl	Over 30 to 50, incl	Over 50 to 100, incl	Over 100 to 200, incl
Over 4.8 to 12, incl	0.08	0.08	0.09	0.10	0.11
Over 12 to 25, incl	--	0.10	0.10	0.11	0.13
Over 25 to 50, incl	--	0.11	0.11	0.13	0.15
Over 50 to 100, incl	--	--	--	0.30%	--

TABLE 3 - Thickness Tolerances, Nonrefractory Alloys, Square and Rectangular Bars

Specified Thickness mm	Thickness Tolerance mm				
	Plus and Minus Width Ranges mm				
Up to 12, incl	Up to 12, incl	Over 12 to 30, incl	Over 30 to 50, incl	Over 50 to 100, incl	Over 100 to 200, incl
Over 4.8 to 12, incl	0.9	0.10	0.11	0.11	0.13
Over 12 to 25, incl	--	0.11	0.13	0.13	0.18
Over 25 to 50, incl	--	0.13	0.13	0.15	0.20
Over 50 to 100, incl	--	--	--	0.30%	--