

Submitted for recognition as an American National Standard

**TOLERANCES, METRIC
Low-Alloy Steel Bars**

1. SCOPE:

This specification covers established metric manufacturing tolerances applicable to low-alloy steel bars ordered to metric dimensions. These tolerances apply to all conditions, unless otherwise noted. The term "exclusive" is used to apply to the higher figure of the specified range.

1.1 No clear cut demarcation is available to differentiate between bar and wire products, so no definitions of these products are included.

1.2 AMS 2251 is the inch/pound version of this MAM.

2. DIAMETER OR THICKNESS:

2.1 Cold Finished:

2.1.1 Cold Drawn: Table 1 includes tolerances for bars that have been annealed, spheroidize annealed, normalized, normalized and tempered, or quenched and tempered before cold finishing. This table does not include tolerances for bars that are spheroidize annealed, normalized, normalized and tempered, or quenched and tempered after cold finishing.

2.1.1.1 Width governs the tolerances for both width and thickness of flats. For example, when the maximum of carbon range is up to 0.28, inclusive, for a flat 50.00 millimeters wide and 25.00 millimeters thick, the width tolerance is 0.15 millimeter and the thickness tolerance is the same, namely 0.15 millimeter.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

TABLE 1 - Tolerances, Millimeter, Minus Only; Maximum of Carbon Range, %

Specified Diameter of Thickness Millimeters	Up to 0.28 Carbon, incl	Over 0.28 to 0.55 Carbon, incl	Up to 0.55 Carbon, incl, Stress Relieved or Annealed After Cold Finishing	Over 0.55, Carbon, With or Without Stress Relieving or Annealing After Cold Finishing, and All Carbons Quenched and Tempered or Normalized and Tempered Before Cold Finishing
ROUNDS				
Up to 25.00, incl, in coils	0.05	0.08	0.10	0.12
Up to 37.50, incl	0.08	0.10	0.15	0.18
Over 37.50 to 62.50, incl	0.10	0.12	0.15	0.18
Over 62.50 to 100.00, incl	0.12	0.15	0.18	0.20
HEXAGONS				
Up to 18.75, incl	0.08	0.10	0.12	0.18
Over 18.75 to 37.50, incl	0.10	0.12	0.15	0.20
Over 37.50 to 62.50, incl	0.12	0.15	0.18	0.22
Over 62.50 to 78.00, incl	0.15	0.18	0.20	0.25
Over 78.00 to 100.00, incl	0.15	--	--	--
SQUARES				
Up to 18.75, incl	0.08	0.12	0.15	0.20
Over 18.75 to 37.50, incl	0.10	0.15	0.18	0.22
Over 37.50 to 62.50, incl	0.12	0.18	0.20	0.25
Over 62.50 to 100.00, incl	0.18	0.22	0.25	0.30
Over 100.00 to 125.00, incl	0.28	--	--	--
FLATS				
Specified Width, Millimeters				
Up to 18.75, incl	0.10	0.12	0.18	0.22
Over 18.75 to 37.50, incl	0.12	0.15	0.22	0.28
Over 37.50 to 75.00, incl	0.15	0.18	0.28	0.32
Over 75.00 to 100.00, incl	0.18	0.22	0.30	0.42
Over 100.00 to 150.00, incl	0.22	0.28	0.32	0.52
Over 150.00	0.35	--	--	--

2.1.1.2 When rough turned round bars are permitted, the tolerances of Table 1 shall be doubled.

2.1.1.3 The tolerances for flats apply to both width and thickness.

2.1.1.4 Tolerances in the column headed "Over 0.28 to 0.55 carbon, inclusive" also apply to all carbons up to 0.55 maximum, annealed or normalized before cold finishing.

2.1.2 Machined Bars: Tolerances for machined bars 9.50 millimeters and over in (R) specified diameter or thickness are shown in Table 2. Bars up to 9.50 millimeters, exclusive, in specified diameter or thickness, are supplied centerless ground.

TABLE 2 - Tolerances, Machined Bars

Specified Diameter or Thickness Millimeters	Tolerance plus only Millimeter	Out of Round Millimeter
9.50 to 50.00, excl	0.40	0.20
50.00 to 75.00, incl	0.80	0.40
Over 75.00	0.80	0.40

2.1.3 Centerless Ground Bars: Tolerances for centerless-ground bars 3.00 to (R) 105.00 millimeters, inclusive, in specified diameter are shown in Table 3. Bars over 105.00 millimeters in specified diameter are supplied machined.

TABLE 3 - Tolerances, Centerless-Ground Bars

Specified Diameter Millimeters	Tolerance plus or minus Millimeter	Out of Round Millimeter
3.00 to 6.25, excl	0.025	0.025
6.25 to 15.75, excl	0.04	0.04
15.75 to 78.00, excl	0.05	0.05
78.00 to 105.00, incl	0.08	0.08

2.1.4 Ground and Polished Rounds: See Table 4.

TABLE 4 - Tolerances, Ground and Polished Rounds

Specified Diameter Millimeters	Tolerance Millimeter Minus Only
Up to 37.50, incl	0.02
Over 37.50 to 62.50, excl	0.038
62.50 to 75.00, incl	0.05
Over 75.00 to 100.00, incl	0.08

2.2 Hot Finished:

2.2.1 Rounds and Squares: See Table 5.

2.2.1.1 Out-of-round is the difference between the maximum and minimum diameters of the bar, measured at the same cross-section. Out-of-square is the difference in the two dimensions at the same cross-section of a square bar between opposite faces.

TABLE 5 - Tolerances, Hot Finished Rounds and Squares

Specified Diameter or Thickness Millimeters	Tolerance Millimeters Plus	Tolerance Millimeter Minus	Out-of-Round or Out-of-Square Millimeters
Up to 7.80, incl	0.12	0.12	0.20
Over 7.80 to 11.00, incl	0.15	0.15	0.23
Over 11.00 to 15.50, incl	0.18	0.18	0.25
Over 15.50 to 22.00, incl	0.20	0.20	0.30
Over 22.00 to 25.00, incl	0.22	0.22	0.32
Over 25.00 to 28.00, incl	0.25	0.25	0.38
Over 28.00 to 31.25, incl	0.28	0.28	0.41
Over 31.25 to 34.50, incl	0.30	0.30	0.45
Over 34.50 to 37.50, incl	0.35	0.35	0.57
Over 37.50 to 50.00, incl	0.40	0.40	0.58
Over 50.00 to 62.50, incl	0.78	0	0.58
Over 62.50 to 87.50, incl	1.18	0	0.88
Over 87.50 to 115.00, incl	1.58	0	1.15
Over 115.00 to 137.50, incl	1.95	0	1.47
Over 137.50 to 165.00, incl	3.12	0	1.75
Over 165.00 to 205.00, incl	3.90	0	2.12
Over 205.00 to 235.00, incl	4.70	0	2.50
Over 235.00 to 250.00, incl	6.25	0	3.00

2.2.2 Hexagons and Octagons: See Table 6.

TABLE 6 - Tolerances, Hot Finished Hexagons and Octagons

Specified Distance Between Parallel Sides, Millimeters	Tolerance Millimeters Plus	Tolerance Millimeter Minus	Maximum Difference, Millimeters, 3 Measurements, For Hexagons Only
Up to 12.50, incl	0.18	0.18	0.28
Over 12.50 to 25.00, incl	0.25	0.25	0.38
Over 25.00 to 37.50, incl	0.52	0.32	0.62
Over 37.50 to 50.00, incl	0.78	0.40	0.78
Over 50.00 to 62.50, incl	1.18	0.40	1.18
Over 62.50 to 87.50, incl	1.58	0.40	1.58

2.2.3 Square-Edged and Round-Edged Flats: See Table 7.

2.2.3.1 Flats over 150 to 200 millimeters, inclusive, in specified width are not available as hot rolled alloy steel bars in thicknesses under 5.75 millimeters.

2.2.3.2 Tolerances shall be negotiated for flats over 150 to 200 millimeters, inclusive, in specified width and over 75.00 millimeters in specified thickness.

TABLE 7 - Thickness Tolerances, Millimeters, Plus and Minus; Thickness Ranges, Millimeters

Specified Width Millimeters	5.00 to 5.75		6.25 to 12.50		Over 12.50 to 25.00		Over 25.00 to 50.00		Over 50.00 to 75.00		Over 75.00	
	to excl	to incl	to excl	to incl	to excl	to incl	to excl	to incl	to excl	to incl	Plus Millimeters	Minus Millimeters
Up to 25.00, incl	0.18	0.18	0.18	0.20	0.25	0.25	--	--	--	--	0.40	0.40
Over 25.00 to 50.00, incl	0.18	0.18	0.30	0.38	0.38	0.38	0.78	0.78	--	--	0.78	0.78
Over 50.00 to 100.00, incl	0.20	0.20	0.38	0.50	0.50	0.50	0.78	1.18	1.18	1.18	1.58	0.78
Over 100.00 to 150.00, incl	0.22	0.22	0.38	0.50	0.50	0.50	0.78	1.18	1.18	1.18	2.35	1.60
Over 150.00 to 200.00, incl	--	0.38	0.40	0.62	0.62	0.78	0.78	1.18	--	--	3.12	2.35

3. WIDTH:

Included in Section 2.

4. LENGTH:

4.1 Cold Finished:

No requirements specified.

4.2 Hot Finished:

4.2.1 Hot Sheared:

4.2.1.1 Rounds, Squares, Hexagons, and Octagons: See Table 8.

TABLE 8 - Tolerances, Millimeters, Plus Only; Length Ranges, Millimeters

Specified Diameter or Distance Between Parallel Sides Millimeters	1500		3000		6000		9000		12000	
	to 3000, excl	excl	to 6000, excl	excl	to 9000, excl	excl	to 12000, excl	excl	to 18000, excl	excl
Up to 25.00, incl	12.50		18.75		31.25		43.75		56.25	
Over 25.00 to 50.00, incl	15.60		25.00		17.50		50.00		62.50	
Over 50.00 to 125.00, incl	25.00		37.50		43.75		56.25		68.75	
Over 125.00 to 240.00, incl	50.00		67.50		68.75		75.00		81.25	

4.2.1.2 Round-Edged and Square-Edged Flats: See Table 9.

TABLE 9 - Tolerances, Millimeters, Plus Only; Length Ranges, Millimeters

Specified Dimensions Millimeters Width	Specified Dimensions Millimeters Thickness	1500		3000		6000		9000		12000	
		to 3000, excl	excl	to 6000, excl	excl	to 9000, excl	excl	to 12000, excl	excl	to 18000, excl	excl
Up to 75.00	Up to 25.00, incl Over 25.00	12.50 15.60		19.00 25.00		31.75 37.50		43.25 50.00		56.25 62.50	
Over 75.00 to 150.00, incl	Up to 25.00, incl Over 25.00	15.60 25.00		25.00 37.50		37.50 43.25		50.00 56.25		56.25 68.75	
Over 150.00 to 200.00, incl	Up to 25.00, incl Over 25.00 to 75.00, incl	19.00 31.25		31.75 43.75		43.25 50.00		87.50 87.50		100.00 100.00	

4.2.2 Hot Sawn:

4.2.2.1 Rounds, Squares, Hexagons, and Octagons: See Table 10.

TABLE 10 - Tolerances, Millimeters, Plus Only; Length Ranges, Millimeters

Specified Diameter or Distance Between Parallel Sides Millimeters	3000	6000	9000	12000
	to 6000, excl	to 9000, excl	to 12000, excl	to 18000, excl
50.00 to 125.00, incl	37.50	43.75	56.25	68.75
Over 125.00 to 240.00, incl	62.50	68.75	75.00	81.25

4.2.2.2 Round-Edged and Square-Edged Flats: See Table 11.

TABLE 11 - Tolerances, Millimeters, Plus Only; Length Ranges, Millimeters

Specified Dimensions Millimeters Width	Specified Dimensions Millimeters Thickness	3000	6000	9000	12000
		to 6000, excl	to 9000, excl	to 12000, excl	to 18000, excl
75.00 and over	25.00 and over	37.50	42.75	56.25	68.75

4.2.3 Special Straightened and Machine Cut on Both Ends: See Table 12.

TABLE 12 - Tolerances, Millimeters; Length Ranges, Millimeters

Specified Diameter of Rounds, Thickness of Hexagons and Squares, Width of Flats, Millimeters	Up to 3000	Up to 3000	Over	Over
	incl Plus	incl Minus	3000 to 7500 Plus	3000 to 7500 Minus
Up to 75.00, incl	4.70	1.55	6.25	1.55
Over 75.00 to 150.00, incl	6.25	1.55	9.40	1.55
Over 150.00 to 200.00, incl	9.40	1.55	12.50	1.55
Over 200.00 to 240.00, incl	12.50	1.55	15.60	1.55