

**AEROSPACE  
MATERIAL  
SPECIFICATION**

**MAM 2251C**

Issued JAN 1983  
Reaffirmed SEP 1998  
Noncurrent MAR 2003  
Cancelled JUN 2007

Superseded by AMS 2251

Tolerances, Metric  
Low-Alloy Steel Bars

**RATIONALE**

MAM 2251B has been designated cancelled and superseded because AMS 2251 provides equivalent technical requirements.

**CANCELLATION NOTICE**

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of June, 2007, and has been superseded by AMS 2251. The requirements of the latest issue of AMS 2251 shall be fulfilled whenever reference is made to the cancelled MAM 2251B. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications noting that it is superseded by AMS 2251.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full text of mam2251C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
SAE WEB ADDRESS: <http://www.sae.org>

SAENORM.COM : Click to view the full PDF of mam2251c

**AEROSPACE  
MATERIAL  
SPECIFICATION**

Issued JAN 1983  
Reaffirmed SEP 1998  
Noncurrent MAR 2003

Superseding MAM 2251A

Tolerances, Metric  
Low-Alloy Steel Bars

**NONCURRENCY NOTICE**

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of March, 2003. It is recommended, therefore, that this specification not be specified for new designs.

AMS 2251 covers the same requirements.

"NONCURRENT" refers to those materials which have been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs.

"NONCURRENT" specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of MAM2251C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 Society of Automotive Engineers, Inc.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [custsvc@sae.org](mailto:custsvc@sae.org)  
**SAE WEB ADDRESS:** <http://www.sae.org>

## 1. SCOPE:

This specification covers established metric manufacturing tolerances applicable to low-alloy steel bars ordered to metric dimensions. These tolerances apply to all conditions, unless otherwise noted. The term "exclusive" is used to apply to the higher figure of the specified range.

1.1 No clear cut demarcation is available to differentiate between bar and wire products, so no definitions of these products are included.

1.2 AMS 2251 is the inch/pound version of this MAM.

## 2. DIAMETER OR THICKNESS:

### 2.1 Cold Finished:

2.1.1 Cold Drawn: Table 1 includes tolerances for bars that have been annealed, spheroidize annealed, normalized, normalized and tempered, or quenched and tempered before cold finishing. This table does not include tolerances for bars that are spheroidize annealed, normalized, normalized and tempered, or quenched and tempered after cold finishing.

2.1.1.1 Width governs the tolerances for both width and thickness of flats. For example, when the maximum of carbon range is up to 0.28, inclusive, for a flat 50.00 millimeters wide and 25.00 millimeters thick, the width tolerance is 0.15 millimeter and the thickness tolerance is the same, namely, 0.15 millimeter.

SAENORM.COM : Click to view the full PDF of mam2251c

TABLE 1 - Tolerances, Millimeter, Minus Only; Maximum of Carbon Range, %

Specified Diameter or Thickness Millimeters	Up to 0.28 Carbon, incl	Over 0.28 to 0.55 Carbon, incl	Up to 0.55 Carbon, incl, Stress Relieved or Annealed After Cold Finishing	Over 0.55, Carbon, With or Without Stress Relieving or Annealing After Cold Finishing, and All Carbons Quenched and Tempered or Normalized and Tempered Before Cold Finishing
ROUNDS				
Up to 25.00, incl, in coils	0.05	0.08	0.10	0.12
Up to 37.50, incl	0.08	0.10	0.15	0.18
Over 37.50 to 62.50, incl	0.10	0.12	0.15	0.18
Over 62.50 to 100.00, incl	0.12	0.15	0.18	0.20
HEXAGONS				
Up to 18.75, incl	0.08	0.10	0.12	0.18
Over 18.75 to 37.50, incl	0.10	0.12	0.15	0.20
Over 37.50 to 62.50, incl	0.12	0.15	0.18	0.22
Over 62.50 to 78.00, incl	0.15	0.18	0.20	0.25
Over 78.00 to 100.00, incl	0.15	-	-	-
SQUARES				
Up to 18.75, incl	0.08	0.12	0.15	0.20
Over 18.75 to 37.50, incl	0.10	0.15	0.18	0.22
Over 37.50 to 62.50, incl	0.12	0.18	0.20	0.25
Over 62.50 to 100.00, incl	0.18	0.22	0.25	0.30
Over 100.00 to 125.00, incl	0.28	-	-	-
FLATS				
Specified Width, Millimeters				
Up to 18.75, incl	0.10	0.12	0.18	0.22
Over 18.75 to 37.50, incl	0.12	0.15	0.22	0.28
Over 37.50 to 75.00, incl	0.15	0.18	0.28	0.32
Over 75.00 to 100.00, incl	0.18	0.22	0.30	0.42
Over 100.00 to 150.00, incl	0.22	0.28	0.32	0.52
Over 150.00	0.35	-	-	-

- 2.1.1.2 When rough turned round bars are permitted, the tolerances of Table 1 shall be doubled.
- 2.1.1.3 The tolerances for flats apply to both width and thickness.
- 2.1.1.4 Tolerances in the column headed "Over 0.28 to 0.55 carbon, inclusive" also apply to all carbons up to 0.55 maximum, annealed or normalized before cold finishing.
- 2.1.2 Machined Bars: Tolerances for machined bars 9.50 millimeters and over in specified diameter or thickness are shown in Table 2. Bars up to 9.50 millimeters, exclusive, in specified diameter or thickness are supplied centerless ground.

TABLE 2 - Tolerances, Machined Bars

Specified Diameter or Thickness Millimeters	Tolerance plus only Millimeter	Out of Round Millimeter
9.50 to 50.00, excl	0.40	0.20
50.00 to 75.00, incl	0.80	0.40
Over 75.00	0.80	0.40

- 2.1.3 Centerless Ground Bars: Tolerances for centerless-ground bars 3.00 to 105.00 millimeters, inclusive, in specified diameter are shown in Table 3. Bars over 105.00 millimeters in specified diameter are supplied machined.

TABLE 3 - Tolerances, Centerless-Ground Bars

Specified Diameter Millimeters	Tolerance plus or minus Millimeter	Out of Round Millimeter
3.00 to 6.25, excl	0.025	0.025
6.25 to 15.75, excl	0.04	0.04
15.75 to 78.00, excl	0.05	0.05
78.00 to 105.00, incl	0.08	0.08

- 2.1.4 Ground and Polished Rounds: See Table 4.

TABLE 4 - Tolerances, Ground and Polished Rounds

Specified Diameter Millimeters	Tolerance Millimeter Minus only
Up to 37.50, incl	0.02
Over 37.50 to 62.50, excl	0.038
62.50 to 75.00, incl	0.05
Over 75.00 to 100.00, incl	0.08

## 2.2 Hot Finished:

## 2.2.1 Rounds and Squares: See Table 5.

2.2.1.1 Out-of-round is the difference between the maximum and minimum diameters of the bar, measured at the same cross-section. Out-of-square is the difference in the two dimensions at the same cross-section of a square bar between opposite faces.

TABLE 5 - Tolerances, Hot Finished Rounds and Squares

Specified Diameter or Thickness Millimeters	Tolerance Millimeters Plus	Tolerance Millimeter Minus	Out-of-Round or Out-of-Square Millimeters
Up to 7.80, incl	0.12	0.12	0.20
Over 7.80 to 11.00, incl	0.15	0.15	0.23
Over 11.00 to 15.50, incl	0.18	0.18	0.25
Over 15.50 to 22.00, incl	0.20	0.20	0.30
Over 22.00 to 25.00, incl	0.22	0.22	0.32
Over 25.00 to 28.00, incl	0.25	0.25	0.38
Over 28.00 to 31.25, incl	0.28	0.28	0.41
Over 31.25 to 34.50, incl	0.30	0.30	0.45
Over 34.50 to 37.50, incl	0.35	0.35	0.57
Over 37.50 to 50.00, incl	0.40	0.40	0.58
Over 50.00 to 62.50, incl	0.78	0	0.58
Over 62.50 to 87.50, incl	1.18	0	0.88
Over 87.50 to 115.00, incl	1.58	0	1.15
Over 115.00 to 137.50, incl	1.95	0	1.47
Over 137.50 to 165.00, incl	3.12	0	1.75
Over 165.00 to 205.00, incl	3.90	0	2.12
Over 205.00 to 235.00, incl	4.70	0	2.50
Over 235.00 to 250.00, incl	6.25	0	3.00

## 2.2.2 Hexagons and Octagons: See Table 6.

TABLE 6 - Tolerances, Hot Finished Hexagons and Octagons

Specified Distance Between Parallel Sides Millimeters	Tolerance Millimeters Plus	Tolerance Millimeters Minus	Maximum Difference, Millimeters, 3 Measurements, For Hexagons Only
Up to 12.50, incl	0.18	0.18	0.28
Over 12.50 to 25.00, incl	0.25	0.25	0.38
Over 25.00 to 37.50, incl	0.52	0.32	0.62
Over 37.50 to 50.00, incl	0.78	0.40	0.78
Over 50.00 to 62.50, incl	1.18	0.40	1.18
Over 62.50 to 87.50, incl	1.58	0.40	1.58

## 2.2.3 Square-Edged and Round-Edged Flats: See Table 7.

2.2.3.1 Flats over 150 to 200 millimeters, inclusive, in specified width are not available as hot rolled alloy steel bars in thicknesses under 5.75 millimeters.

2.2.3.2 Tolerances shall be negotiated for flats over 150 to 200 millimeters, inclusive, in specified width and over 75.00 millimeters in specified thickness.

TABLE 7 - Thickness Tolerances, Inch, Plus and Minus; Thickness Ranges, Millimeters

Specified Width Millimeters	5.00 to 5.75, excl	5.75 to 6.25, excl	6.25 to 12.50, incl	Over	Over	Over	Over 75.00	Width Tolerance Millimeters Plus	Width Tolerance Millimeters Minus
				12.50 to 25.00, incl	25.00 to 50.00, incl	50.00 to 75.00, incl			
Up to 25.00, incl	0.18	0.18	0.20	0.25	-	-	-	0.40	0.40
Over 25.00 to 50.00, incl	0.18	0.18	0.30	0.38	0.78	-	-	0.78	0.78
Over 50.00 to 100.00, incl	0.20	0.20	0.38	0.50	0.78	1.18	1.18	1.58	0.78
Over 100.00 to 150.00, incl	0.22	0.22	0.38	0.50	0.78	1.18	1.18	2.35	1.60
Over 150.00 to 200.00, incl	-	0.38	0.40	0.62	0.78	1.18	-	3.12	2.35

## 3. WIDTH:

Included in Section 2.

## 4. LENGTH:

## 4.1 Cold Finished:

No requirements specified.

## 4.2 Hot Finished:

## 4.2.1 Hot Sheared:

## 4.2.1.1 Rounds, Squares, Hexagons, and Octagons: See Table 8.

TABLE 8 - Tolerances, Millimeters, Plus Only; Length Ranges, Millimeters

Specified Diameter or Distance Between Parallel Sides Millimeters	1500	3000	6000	9000	12000
	to 3000, excl	to 6000, excl	to 9000, excl	to 12000, excl	to 18000, excl
Up to 25.00, incl	12.50	18.75	31.25	43.75	56.25
Over 25.00 to 50.00, incl	15.60	25.00	17.50	50.00	62.50
Over 50.00 to 125.00, incl	25.00	37.50	43.75	56.25	68.75
Over 125.00 to 240.00, incl	50.00	67.50	68.75	75.00	81.25

## 4.2.1.2 Round-Edged and Square-Edged Flats: See Table 9.

TABLE 9 - Tolerances, Millimeters Plus Only; Length Ranges, Millimeters

Specified Dimensions Millimeters Width	Specified Dimensions Millimeters Thickness	1500	3000	6000	9000	12000
		to 3000, excl	to 6000, excl	to 9000, excl	to 12000, excl	to 18000, excl
Up to 75.00,	Up to 25.00, incl	12.50	19.00	31.75	43.25	56.25
	Over 25.00	15.60	25.00	37.50	50.00	62.50
Over 75.00 to 150.00, incl	Up to 25.00, incl	15.60	25.00	37.50	50.00	56.25
	Over 25.00	25.00	37.50	43.25	56.25	68.75
Over 150.00 to 200.00, incl	Up to 25.00, incl	19.00	31.75	43.25	87.50	100.00
	Over 25.00 to 75.00, incl	31.25	43.75	50.00	87.50	100.00