

AEROSPACE MATERIAL SPECIFICATION



MAM 5822A

Issued JAN 1993
Revised JUN 2000

Superseding MAM 5822

Steel, Corrosion and Heat Resistant, Welding Wire
11.8Cr - 2.8Ni - 1.6Co - 1.8Mo - 0.32V
Vacuum Induction Melted

UNS S41780

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant steel in the form of welding wire.

1.1.1 AMS 5822 is the inch/pound version of this MAM.

1.2 Application:

This product has been used typically as bare filler metal for gas-metal-arc or gas-tungsten-arc welding of steels of similar composition, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order form a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2813	Packaging and Marking of Packaging of Welding Wire, Standard Method
AMS 2814	Packaging and Marking of Packaging of Welding Wire, Premium Quality

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 (Continued):

AMS 2816 Identification, Welding Wire, Tab Marking Method
 AMS 2819 Identification, Welding Wire, Direct Color Code System

ARP1876 Weldability Test for Weld Filler Metal Wire
 ARP4926 Alloy Verification and Chemical Analysis Inspection of Welding Wire

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Wire shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon (3.1.3)	0.10	0.15
Manganese	0.40	1.30
Silicon	--	0.40
Phosphorus	--	0.010
Sulfur	--	0.008
Chromium	11.00	12.50
Nickel	2.50	3.00
Cobalt	1.30	2.00
Molybdenum	1.50	2.00
Vanadium	0.25	0.40
Copper	--	0.75
Oxygen (3.1.3)	--	0.005 (50 ppm)
Nitrogen (3.1.3)	--	0.040 (400 ppm)
Hydrogen (3.1.3)	--	0.001 (10 ppm)

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248. No variation over maximum is permitted for oxygen, nitrogen, and hydrogen.

3.1.2 Chemical analysis of initial ingot, bar, or rod stock before drawing, other than those analyses required to be done on the finished wire, is acceptable provided the processes used for drawing or rolling, annealing, and cleaning, are controlled to ensure continued conformance to chemical composition requirements.

3.1.3 Shall be determined on finished wire.

3.2 Melt Practice:

Steel shall be vacuum induction melted; it may be remelted using consumable electrode vacuum process, but remelting is not required.

3.3 Condition:

Cold worked, bright finish, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.4 Fabrication:

3.4.1 Wire shall be formed from rod or bar descaled by a process which does not affect the composition of the wire. Surface irregularities inherent with a forming process that does not tear the wire surfaces are acceptable provided the wire conforms to the tolerances of 3.7.

3.4.2 Butt welding is permissible provided both ends to be joined are alloy verified using a method capable of distinguishing the alloy from all other alloys processed in the facility, or the repair is made at the wire processing station. The butt weld shall not interfere with uniform, uninterrupted feeding of the wire in machine welding.

3.4.3 In-process annealing, if required, between cold rolling or drawing operations, shall be performed in vacuum or protective atmospheres to ensure freedom from surface oxidation and absorption of other extraneous elements.

3.4.4 Residual elements, drawing compounds, oxides, dirt, oil, dissolved gasses and other foreign materials picked up during wire processing that can adversely affect the welding characteristics, the operation of the equipment, or the properties of the weld metal, shall be removed by cleaning processes that will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.5 Properties:

Wire shall conform to the following requirements:

3.5.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.5.2 Spooled Wire: Shall conform to 3.5.2.1 and 3.5.2.2.

3.5.2.1 Cast: Wire, wound on standard 300-mm diameter spools, shall have imparted to it a curvature such that a specimen, sufficient in length to form one loop with a 25 mm overlap, when cut from the spool and laid on a flat surface, shall form a circle 380 to 1270 mm in diameter.

3.5.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 25 mm.

3.6 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.7 Sizes and Tolerances:

Wire shall be supplied in the following sizes and to the tolerances shown in 3.7.1 and 3.7.2.

3.7.1 Diameter: Shall be as shown in Table 2.

TABLE 2 - Wire Sizes and Tolerances

Form	Nominal Diameter Millimeters	Tolerance	Tolerance
		Millimeter Plus	Millimeter Minus
Cut Lengths	0.8, 1.0, 1.2	0.03	0.03
Cut Lengths	1.6, 2.4, 3.2, 4.0, 4.8	0.05	0.05
Spools	0.3	0.01	0.01
Spools	0.5, 0.8, 1.0, 1.2	0.03	0.03
Spools	1.6, 2.0, 2.4	0.05	0.05

3.7.2 Length: Cut lengths shall be furnished in 500, 750, or 900 mm lengths, as ordered, and shall not vary more than +0, -10 mm from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), sizes and tolerances (3.7), and alloy verification (5.2.1) are acceptance tests and shall be performed on each heat or lot as applicable.