

**AEROSPACE
MATERIAL
SPECIFICATION**



MAM 6415C

Issued JAN 1989
Revised MAR 1998
Cancelled MAR 2003

Superseding MAM 6415B

Steel, Bars, Forgings, and Tubing
0.80Cr - 1.8Ni - 0.25Mo (0.38 - 0.43C) (SAE 4340)

G43406

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of March, 2003. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications.

AMS 6415 covers the same material.

"CANCELLED" specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of MAM 6415C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 Society of Automotive Engineers, Inc.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

1. SCOPE:

1.1 Form:

This specification covers an aircraft-quality, low-alloy steel in the form of bars, forgings, mechanical tubing, and forging stock procured in SI (Metric) units.

1.1.1 AMS 6415 is the inch/pound version of this MAM.

1.2 Application:

These products have been used typically for parts, 90 millimeters and under in nominal thickness at time of heat treatment, requiring a through-hardening steel capable of developing a minimum hardness of 40 HRC when properly hardened and tempered and also for parts of greater thickness but requiring proportionately lower hardness, but usage is not limited to such applications.

1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking after heat treatment; ARP1110 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

MAM 2251	Tolerances, Metric, Low-Alloy Steel Bars
MAM 2253	Tolerances, Metric, Carbon and Alloy Steel Tubing
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
MAM 2301	Cleanliness, Aircraft-Quality Steel, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS 2372	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
AMS 2808	Identification, Forgings
AS1182	Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing
ARP1110	Minimizing Stress Corrosion Cracking in Wrought Forms of Steels and Corrosion Resistant Steels and Alloys

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 255 End-Quench Test for Hardenability of Steel

ASTM A 370 Mechanical Testing of Steel Products

ASTM E 112 Determining the Average Grain Size

ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

ASTM E 381 Macroetch Testing Steel, Bars, Billets, Blooms, and Forgings

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-H-6875 Heat Treatment of Steel, Process for

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.38	0.43
Manganese	0.65	0.85
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.70	0.90
Nickel	1.65	2.00
Molybdenum	0.20	0.30
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370.

3.2.1 Bars:

3.2.1.1 Bars 12.50 Millimeters and Under in Nominal Diameter or Distance Between Parallel Sides: Cold finished having tensile strength not higher than 862 MPa or hardness not higher than 27 HRC, or equivalent (See 8.2).

3.2.1.2 Bars Over 12.50 Millimeters in Nominal Diameter or Distance Between Parallel Sides: Hot finished and annealed, unless otherwise ordered, having hardness not higher than 235 HB, or equivalent (See 8.2). Bars ordered cold finished may have hardness as high as 255 HB, or equivalent.

3.2.2 Forgings: Normalized and tempered in accordance with MIL-H-6875 to a hardness not higher than 269 HB, or equivalent (See 8.2).

3.2.3 Mechanical Tubing: Cold finished, unless otherwise ordered, having hardness not higher than 25 HRC, or equivalent (See 8.2). Tubing ordered hot finished and annealed shall have hardness not higher than 99 HRB, or equivalent.

3.2.4 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties:

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

3.3.1 Macrostructure: Visual examination of transverse full cross-sections from bars, billets, tube rounds, or forging stock, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E 381 shown in Table 2.

TABLE 2 - Macrostructure Limits

Cross-Sectional Area	
Square Centimeters	Macrographs
Up to 230, incl	S2 - R1 - C2
Over 230 to 645, incl	S2 - R2 - C3

3.3.2 Average Grain Size: Shall be ASTM 5 or finer, determined in accordance with ASTM E 112.

3.3.3 Hardenability: Shall be J 19mm = 53 HRC, minimum, and J 32 mm = 50 HRC, minimum, (See 8.3), determined on the standard end-quench test specimen in accordance with ASTM A 255 except that the steel shall be normalized at $870\text{ }^{\circ}\text{C} \pm 15$ and the test specimen austenitized at $845\text{ }^{\circ}\text{C} \pm 15$.

3.3.4 Decarburization:

- 3.3.4.1 Bars and tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.
- 3.3.4.2 Allowable decarburization of bars, billets, and tube rounds ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.
- 3.3.4.3 Decarburization of bars to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table 3.

TABLE 3 - Maximum Decarburization

Nominal Diameter or Distance Between Parallel Sides Millimeters		Depth of Decarburization Millimeters
Up to	9.50, incl	0.25
Over	9.50 to 12.50, incl	0.30
Over	12.50 to 15.65, incl	0.35
Over	15.65 to 25.00, incl	0.40
Over	25.00 to 37.50, incl	0.50
Over	37.50 to 50.00, incl	0.60
Over	50.00 to 62.50, incl	0.75
Over	62.50 to 75.00, incl	0.90
Over	75.00 to 100.00, incl	1.15

- 3.3.4.4 Decarburization of tubing to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table 4.

TABLE 4 - Maximum Decarburization

Nominal Wall Thickness Millimeters	Depth ID Millimeter	Depth OD Millimeter
Up to 2.75, incl	0.20	0.35
Over 2.75 to 5.00, incl	0.25	0.50
Over 5.00 to 10.00, incl	0.30	0.60
Over 10.00 to 15.00, incl	0.35	0.75
Over 15.00 to 25.00, incl	0.40	0.90
Over 25.00	0.50	1.00

3.3.4.5 Decarburization shall be measured by the microscopic method or by HR30N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by decarburization thereon.

3.3.4.5.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.13 millimeter and the width is 1.65 millimeters or less.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Steel shall be aircraft-quality conforming to MAM 2301.

3.4.2 Bars and mechanical tubing ordered hot rolled or cold drawn, or ground, turned, or polished, shall after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

3.4.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.5 Tolerances:

Shall be as follows:

3.5.1 Bars: In accordance with MAM 2251.

3.5.2 Mechanical Tubing: In accordance with MAM 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), condition (3.2), macrostructure (3.3.1), average grain size (3.3.2), hardenability (3.3.3), decarburization (3.3.4), frequency-severity cleanliness rating (3.4.1), and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Grain flow of die forgings (3.4.3) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 Bars, Mechanical Tubing, and Forging Stock: In accordance with AMS 2370.

4.3.2 Forgings: In accordance with AMS 2372.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition, macrostructure, average grain size, hardenability, and frequency-severity cleanliness rating of each heat or lot, as applicable, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, MAM 6415B, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.5 Resampling and Retesting:

Shall be as follows:

4.5.1 Bars, Mechanical Tubing, and Forging Stock: In accordance with AMS 2370.

4.5.2 Forgings: In accordance with AMS 2372.