

GRAIN FLOW PATTERN FOR BOLTS AND SCREWS

1. SCOPE:

This specification covers the grain flow pattern requirements in headed bolts and screws. The heading practice in the manufacture of the bolt or screw sets the grain flow pattern, but it is also greatly influenced by the fastener design.

2. TEST PROCEDURE:

- 2.1 Testing for grain flow shall be done after heading, prior to heat treatment and subsequent processing of parts.
- 2.2 The head and shank shall be sectioned approximately on the centerline, with the shank having a minimum length of 1.0 X the diameter of the shank.
- 2.3 Macroetch the sectioned head and shank sufficient to reveal the grain flow pattern, using etching practice based upon ASTM E340, and shown in the manufacturer's control plan. Grain flow samples shall be viewed at sufficient magnification to allow for adequate resolution of the grain flow lines.
- 2.4 The sample size and frequency for the above testing shall be identified in the manufacturer's control plan.

3. GRAIN FLOW PATTERN REQUIREMENTS:

- 3.1 Grain flow throughout the product shall be continuous and uninterrupted except in those instances where a flash trim line has been determined to be acceptable. A continuous and uninterrupted grain flow must be maintained around the fillets and radii, but may be compressed. Grain flow lines terminating in head to shank fillets, radii, or onto the shank surface are not acceptable. In upset parts, the entire material compression zone in the head shall be above the head to shank radius.

The research data, analysis, conclusion, opinions and other contents of this document are solely the product of the authors. Neither the Society of Automotive Engineers, Inc. (SAE) nor the United States Council for Automotive Research (USCAR) certifies the compliance of any products with the requirements of nor makes any representations as to the accuracy of the contents of this document nor to its applicability for purpose. It is the sole responsibility of the user of this document to determine whether or not it is applicable for their purposes.

3.2 Figure #1 shows the acceptable grain flow pattern typical in flange heads and Figure #2 shows the unacceptable grain flow pattern typical in flange heads for comparison.

4. REVERIFICATION:

Changes in design or processing that effect grain flow pattern require reverification.

5. REFERENCES:

ASTM E340

6. KEY WORDS:

End Grain, Compression Zone, Grain Flow.

SAENORM.COM : Click to view the full PDF of uscar8

PREPARED BY THE USCAR FASTENER TECHNICAL COMMITTEE




FIGURE 1 - Acceptable Grain Flow Pattern