



UL 1072

STANDARD FOR SAFETY

Medium-Voltage Power Cables

[ULNORM.COM](https://www.ulnorm.com) : Click to view the full PDF of UL 1072 2020

[ULNORM.COM](https://www.ulnorm.com) : Click to view the full PDF of UL 1072 2020

UL Standard for Safety for Medium-Voltage Power Cables, UL 1072

Fourth Edition, Dated June 30, 2006

SUMMARY OF TOPICS

This revision of ANSI/UL 1072 dated April 13, 2020 includes a correction to [Table 18.1](#), Construction of metal component of insulation shielding.

Text that has been changed in any manner or impacted by UL's electronic publishing system is marked with a vertical line in the margin.

The requirements are substantially in accordance with Proposal(s) on this subject dated January 17, 2020.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form by any means, electronic, mechanical photocopying, recording, or otherwise without prior permission of UL.

UL provides this Standard "as is" without warranty of any kind, either expressed or implied, including but not limited to, the implied warranties of merchantability or fitness for any purpose.

In no event will UL be liable for any special, incidental, consequential, indirect or similar damages, including loss of profits, lost savings, loss of data, or any other damages arising out of the use of or the inability to use this Standard, even if UL or an authorized UL representative has been advised of the possibility of such damage. In no event shall UL's liability for any damage ever exceed the price paid for this Standard, regardless of the form of the claim.

Users of the electronic versions of UL's Standards for Safety agree to defend, indemnify, and hold UL harmless from and against any loss, expense, liability, damage, claim, or judgment (including reasonable attorney's fees) resulting from any error or deviation introduced while purchaser is storing an electronic Standard on the purchaser's computer system.

No Text on This Page

[ULNORM.COM](https://www.ulnorm.com) : Click to view the full PDF of UL 1072 2020

JUNE 30, 2006
(Title Page Reprinted: April 13, 2020)



ANSI/UL 1072-2020

1

UL 1072

Standard for Medium-Voltage Power Cables

First Edition – August, 1986
Second Edition – May, 1995
Third Edition – December, 2001

Fourth Edition

June 30, 2006

This ANSI/UL Standard for Safety consists of the Fourth Edition including revisions through April 13, 2020.

The most recent designation of ANSI/UL 1072 as an American National Standard (ANSI) occurred on March 12, 2020. ANSI approval for a standard does not include the Cover Page, Transmittal Pages, and Title Page.

Comments or proposals for revisions on any part of the Standard may be submitted to UL at any time. Proposals should be submitted via a Proposal Request in UL's On-Line Collaborative Standards Development System (CSDS) at <https://csds.ul.com>.

UL's Standards for Safety are copyrighted by UL. Neither a printed nor electronic copy of a Standard should be altered in any way. All of UL's Standards and all copyrights, ownerships, and rights regarding those Standards shall remain the sole and exclusive property of UL.

COPYRIGHT © 2020 UNDERWRITERS LABORATORIES INC.

No Text on This Page

ULNORM.COM : Click to view the full PDF of UL 1072 2020

CONTENTS**INTRODUCTION**

1	Scope	7
2	Units of Measurement	12
3	References.....	12

CONSTRUCTION

4	Materials	12
5	General.....	12

CONDUCTOR(S)

6	Materials	12
7	Resistance	12
8	Conductor Diameter	13
9	Stranding	13
10	Strand Filler.....	15
11	Metal Coating.....	15
12	Joints	15

CONDUCTOR STRESS RELIEF (CONDUCTOR SHIELDING)

13	Details.....	16
----	--------------	----

INSULATION

14	Material, Application, and Centering	17
15	Thicknesses	23

INSULATION SHIELDING

16	General.....	26
17	Conductive Nonmetallic Covering.....	26
18	Nonmagnetic Metal Component.....	29

JACKET ON INDIVIDUAL CIRCUIT CONDUCTORS FOR MULTIPLE-CONDUCTOR CABLE

19	Details.....	30
----	--------------	----

OPTICAL-FIBER MEMBER(S)

20	Construction	32
----	--------------------	----

ASSEMBLY OF MULTIPLE-CONDUCTOR CABLE

21	Optical-Fiber Member(s).....	32
22	Circuit Conductors.....	32
23	Grounding Conductor	33
24	Fillers	37
25	Assembly Covering	37

OVERALL COVERING(S)

26	General	38
27	Jacket	40
28	Metal Covering.....	49
29	Supplementary Jacket over Metal Covering.....	53

PERFORMANCE

30	Test or Examination for Integrity and Continuity of Non-conductive Jacket Over Insulation Shielding or Over a Metal Sheath or Armor	54
31	Physical Properties Tests	57
32	Corrosion of Uncoated Copper Conductors	57
33	Adhesion (Stripping-Tension) Test of Extruded Insulation Shielding.....	57
34	Deformation Test of EPCV or XLPE Insulation	58
35	Deformation Test of Non-conductive Thermoplastic Jackets	59
36	Set of Non-conductive Thermoset Jackets	61
37	Heat Shock Test of Non-conductive PVC and TPE Jackets.....	62
38	Cold Bend Test of Complete Cable	62
39	Cold-Impact Test	63
40	Accelerated Water Absorption – Electrical Method – Tests of DREP, EP, and XLPE Insulations	63
41	Room-Temperature Relative Permittivity and Power Factor Tests at Rated Voltage for EP, DREP, and XLPE Insulations on 8 – 35-kV Circuit Conductors.....	65
42	Dry Electrical Test	66
43	Environmental Cracking Test of Non-conductive PE Jacket	67
44	Volume Resistivity of Conductive Conductor Shielding	68
45	Relative Permittivity and Dielectric Withstand Stress of Extruded Nonconducting Conductor Stress Control	69
46	Volume Resistivity of Insulation Shielding.....	70
47	Specific Surface Resistivity of Nonshielded Single-Conductor Cable.....	71
48	Alternative Tests for Resistance to Tracking of Nonshielded Dry-Locations 2400 V Single-Conductor Cable Insulated with EPCV or XLPE	72
49	U-Bend Discharge Test of Nonshielded Single-Conductor Cable.....	74
50	Copper Sulphate Test of Zinc Coating on Steel Strip for and from Steel Armor	75
51	Weight of Zinc Coating on Steel Strip for Steel Armor.....	76
52	Tension Test of Interlocked Armor.....	78
53	Flexibility Test for Cable Having Interlocked Armor or a Smooth or Corrugated Metal Sheath ...	80
54	Tightness of Armor or Metal Sheath.....	81
55	Partial Discharge (Corona) Level of Each Circuit Conductor Having Insulation Shielding	83
	55.1 Requirement.....	83
	55.2 Definitions	83
	55.3 Test apparatus	83
	55.4 Calibration of test equipment.....	84
	55.5 Items to be tested.....	85
	55.6 Test procedure	85
56	A-C Dielectric Withstand Test of Each Conductor Having Insulation Shielding.....	85
57	A-C Dielectric Withstand Test of Each Nonshielded Conductor	86
58	Partial Discharge (Corona) Resistance of DREP Insulation	87
	58.1 Requirement.....	87
	58.2 Method and apparatus.....	87
59	Insulation Resistance of Each Conductor Having Insulation Shielding	88
60	Insulation Resistance of Each Nonshielded Conductor.....	89
61	Test Procedure for Determining the Multiplying-Factor Column for Adjusting Insulation Resistance.....	89
62	Vertical-Tray Flame Test	91

63 Limited Smoke Test 92
64 Sunlight Resistance..... 92
65 Hot Creep Tests 92
66 Durability of Ink Printing 96

MARKINGS

67 Intervals 96
68 Color of Circuit Conductor(s) 97
69 Identification of Conductive Nonmetallic Covering Portion of Insulation Shielding 97
70 On or in the Cable 98
71 Responsibility for the Insulated Conductors 100
72 On the Tag, Reel, or Carton..... 101
73 Marking of Direct-Burial Cable..... 102
74 Date of Manufacture 102

ULNORM.COM : Click to view the full PDF of UL 1072 2020

No Text on This Page

ULNORM.COM : Click to view the full PDF of UL 1072 2020

INTRODUCTION

1 Scope

1.1 These requirements cover the shielded and nonshielded medium-voltage power cables that are described in [Table 1.1](#) (single-conductor) and [Table 1.2](#) (multiple-conductor). Multiple-conductor cables may include one or more individually jacketed non-conductive optical-fiber members. These electrical and hybrid electrical and optical-fiber cables are for use (optical and electrical functions associated in the case of a hybrid cable) in accordance with Article 328 and other applicable parts of the National Electrical Code (NEC), ANSI/NFPA 70.

1.2 These cables have one or more stranded copper or aluminum conductors that are insulated with a solid, extruded dielectric. Cables that have a metal sheath or interlocked armor incorporate an effective grounding path. A grounding conductor is optional in other cables. Cables for direct burial are so marked and have an overall covering (see [1.4](#) for direct-burial cables that are not covered). Cables that are for use in cable trays generally are so marked (see [62.1](#) and [62.2](#)). Cables that are sunlight-resistant generally are so marked (see [64.1](#) – [64.3](#)). Cables that are marked “MV-90” or “MV-90 dry” have a maximum operating temperature of 90°C (194°F). Cables that are marked “MV-105” have a maximum operating temperature of 105°C (221°F) for use where design conditions require a maximum conductor temperature above 90°C (194°F). Cables that are marked “dry” have insulation for use only in dry locations. All other cables have insulation that is for use in both wet and dry locations. Multiple-conductor cables that include one or more optical-fiber members are surface marked to so indicate. Cables that are marked “oil resistant II” are for exposure to mineral oil at temperatures not in excess of 75°C (167°F). Cables that are marked “oil resistant I” are for exposure to mineral oil at temperatures not in excess of 60°C (140°F).

1.3 A multiple-conductor Type MV cable that has a smooth (other than lead) or corrugated metal sheath or that has interlocked metal armor may be marked for use also as Type MC cable.

1.4 This standard does not include requirements for cables with concentric neutral conductors. However, it is possible to have a single-conductor cable with a concentric neutral conductor manufactured in accordance with the requirements of other standards, that meets the requirements for jacketed single-conductor shielded cable in this standard.

ULNORM.COM : Click to view the full PDF of UL 1072-2020

Table 1.1
Single-conductor Type MV cables

Voltage rating	Size	Use	Insulation material	Percent insulation level	Insulation thicknesses	Shield	Overall covering
2400	8 AWG – 1000 kcmil	90°C (194°F) dry	XLPE or EPCV	–	Column A Table 15.3	nonshielded	None
		90°C (194°F) dry	XLPE, EPCV, DREP, or EP	–	Column B Table 15.3	nonshielded	Nonconductive jacket Column B Table 27.20
		90°C (194°F) wet or dry	XLPE, DREP, or EP	–	Column C Table 15.3	nonshielded	Nonconductive jacket Column C Table 27.20
5000	8 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100 or 133	Table 15.1 or Table 15.2	Shielded	a
8000	6 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 or Table 15.2	Shielded	a
15000	2 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 or Table 15.2	Shielded	a
25000	1 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 or Table 15.2	Shielded	a
28000	1 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 or Table 15.2	Shielded	a
35000	1/0 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 or Table 15.2	Shielded	a

^a The overall covering consists of one of the following (see [Table 26.1](#) for complete descriptions):

- 1) Conductive nonmetallic insulation covering ([Table 17.3](#)) as part of shielding, with or without nonmagnetic metal sheath or armor over conductive nonmetallic insulation covering as part of shielding, with or without supplementary non-conductive jacket ([Table 29.1](#)) over metal sheath or armor.
- 2) Non-conductive jacket ([Table 27.18](#)) over shielding, with or without nonmagnetic metal sheath or armor over non-conductive jacket, with or without supplementary non-conductive jacket ([Table 29.1](#)) over metal sheath or armor.
- 3) Nonmagnetic metal sheath or armor as part of shielding, with or without supplementary non-conductive jacket ([Table 29.1](#)) over metal sheath or armor.

**Table 1.2
Multiple-conductor Type MV cables**

Voltage rating	Circuit conductors							Grounding conductor	Overall covering
	Size	Use	Insulation material	Percent insulation level	Insulation thicknesses	Shield	Individual covering		
2400	8 AWG – 1000 kcmil	90°C (194°F) dry	XLPE or EPCV	–	Column A Table 15.3	nonshielded	None	Optional Covered 23.1	None – assembly of single-conductor cables
		90°C (194°F) dry	XLPE, EPCV, DREP, or EP	–	Column B Table 15.3	nonshielded	Non-conductive jacket Column B Table 27.20	Optional Covered 23.1	None – assembly of single-conductor cables
		90°C (194°F) wet or dry	XLPE, DREP, or EP	–	Column C Table 15.3	nonshielded	Non-conductive jacket Column C Table 27.20	Optional Covered Table 23.1	None – assembly of single-conductor cables
		90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	–	Column C Table 15.3	nonshielded	None or Non-conductive jacket (Table 19.1)	Optional Bare 23.5	Non-conductive jacket (Table 27.18)
–					Required Bare 23.1	Interlocked armor with or without Supplementary jacket			
5000	8 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F)	XLPE, DREP, or EP	100	Table 15.1 , Table 15.2	Shielded	Non-conductive jacket (Table 27.18) over shield	Optional Covered 23.1	None
							Conductive nonmetallic insulation covering (Table 17.3) as part of shield	Optional Covered Table 23.1	None

Table 1.2 Continued on Next Page

Table 1.2 Continued

Voltage rating	Circuit conductors							Grounding conductor	Overall covering	
	Size	Use	Insulation material	Percent insulation level	Insulation thicknesses	Shield	Individual covering			
								Optional Covered 23.1	None	
8000	6 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 , Table 15.2	Shielded	Metal sheath as part of shield with or without Supplementary jacket	None or Non-conductive jacket (Table 19.1)	Optional Bare 23.5	Non-conductive jacket (Table 27.18)
									Required Bare 23.1	Interlocked armor with or without Supplementary jacket
15000	2 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 , Table 15.2	Shielded	Metal sheath as part of shield with or without Supplementary jacket	May be required to Bare 23.3 and 23.4	Metal sheath with or without Supplementary jacket	
								Non-conductive jacket (Table 27.18) over shield	Optional Covered 23.1	None
25000	1 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 , Table 15.2	Shielded	Metal sheath as part of shield with or without supplementary jacket	Conductive nonmetallic insulation covering (Table 17.3) as part of shield	Optional Covered 23.1	None
									Optional Covered 23.1	None
28000	1 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 , Table 15.2		None or Non-conductive jacket (Table 19.1)	Optional Bare 23.5	Non-conductive jacket (Table 27.18)	

Table 1.2 Continued on Next Page

Table 1.2 Continued

Voltage rating	Circuit conductors							Grounding conductor	Overall covering
	Size	Use	Insulation material	Percent insulation level	Insulation thicknesses	Shield	Individual covering		
								Required Bare 23.2	Interlocked armor with or without Supplementary jacket
								May be required Bare 23.3 and 23.4	Metal sheath with or without Supplementary jacket
35000	1/0 AWG – 2000 kcmil	90°C (194°F) or 105°C (221°F) wet or dry	XLPE, DREP, or EP	100, 133, or 173	Table 15.1 , Table 15.2	Shielded	Non-conductive jacket (Table 27.18) over shield	Optional Covered Table 23.1	None
							Conductive nonmetallic insulation covering (Table 17.3) as part of shield	Optional Covered 23.1	None
							Metal sheath as part of shield with or without Supplementary jacket	Optional Covered 23.1	None

ULNORM.COM : Click to view the full PDF of UL 1072 2020

2 Units of Measurement

2.1 In addition to being stated in the inch/pound units that are customary in the USA, each numerical requirement in this standard is also stated in units that make the requirement conveniently usable in countries employing the various metric systems (practical SI and customary). Equivalent – although not necessarily exactly identical – results are to be expected from applying a requirement in USA or metric terms. Equipment calibrated in metric units is to be used when a requirement is applied in metric terms.

3 References

3.1 Wherever the designation “UL 1581” is used in this cable standard, reference is to be made to the designated part(s) of the Reference Standard for Electrical Wires, Cables, and Flexible Cords (UL 1581).

3.2 Any undated reference to a code or standard appearing in the requirements of this standard shall be interpreted as referring to the latest edition of that code or standard.

CONSTRUCTION

4 Materials

4.1 Only materials that are acceptable for the particular use shall be used in a cable.

4.2 Each material used in a cable shall be compatible with all of the other materials used in the cable.

5 General

5.1 Medium-voltage cable shall be designated as Type MV and shall comply in all respects with the applicable requirements for construction details, test performance, and markings.

CONDUCTOR(S)

6 Materials

6.1 The conductor(s) in a cable shall be of soft-annealed copper or of semi-annealed (1/2 – 3/4 hard) or hard-drawn aluminum. Soft-annealed copper wires (strands) shall comply with ASTM B 3. A metal coating that is provided on soft-annealed copper in accordance with [9.1](#) or [9.2](#) shall be of tin complying with ASTM B 33. An aluminum conductor shall comply with the Requirements for Aluminum Conductors of an 8000 Series Alloy, Section 10 of UL 1581, or shall be of a 1/2 – 3/4 hard 1350 Series aluminum alloy having either the tensile strength required for a 1350-H19 (extra-hard) aluminum alloy in the American Society for Testing and Materials Standard Specification for Aluminum 1350-H19 Wire for Electrical Purposes, ASTM B 230, or the tensile strength required for a semi-annealed 8000 Series alloy.

6.2 An individual conductor shall not be smaller than 8 AWG (8.367 mm²) and shall not be larger than 2000 kcmil or 113 mm². The nominal cross-sectional area of a conductor is indicated in Table 20.1 of UL 1581.

7 Resistance

7.1 The direct-current resistance of any length of conductor in ohms per thousand conductor feet or in ohms per conductor kilometer shall not be higher than the maximum (nominal x 1.02) resistance indicated in the applicable table in D-C Conductor Resistance, Section 30 of UL 1581, at 20°C (68°F) or at 25°C (77°F) when measured as described in D-C Conductor Resistance, Section 220 of UL 1581, except that the equipment selected shall be accurate to within 0.5 percent of the value read. If, as provided for in [11.2](#),

metal-coated wires are used in only the outer layer of an uncoated copper conductor, the direct-current resistance of the resulting conductor shall not exceed the value tabulated for an uncoated conductor of the same size and construction. See 7.2 for cabling factors applicable to multiple-conductor cables.

7.2 In a finished multiple-conductor cable, the increased resistance of a conductor because of cabling shall not be higher than the applicable value multiplied by the following factor, with the result rounded off to the same number of decimal places as the tabulated value.

a) One layer of conductors: 1.02

b) More than one layer of conductors: 1.03

8 Conductor Diameter

8.1 The nominal, maximum (1.01 x nominal), and minimum (0.98 x nominal) diameters of solid and stranded conductors are shown in Tables 20.1, 20.2, 20.3, 20.3.1, 20.4, and 20.6 of UL 1581. Conductor diameter is to be measured using the method shown in Conductor Diameter, Section 200 of UL 1581.

8.2 Compressed unilay copper conductors that are smaller in diameter than the requirement (0.98 x nominal as indicated in Table 20.3 of UL 1581) for compressed concentric-lay conductors shall be marked the same as compact conductors in accordance with 70.1(n).

9 Stranding

9.1 Each conductor shall be solid: concentric-lay-stranded (in this standard, this term includes compressed-stranded and compact-stranded), with at least the number of strands indicated in Table 9.1, or shall be rope-lay-stranded. The outer layer shall be left-hand in all cases. Copper wires (strands) smaller than 36 AWG (0.005 inch or 0.127 mm in diameter) and aluminum wires (strands) smaller than 22 AWG (0.0253 inch or 0.642 mm in diameter) shall not be used.

Table 9.1
Conductor stranding

Conductor size	Number of strands in combination unilay	Minimum number of strands	
		Compact stranded	All others
8 AWG	19 ^a	7	7
7	—	7	7
6 – 2	19	7	7
1 – 4/0	19	18	19
213 – 500 kcmil	—	35	37
501 – 1000	—	58	61
1001 – 1500	—	—	91
1501 – 2000	—	—	127

^a Copper only

^b Conductors with a lesser number of strands shall be permitted based on the results of an investigation which shall include testing for connectability and bending.

9.2 A compact-stranded conductor shall be a round conductor consisting of a central core wire (one or more strands) surrounded by one or more layers of helically laid (strands). A compact-stranded copper conductor shall consist of uncoated strands. Compact-stranded aluminum conductor and compact-stranded copper conductor shall have all layers with the same direction of lay (unidirectional) or shall have the direction of lay reversed in adjacent layers (concentric-lay-stranded). Each layer shall be rolled, drawn, or otherwise compressively formed to change the originally round strands to various close-fitting shapes

that achieve almost complete filling of the spaces originally present between the strands. Each compacted layer – including the outermost layer – shall have a smooth, round outer surface. The length of lay of the strands in the outer layer of a 1 AWG – 1000 kcmil conductor shall be 8 – 16 times the overall diameter of that layer. The length of lay of the strands in the outer layer of an 8 – 2 AWG conductor shall be 8.0 – 17.5 times the overall diameter of that layer. A compact-stranded conductor shall not be segmented.

9.3 A compressed-stranded conductor shall be a round conductor consisting of a central core wire (one or more strands) surrounded by one or more layers of helically laid (strands) having the unilay construction, the unidirectional lay construction, or with the direction of lay reversed in successive layers. The strands of one or more layers shall be slightly compressed by rolling, drawing, or other means to change the originally round strands to various shapes that achieve filling of some of the spaces originally present between the strands.

9.4 A 19-wire combination round-wire unilay-stranded soft-annealed copper or an acceptable aluminum alloy conductor shall be round and shall consist of a straight central wire, an inner layer of six wires of the same diameter as the central wire with the six wires having identical lengths of lay, and an outer layer consisting of six wires of the same diameter as the central wire alternated with six smaller wires having a diameter of 0.732 times the diameter of the central wire and with all twelve wires of the outer layer having the same length of lay and direction of lay as the six wires of the inner layer.

9.5 Concentric-lay-stranded coated or uncoated annealed copper conductors (including compressed conductors) shall comply with the applicable parts of ASTM B 8. Compact round concentric-lay-stranded uncoated copper conductors shall comply with the applicable parts of ASTM B 496.

9.6 Concentric-lay-stranded aluminum conductors (including compressed conductors) shall comply with the applicable parts of ASTM B 231. Compact stranded aluminum shall comply with the applicable parts of ASTM B 400.

9.7 The length of lay in only the outer layer of a 1 AWG – 1000 kcmil round compact-stranded conductor shall neither be less than 8 nor more than 16 times the overall diameter of that layer. The length of lay of the strands in the outer layer of a 8 – 2 AWG compact-stranded conductor shall be 8.0 – 17.5 times the overall diameter of that layer. The direction of lay of the outer layer shall be left-hand.

9.8 Every stranded conductor other than a compact-stranded conductor shall comply with the following:

a) The direction of lay of the strands, members, or ropes in a 6 AWG – 2000 kcmil conductor other than a combination unilay, compressed unilay, or compressed unidirectional lay conductor shall be reversed in successive layers. Rope-bunched lay and rope-concentric lay conductors shall be either unidirectional or reversed.

b) For a bunch-stranded member of a rope-lay-stranded conductor in which the members are formed into rope-stranded components that are then cabled into the final conductor, the length of lay of the individual strands within each component shall not be more than 30 times the outside diameter of one of those members.

c) For a concentric-stranded member of a rope-lay-stranded conductor, the length of lay of the individual strands in a member shall be 8 – 16 times the outside diameter of the member. The direction of lay of the strands in each member shall be reversed in successive layers of the member.

d) The length of lay of the strands in both layers of a 19-wire combination round-wire unilay-stranded copper or aluminum conductor shall be 8 – 16 times the outside diameter of the completed conductor. Otherwise, the length of lay of the strands in every layer of a concentric-lay-stranded conductor consisting of fewer than 37 strands shall be 8 – 16 times the outside diameter of that layer.

e) The length of lay of the strands in the outer two layers of a concentric-lay-stranded conductor consisting of 37 or more strands shall be 8 – 16 times the outside diameter of the conductor.

f) The length of lay of the members or ropes in the outer layer of a rope-lay-stranded conductor shall be 8 – 16 times the outside diameter of that layer.

10 Strand Filler

10.1 A moisture-excluding filler material is acceptable in the interstices of the inner layers of the conductor strands for the purpose of keeping moisture from entering the cable. Such a material shall be investigated and found acceptable. The investigation shall consist of testing to determine that the material does not have a detrimental effect on either of the following:

a) The conductor stress relief layer – The test is described in the Insulated Cable Engineers Association Publication T-32-645, 1993 “Guide for Establishing Compatibility of Sealed Conductor Filler Compounds with Conducting Stress Control Materials”.

b) The ability to properly terminate the cable as intended – The tests are described in the Standard for Wire Connectors, UL 486A-486B. These tests could include one or all of the following: secureness, heating, pullout, and cyclic heating.

11 Metal Coating

11.1 If the insulation or other material adjacent to a copper conductor corrodes unprotected copper in the test in [32.1](#), each of the individual strands of that conductor shall be separately covered with a metal coating that complies with [6.1](#).

11.2 In the case of a copper conductor on whose wires a coating is not needed for corrosion protection but is used, it is acceptable to coat only the wires of the outer layer (see [7.1](#)) or to coat all of the wires. The metal coating used shall comply with [6.1](#).

12 Joints

12.1 A joint in one of the individual wires (strands) shall be made in a workmanlike manner, shall not change the diameter of the wire (strand) or of the overall conductor, and shall not lessen the mechanical strength or impair the flexibility of the overall conductor. A joint shall not be made in the stranded conductor as a whole but, for other than a rope-lay-stranded conductor (see [12.2](#)) shall be made by separately joining each individual wire (strand) in a manner that does not increase the overall diameter of the entire stranded conductor. A joint in a compact-stranded or compressed-stranded conductor shall be made before compacting or compressing. A joint in any conductor shall be made before the conductor-stress-relief material, the insulation, and other coverings are applied.

12.2 In a rope-lay-stranded conductor consisting of a central core surrounded by one or more layers of stranded members (primary groups), each member may be considered to be equivalent to a solid wire and, as such, may be spliced as a unit. These joints are to be dispersed throughout the length of the conductor so that the diameter and configuration of the completed conductor are not substantially affected, and so that the flexibility of the completed conductor is not adversely affected thereby. In no case shall these joints be closer together than two lay lengths.

CONDUCTOR STRESS RELIEF (CONDUCTOR SHIELDING)

13 Details

13.1 Conductor stress relief shall be provided on each circuit conductor. It shall be readily removable from the conductor and shall be bonded to the insulation (the tension necessary to remove the stress relief from the insulation is not specified). The conductor stress relief used with XLPE or EPCV insulation shall be of conductive nonmetallic material. The conductor stress relief used with EP or DREP insulation shall be of either conductive or non-conductive nonmetallic material. The conductor stress relief shall comply with [Table 13.1](#) (form), [Table 13.2](#) (thicknesses), and [Table 13.3](#) (material).

13.2 The thickness(es) of a conductive tape used alone, of a conductive or non-conductive extrusion used alone, or of a conductive or non-conductive extrusion plus a conductive tape are to be determined on a full cross section of the conductor shielding produced by cutting a specimen of the finished conductor through perpendicular to its longitudinal axis. All measurements are to be made over the tops of strands or at the impressions left by strands. In the case of a conductive tape used alone, the minimum thickness is to be measured directly by means of one of the following:

- a) A dead-weight dial micrometer having a presser foot 0.250 ± 0.010 inch or 6.4 ± 0.2 mm in diameter and exerting a total of 3.0 ± 0.1 ozf or 85 ± 3 gf or 0.84 ± 0.02 N on the specimen – the load being applied by means of a weight, or
- b) An optical device that is accurate to at least 0.001 inch or 0.01 mm.

In all other cases, the minimum thicknesses are each to be measured directly by means of an optical device that is accurate to at least 0.001 inch or 0.01 mm.

13.3 The volume resistivity of the finished conductive conductor shielding taken as a unit shall comply with [44.1](#). The relative permittivity and the dielectric withstand stress of specimens of the non-conductive conductor stress control shall comply with [45.1](#).

Table 13.1
Conductor shielding

Voltage ratings	Construction of conductor stress relief
2400, 5000, 8000, and 15000	A conductive or non-conductive extrusion of any insulation or jacketing material mentioned in Section 14 or 27 directly on the conductor or Overlapping ^a conductive tape covered by a conductive or non-conductive extrusion of any insulation or jacketing material mentioned in Section 14 or 27 or Overlapping ^a conductive tape alone
25000, 28000, and 35000	A conductive or non-conductive extrusion of any insulation or jacketing material mentioned in Section 14 or 27 directly on the conductor or Overlapping ^a conductive tape covered by a conductive or non-conductive extrusion of any insulation or jacketing material mentioned in Section 14 or 27
^a The amount of overlap is not specified.	

Table 13.2
Thicknesses of conductor stress relief

Material	Minimum thickness at any point ^a
Conductive tape of any convenient width applied with an unspecified overlap directly to the conductor	2.5 mils or 0.06 mm
A conductive extrusion of any insulation or jacketing material mentioned in Section 14 or 27 over the above-mentioned tape or directly on the conductor.	6 mils or 0.15 mm
The properties of the material used shall comply with 13.3 when specimens are prepared and tested as indicated in the method to which reference is made in 13.3.	
^a Where both tape and extruded material are used, no reduction is acceptable in any of the specified thicknesses of the tape or extruded material.	

Table 13.3
Properties of extruded conductor stress relief

Property	Value
I. Ultimate elongation (see Section 30 for method) using 1-inch or 25-mm bench marks on specimens that first are die-cut from a specially molded slab that is not more than 0.1 inch or 2.5 mm thick and then are aged as follows in a full-draft circulating-air oven for 168 h at 121.0 ±1.0°C (249.8 ±1.8°F) for 90°C (194°F) cable or at 136.0 ±1.0°C (276.8 ±1.8°F) for 105°C (221°F) cable.	100 percent (minimum)
II. Brittleness temperature by the Acceptance Impact Procedure B described in ASTM D 746 using five die-punched specimens that are 0.25 ±0.02 inch or 6.35 ±0.51 mm wide	-10°C (+14°F) (maximum)
III. Cold – see Section 38 for method	No damage shall result

INSULATION

14 Material, Application, and Centering

14.1 Each circuit conductor shall be insulated for its entire length with a thermoset insulation that complies with Table 14.1 (XLPE), Table 14.4 (EP), Table 14.7 (EPCV), or Table 14.10 [DREP (Discharge Resistant EP)] – see 14.4 for the long-term evaluation of a thermoset insulation material not named in Table 14.1 or 14.4 or not complying with the specified short-term tests. The insulation shall be applied directly to the outer surface of the conductor stress relief and shall be bonded thereto (see 13.1). The insulation shall not have any repairs or joints and shall not have defects (bubbles, open spots, rips, tears, cuts, or foreign material) that are visible with normal or corrected vision without magnification.

14.2 The insulation in 2400 V nonshielded single-conductor cables constructed as indicated in columns A and B of Table 15.3 is not required to be for use in wet locations. Insulation that is for use in wet locations shall be used in all other single-conductor cables and in all multiple-conductor cables other than those consisting of an assembly of the 2400 V nonshielded single-conductor cables constructed without any overall covering as indicated in column A or B of Table 15.3.

14.3 The insulation shall have a circular cross section and shall be applied concentrically about the conductor and the conductor stress relief.

14.4 Either of the following materials that the manufacturer wishes to use as insulation or a jacket shall be evaluated for the requested temperature rating as described in Long-Term Aging, Section 481 of UL 1581:

- a) Material generically different from any insulation material that is named in 14.1 or any – jacket material that is referenced in 19.2, 27.1, or 29.1 (new material).