



# UL 746B

## STANDARD FOR SAFETY

Polymeric Materials – Long Term  
Property Evaluations

[ULNORM.COM](https://www.ulnorm.com) : Click to view the full PDF of UL 746B 2022

[ULNORM.COM](https://www.ulnorm.com) : Click to view the full PDF of UL 746B 2022

UL Standard for Safety for Polymeric Materials – Long Term Property Evaluations, UL 746B

Fifth Edition, Dated August 15, 2018

### **SUMMARY OF TOPICS**

***This revision of ANSI/UL 746B dated October 3, 2022 includes the removal of dated references from ASTM Standards Referenced; [9.1.1](#).***

Text that has been changed in any manner or impacted by UL's electronic publishing system is marked with a vertical line in the margin.

The revised requirements are substantially in accordance with Proposal(s) on this subject dated August 26, 2022.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form by any means, electronic, mechanical photocopying, recording, or otherwise without prior permission of UL.

UL provides this Standard "as is" without warranty of any kind, either expressed or implied, including but not limited to, the implied warranties of merchantability or fitness for any purpose.

In no event will UL be liable for any special, incidental, consequential, indirect or similar damages, including loss of profits, lost savings, loss of data, or any other damages arising out of the use of or the inability to use this Standard, even if UL or an authorized UL representative has been advised of the possibility of such damage. In no event shall UL's liability for any damage ever exceed the price paid for this Standard, regardless of the form of the claim.

Users of the electronic versions of UL's Standards for Safety agree to defend, indemnify, and hold UL harmless from and against any loss, expense, liability, damage, claim, or judgment (including reasonable attorney's fees) resulting from any error or deviation introduced while purchaser is storing an electronic Standard on the purchaser's computer system.

No Text on This Page

[ULNORM.COM](https://ulnorm.com) : Click to view the full PDF of UL 746B 2022

**AUGUST 15, 2018**  
(Title Page Reprinted: October 3, 2022)



**ANSI/UL 746B-2022**

1

**UL 746B**

**Standard for Polymeric Materials – Long Term Property Evaluations**

First Edition – September, 1975  
Second Edition – June, 1979  
Third Edition – August, 1996  
Fourth Edition – April, 2013

**Fifth Edition**

**August 15, 2018**

This ANSI/UL Standard for Safety consists of the Fifth Edition including revisions through October 3, 2022.

The most recent designation of ANSI/UL 746B as an American National Standard (ANSI) occurred on October 3, 2022. ANSI approval for a standard does not include the Cover Page, Transmittal Pages, and Title Page.

Comments or proposals for revisions on any part of the Standard may be submitted to UL at any time. Proposals should be submitted via a Proposal Request in UL's On-Line Collaborative Standards Development System (CSDS) at <https://csds.ul.com>.

UL's Standards for Safety are copyrighted by UL. Neither a printed nor electronic copy of a Standard should be altered in any way. All of UL's Standards and all copyrights, ownerships, and rights regarding those Standards shall remain the sole and exclusive property of UL.

**COPYRIGHT © 2022 UNDERWRITERS LABORATORIES INC.**

No Text on This Page

[ULNORM.COM](https://ULNORM.COM) : Click to view the full PDF of UL 746B 2022

## CONTENTS

### INTRODUCTION

1	Scope .....	5
2	References .....	5
3	Supplementary Test Procedures .....	5
4	Characteristics of Polymeric Materials .....	5
5	Use of Polymeric Materials .....	6

### DETERMINATION OF THE RELATIVE THERMAL INDICES OF POLYMERIC MATERIALS

6	General .....	6
7	Relative Thermal Index – Based Upon Historical Record .....	7
8	Relative Thermal Index – Based Upon Long-Term Thermal-Aging Programs .....	10
9	Apparatus .....	10
	9.1 Ovens .....	10
10	Scope of Test Programs .....	11
	10.1 Selection of test properties .....	11
11	Property-Evaluation Tests .....	12
	11.1 General .....	12
	11.2 Choice of end-point .....	13
12	Sampling Programs .....	13
13	Selection of Oven Temperatures .....	13
14	Selection of Control Material .....	15
15	Specimens .....	15
16	Thermal Aging .....	15
17	End-of-Life .....	18
	17.1 Primary properties .....	18
	17.2 Secondary properties .....	18
18	Proof Testing .....	19
19	Analysis and Evaluation .....	19
20	Related Material – Coverage of Variations in Material Composition .....	25
	20.1 General .....	25
	20.2 Thermoplastic materials .....	25
	20.3 Thermosetting molded materials .....	28
21	Aging, Specimen, and Check-Test Schedules .....	30
	21.1 General .....	30
	21.2 Polypropylene .....	30
	21.3 Coating powders .....	30
22	Fixed Time Sampling Method .....	36
	22.1 General .....	36
	22.2 Screening procedure .....	36
	22.3 Remainder of Fixed Time sampling method .....	37

### DETERMINATION OF THE TEMPERATURE INDICES OF POLYMERIC MATERIALS

22A	General .....	38
22B	Temperature Index – Based Upon Long-Term Thermal-Aging Programs .....	38
22C	Ovens .....	39
22D	Test Program .....	39
	22D.1 Scope, thicknesses .....	39
	22D.2 Sampling programs .....	39
	22D.3 Selection of oven temperatures .....	39
22E	Specimens and Thermal Aging .....	40

22F	Analysis and Evaluation .....	40
22G	Reporting Temperature Indices .....	41

#### RELATIVE THERMAL INDEX CLASS

23	Assignment of Temperature Classifications .....	42
----	---	----

#### MARKING

24	General .....	42
----	---------------	----

#### SUPPLEMENT SA – FOLLOW-UP INSPECTION INSTRUCTIONS

#### INTRODUCTION

SA1	Scope .....	43
SA2	Glossary .....	43
SA3	Responsibility of the Manufacturer .....	44
SA4	Responsibility of the Field Representative .....	44
SA5	Selection of Samples for Follow-Up Testing .....	45
SA6	Follow-Up Test Program .....	45

ULNORM.COM : Click to view the full PDF of UL 746B 2022

## INTRODUCTION

### 1 Scope

1.1 These requirements cover long-term test procedures to be used for the evaluation of materials used for parts intended for specific applications in end products.

1.2 Together with the Standards mentioned in Supplementary Test Procedures, Section 3, these investigations provide data with respect to the physical, electrical, flammability, thermal, and other properties of the materials under consideration and are intended to provide guidance for the material manufacturer, the molder, the end-product manufacturer, safety engineers, and other interested parties.

### 2 References

2.1 Any undated reference to a code or standard appearing in the requirements of this standard shall be interpreted as referring to the latest edition of that code or standard.

### 3 Supplementary Test Procedures

3.1 The Standard for Tests for Flammability of Plastic Materials for Parts in Devices and Appliances, UL 94, covers flammability of polymeric materials used for parts in devices and appliances. The Standard for Polymeric Materials – Short Term Property Evaluations, UL 746A, contains short-term test procedures to be used for the evaluation of materials used for parts intended for specific applications in electrical end products. The Standard for Polymeric Materials – Fabricated Parts, UL 746D, contains requirements for traceability and performance of parts molded and fabricated from polymeric materials.

3.2 Programs for the investigation of material part modifications, such as the plating of plastics or the use of flame-retardant paints, are contained in the Standard for Polymeric Materials – Use in Electrical Equipment Evaluations, UL 746C.

3.3 Data concerning the effect of various environments and contaminants upon the properties of materials can also be obtained through standard test procedures. The more commonly used procedures are briefly described in the Standard for Polymeric Materials – Short Term Evaluations, UL 746A.

3.4 Test procedures are provided in the Standard for Polymeric Materials – Use in Electrical Equipment Evaluation, UL 746C, for the evaluation of polymeric materials in specific applications in end products. These test procedures include references to the data obtained from the standard property tests as well as other practical means of evaluation.

3.5 Requirements for materials that have been modified to match the requirements of a specific application, including the use of recycled and regrind materials, the use of additives and colorants, and the blending of two or more materials, are described in the Standard for Polymeric Materials – Fabricated Parts, UL 746D.

3.6 A method and tool for the statistical analysis of long term property evaluation data and including the determination of a temperature index (TI) is described in Sections 22A – 22J based on the Standard for Electrical insulating materials – Thermal endurance properties – Part 3: Instructions for calculating thermal endurance characteristics, IEC 60216-3.

### 4 Characteristics of Polymeric Materials

4.1 Polymeric materials include thermoplastic, thermosetting, and elastomeric materials. A thermoplastic material can be easily softened and resoftened by repeated heating. A thermosetting material cures by

chemical reaction and, when cured, cannot be resoftened. An elastomeric material is capable of being stretched at room temperature to at least twice its length under low stress and recovers to its original length when released from the stress.

4.2 Characteristics of polymeric materials that necessitate additional consideration include:

- a) Mold stresses
- b) Insulating quality
- c) Resistance to ignition
- d) Extinguishing characteristics
- e) Production of smoke and gases
- f) Mechanical Strength
- g) Compatibility with solvents
- h) Melting or distortion
- i) Cold flow, if under stress
- j) Fuel contribution
- k) Dimensional stability

## 5 Use of Polymeric Materials

5.1 The reduction to an acceptable level of the risks of electric shock, fire, and personal injury from electrical equipment depends upon the selection of materials, design, and processing of parts as well as the assembly, mounting, and relative positions of these parts.

5.2 The properties needed by individual parts are defined by the function or functions of the part. An enclosure, for example, must ordinarily be designed to withstand mechanical abuse. Accordingly, a material known to have substantial impact strength would normally be used although a material that has a lower impact strength, but is reinforced, might also be acceptable.

5.3 Electrical equipment of necessity employs many materials that usually have divergent properties. The ability to match the demands of the application with the characteristics of a material as well as the ability to compare the properties of one material with those of another can lead to an acceptable selection of materials.

5.4 The information gained from the data obtained from these tests can be used as an aid in the evaluation of electrical equipment using parts made of polymeric materials. Knowledge of materials can be obtained from an analysis of data from standard tests conducted on small specimens.

## DETERMINATION OF THE RELATIVE THERMAL INDICES OF POLYMERIC MATERIALS

### 6 General

6.1 A relative thermal index of a material (RTI) is an indication of the material's ability to retain a particular property (physical, electrical, etc.) when exposed to elevated temperatures for an extended period of time. It is a measure of the material's thermal endurance. For each material, a number of relative